



# 检

验

报

告

TEST REPORT

中心编号(No.): 201606AW233

样品名称: 蒸压粉煤灰砖
Sample Name

委托单位: 北京嘉诚兴业建材有限公司

Client

检验类别: 本本的 委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



(国家)建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201606AW233

第1页共2页

			77 1 25 25				
样品名称	蒸压粉煤灰砖	检验类别	委托检验				
委托单位	北京嘉诚兴业建材有限公司	商标					
生产单位	北京嘉诚兴业建材有限公司	等级	MUI0 级				
生产日期		样品编号	超级				
来样日期	2016年06月29日	规格型号	AFB 190mm×90mm×53mm				
样品数量		样品状态	块状, 外观完好				
检验依据	GB 11945-1999《秦压灰砂砖》						
检验项目	1. 就在羅皮。1950年1950年1950年1950年1950年1950年1950年1950年						
检验结论	*经检验,送检样品的抗压引中 MU10 强度级别的技术指标要	米。* 发日期; <b>2016</b>	符合标准 GB 11945-1999 年 07 月 05 日 金验测试章)				
备注:(此处空旬)							

#### (国家)建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201606AW233

第2页共2页

序号	检验项目	标准要求 (MU10 强度级别)		检验结果		单项 结论
語	抗压强度/MPa	平均值	学块值。	平均值	单块值	
紹		≥10.0	≥8.0	12.0	F10.07	合格

(以下空白)

备注: (此处空白)

### 说明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
  This test report is invalid if crased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作目内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伤纸张,复印后应带有网络底纹。
  This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code): 100024

电话(Tel):(010)51164723 51164718

传真(Fax):(010) 51164724

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com