

150002283084



# 验报告

TEST REPORT

中心编号(No.): 201706AW194

样品名称:一个、轻集料混凝土小型空心砌块

Sample Name

委托单位。 保定中拓远扬水泥制品制造有限公司

Client

9769767多种检验 检验类别:

Test Type

日国家广建筑材料工业技术监督研究中心

建筑材料工业干湿砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



(国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

第1页共2页 中心编号(No.): 201706AW194 样品名称一条集料混凝土小型空心砌块 检验类别 委托检验 委托单位一保定中福远杨水泥制品制造有限公司 商 标 等 生产单位 900级 保定中格远扬水泥制品制造有限公司 级 MU3.5 生产日期 样品编号 规格型号 来样日期 2017 年 06 月 09 1 400mm×200mm×180mm 样品状态 块状 样品数量 10块 检验依据 GB/T 15229-2011《轻集料混凝土小型室心砌块》 检验项目,从密度等级口 2. 抗压强度 \*经检验, 送检样品的密度等级的检验结果符合标准 GB/T 15229-2011 中密度等级 900 级的技术指标要求: 抗压强度的检验结果符合标准 GB/T 15229-2011 中强度等级 MU3.5 的技术指标要求。\* 检验结论 签发日期 2017年06月26日 生(检验测试量) 备注:(此处空台)

审核: 大多 悠編 制: 共享 准: #

#### (国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.):-201706AW194

序号。一个检验项目	标准要求	检验结果	单项结论
密度等級/(kg/mi) (密度等級 900 級)	≥810, ≤900	890	
から 大 大 大 大 大 大 大 大 大 大 大 大 大	<b>奔均便</b> 最小值	来均值,最小值	
7. 1. 1. 1. 1. 1. 1. 1. 1. 1. 1. 1. 1. 1.	≥3.50 ≥2.8	3.6	

(山空中)

备注:(此处空句)

### 说。公明

#### Notice

- C 本报告无由心"检验测试章"和骑锋章无效。
  This test report is invalid without the seal.
- 2、本报告无少编制、审核、批准"签字宏效。
  This test report is invalid without the signatures of the related persons.
- 3个本报告徐改一部分复印历效。
  - This test report is invalid if erased, altered or copied partially.
- - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委託检验样品和委托信息由委托入提供,中心不对真实性负责,委托检验结果仅对来撤负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伤纸张、复印后应带有网络底纹。
  This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地加(Address)、此京市朝阳区管电东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code)。100024

电話(TeD: (010) 51164723 51164718

传真(Bax):(010) 51164724

报告真伪查询(Tel);(010)51164716

网址 (Web): http://www.dmtc.org.cm/

电子邮箱(E-mail): dmtc2007ai163.com



