



检验报告

TEST REPORT

中心编号(No.): 201601DW114

三江八红色

样品名称:	品名称: 南极海硅藻泥 (内墙)					
Sample Name						
委托单位:	北京南极海新材料股份有限公司					
Client						
检验类别:	委托检验					
Test Type						

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(1	No.): 201601DW114	第	1页共2页			
样品名称	南极海硅藻泥 (内墙)	检验类别	委托检验			
委托单位	北京南极海新材料股份有限公司	商标	南极海			
生产单位	北京南极海新材料股份有限公司	等级				
生产日期		样品编号				
来样日期	2016年01月13日	规格型号				
样品数量	5kg	样品状态	粉状。			
检验依据	GB 8624-2012《建筑材料及制品燃烧性能分级》					
检验项目	1. 燃烧性能等级					
检验结论	*经检验,送检样品的燃烧性 8624-2012 中燃烧性能等级 A(A1)级	的技术指标要求 签发日期: 2	。* 016年93月04日			
路等路	\$P\$		(检验测试章)			

备注: (此处空白)

批准:例如

核: 75年

编制:



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201601DW114

第2页 共2页

序号	检验项目		标准要求	检验结果	单项结论
		炉内温升℃	€30	23	合格
燃烧性 能等级 A (A1) 级	质量损失率/%	€50	21415	合格	
	持续燃烧时间/s	9		合格	
	总热值/(MJ/kg)	€2.0	0.7	合格	

(以下空白)

备注: (1) 配比: 粉:水=1.0:1.2;

(2)燃烧性能等级试验结果只与制品的试样在特定试验条件下的性能相关,不能 作为评价该制品在实际使用中潜在火灾危险性的唯一依据。

邮编: 100024

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.

本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.

4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.

本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>dmtc2007@163.com</u>