





检验报告

TEST REPORT

中心编号(No.): 201212FW124

样品名称:	高性能复合阻锈防腐剂		
Sample Name			

委托单位: 山西鸿伟益达建材科技有限公司

Client

检验类别: 委托检验

Test Type



Technical Supervision and Research Center of the Building Materials Industry





检验报告

TEST REPORT

中心编号(No.): 201212FW124

第1页共2页

中心编亏(NO.): <u>201212F W124</u>		THA THURSDAY	W. 12 V. 2			
样品名称	高性能复合阻锈防腐剂		检验类别	委托检验		
委托单位	山西鸿伟益达建材科技有限公司		商标			
生产单位	山西鴻伟益达建材科技有限公司		样品状态	粉状, 无结块		
生产日期			生产批号			
来样日期	2012年12月24日		样品编号			
样品数量	10kg		规格型号	HD-10		
检验依据	JC/T 1011-2006《混凝土抗硫酸盐类侵蚀防腐剂》					
检验项目	1.比表面积 4.膨胀率 7.氧化镁	2.凝结时间 5.抗蚀系数 8.氯离子	3.抗压强度比 6.膨胀系数 9.碱含量			
检验结论	*经检验,送检粒 蚀系数、膨胀系数、氧 中抗硫酸盐类侵蚀防	腐剂的技术指标要求	量的检验结果符。* * 发日期: 2013	度比、膨胀率、 - 合 JC/T 1011-200 年 04 月 08 日 验测试章)		

备注:(此处空白)

批准:分野

审核: 王英双

编制:



电话: 010-51164723

邮编: 100024



(国家)建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

检验报告

TEST REPORT

中心编号(No.): 201212FW124

第2页共2页

序号	检验项目		标准要求 (抗硫酸盐类侵蚀防腐剂)	检验结果	单项结论
記	比表面积/m²/kg		≥300	490	合格
2	凝结	初凝/min	≥45	202	合格
	时间	终凝/h	≤10	200 4 5 5 6	合格
	抗压强	7d	>90 €	123	合格
	度比/%	28d	≥100	132	合格
4 膨胀率 /%	膨胀率	ld	≥0.05	0.088	合格
	/%	28d	€0.60	0.185	合格
55	抗蚀系数(K)		≥0.85	1.0	合格
6	膨胀系数(E)		≤1.50	1.14	合格
7	氧化镁/%		≤5.0	2.7	合格
8	氯离子/%		≤0.05	0.019	合格
9	磁含量/%		≤0.60	0.32	合格

备注: 试验时,高性能复合阻锈防腐剂的掺量为内掺 4%。

说明

Notice

- 本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if crased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期恕不 受理。
 - Any doubt should inform us within 15 days after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164723 51164718

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>sj13146197542@126.com</u>

