



检验报告

TEST REPORT

中心编号(No.): 201611AW008


丁川川广

样品名称:	蒸压加气混凝土砌块
Sample Name	
委托单位:	保定信丰瑞通建材有限公司
Client	
检验类别:	委托检验
Test Type	

国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortan





150002283084 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201611AW008

第1页 共2页

1.00000	201011AW008		弗 1 贝 共 2 贝			
样品名称	蒸压加气混凝土砌块	检验类别	委托检验			
委托单位	保定信丰瑞通建材有限公司	商标	1446年			
生产单位	保定信丰瑞通建材有限公司	等 级	B07 A5.0			
生产日期		样品编号	非程序程			
来样日期	2016年11月14日	规格型号	600mm×250mm×150mm			
样品数量	6块	样品状态	块状			
检验依据	GB 11968-2006《蒸压加气混凝	土砌块》				
检验项目	1. 干密度 2. 立方体抗压强度					
检验结论	*经检验,送检样品的干密 B07 级-合格品的技术指标要求 GB 11968-2006 中 A5.0 级的技术	: 立方体抗压	合标准 GB 11968-2006 中 强度的检验结果符合标准			
		The Control of the Co	6年11月24日 检验测试章			

制: 书.克

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201611AW008

第2页 共2页

序号	检验项目	(B07 级-合格品)		检验结果 710		单项 结论 合格
1	千密度/ (kg/m³)					
2	立方体抗压强度/MPa (A5.0 级)	平均值	单组 最小值	平均值	单组 最小值	合格
		≥5.0	≥4.0	5.1	5.0	

(以下空白)

电话: 010-51164723

邮编: 100024

备注:(此处空白)

说 明

Notice

- 本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



