





检验报告

TEST REPORT

中心编号(No.): 201201AC142

样品名称:	子的人工。一名杨板工工,1000年1100年1100日
Sample Name	
受检单位: Client	廊坊富尔达化工建材有限公司
检验类别:	指样检验

国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201201AC142

第1页共2页

T >11 -2 (T.	(0.): 2012017(C142		# 1 X 7 4 X		
产品名称	岩棉板	检验类别	抽样检验		
受检单位	廊坊富尔达化工建材有限公司	产品批号	Service Bless		
生产单位	廊坊宫尔达化工建材有限公司	生产日期	201] 年12月		
抽样地点	企业成品库房	商标	建筑研究		
抽样人	陈嘉宇、苏充	规格型号	(1000×600×50) mm		
抽样日期	2012年01月28日	抽样数量	8块		
样品状态	被张 3 F X 5 3 C F 6 F 2 X 5	抽样基数	30m ³		
抽样单位	建筑材料工业干混砂浆产品质量监督检验测试中心				
检验依据	GB/T 11835-2007《绝热用岩棉、矿造棉及其制品》				
检验项目	1. 纤维平均直径 2. 渣球含量 5. 密度 6. 导热系数 9. 有机物含量 10. 吸湿率	The second of th	4. 尺寸允许偏差 8. 热荷重收缩温度		
检验结论	*经检验,抽检样品所见项目标 板的密度等级(101-160) kg/m 签	3的技术指标要			

备注: (此处空白)

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201201AC142

第2页共2页

序号	检验项目		标准要求	检验结果	单项结论
	纤维平均直径/µm		<7.0 ≤7.0	5.2	合格
2	造球合量 (粒径大于 0.25mm)/%		≤10.0	8.0	合格
35	外观质量		表面平整,不得有妨碍使用的伤痕,污迹、破损。	表面平整、无伤痕、 污迹、破损	合格
	尺寸允	长度	3~+15	0 ~ +4	合格
040	许偏差	宽度	25 0 3 - +5 5 5 3	0~+3	合格
	/mm	厚度	3-15-02	0 -+1	合格
5	密度/ (kg/m³)		101 - 160	155	合格
6	平热系数 (平均温度 70 ° ℃), W/(m·K)		≤ 0.043	0.041(平均温度 70.00℃)	合格
7	燃烧性能			不燃材料	合格
8	热荷重收缩温度/°C		≥ 600	600	合格
9	有机物含量/%		€4,0	33	合格
10	吸湿率%		€5,0	3.5	合格
tir	槽水率/%		>98.0	98.0	合格

备注: (此处空白)



电话: 010-51164723

说明

Notice

- 本报告无中心"检验测试章"和崭缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if crased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期怨不 受理。

Any doubt should inform us within 15 days after receiving the test report.

- 5、委託检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真(Fax):(010)51164723 51164718

Mh (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): sj13146197542@126.com