



检验报告

REPORT TEST

中心编号(No.): 201706AW143

样品名称:

聚合物粘结砂浆

Sample Name

委托单位: 北京鑫臣佳业建筑材料有限公司

Client

检验类别:

委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Conter for Quality Supervision and Test of Dry-mixed Mortar







(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

第1页共2页 中心编号(No.): 201706AW143 检验类别 委托检验 样品名称 聚合物粘结砂浆 商 委托单位 北京鑫巨佳业建筑材料有限公司 标 生产单位 等 北京鑫巨佳业建筑材料有限公司 级 生产日期 样品编号 规格型号 来样日期 2017年06月05日 干粉型 样品状态 样品数量 粉状 20kg 检验依据 JG 149-2003《膨胀聚苯板薄抹灰外墙外保温系统》 检验项目 1. 拉伸粘接强度(与水泥砂浆) *经检验,送检样品的拉伸粘接强度(与水泥砂浆)的检验结果符合 标准JG149-2003 中胶粘剂的技术指标要求。 检验结论 签发日期:2017年07月05日 (检验测试量) 备注:(此处空百)

批准: Cano

检验单位地址:北京市朝阳区管庄中国建材院内北楼 电话:010-51164723 邮编:100024

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201706AW143

第2页共2页

序。检验项目		标准要求 (股粘剂)	检验结果	单项结论
拉伸粘接强度 12 (当水混砂浆)	原强度	≥0.60	0.85	
HO TO MPA		≥0.40	0.67	

备注:配比:粉:水4:1。

说 明

Notice

- 八、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 21 本报告无广编制,审核、批准"八签字无效。 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起中五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托太提供,中心不对真实性负责,委托检验结 果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 71 本报告采用防伪纸张,复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code):100024

电话(Tel):(010) 51164723 51164718

传真(Fax):(010) 51164724

报告真伪查询(Tel):(010) 51164716

网址 (Web): http://www.dmtc.org.en/

电子邮箱(E-mail): dmtc2007@163.com



