





# 检验报告

TEST REPORT

中心编号(No.): 201302AC036

样品名称:	HM-耐水腻子				
Sample Name					
受检单位: Client	北京华美筑诚建材有限公司				
检验类别:	抽样检验				
Test Type					

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201302AC036

第1页共2页

中心编号(	No.): 201302AC036	第1 以 共 4 以			
产品名称	HM-耐水腻子	检验类别	抽样检验		
受检单位	北京华美筑诚建材有限公司	产品批号			
生产单位	北京华美筑诚建材有限公司	生产日期	2013年01月		
抽样地点	企业成品库房	商标	华美		
抽样人	陈嘉宇 苏亮	规格型号	干粉型		
抽样日期	2013年02月07日	抽样数量	20kg		
样品状态	粉状,无结块	抽样基数	51 23		
抽样单位	建筑材料工业干混砂浆产品质量监督检验测试中心				
检验依据	JG/T 298-2010《建筑室内用腻子》				
检验项目	1. 粘结强度				
检验结论	*经检验,抽检样品的粘结的中耐水型(N)的技术指标要求。		04月01日		

备注: (此处空白)

批准: 分型

审核: 文英机

编制:

带

检验单分地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024

#### (国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201302AC036

第2页 共2页

序号	检验项目		标准要求 [耐水型(N)]	检验结果	单项结论
	HALZE À AO	标准状态	> 0.50	0.70	合格
	粘结强度,MPa	浸水后	> 0.30	0.54	合格

(以下空白)

备注: 配比: 粉: 水=1: 0.40。

### 说明

### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
  This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期恕不 受理。

Any doubt should inform us within 15 days after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告采用防伪纸张,复印后应带有网络底纹。
This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164723 51164718

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): sj13146197542@126.com