



检验报告

TEST REPORT

中心编号(No.): 201606AW236

样品名称:	GRC 制品		
Sample Name			
委托单位: Client	北京隆诚装饰材料厂		
检验类别: Test Type	委托检验		

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201606AW236

第1页共2页

		HILL THE		
样品名称	GRC 制品	检验类别	委托检验	
委托单位	北京隆诚装饰材料厂	商一标		
生产单位	北京隆诚装饰材料厂	等级	33333	
生产日期	認認認認	样品编号		
来样日期	2016年06月29日	规格型号		
样品数量		样品状态	块状	
检验依据	JC/T 940-2004《玻璃纤维增强水泥(GRC)装饰制品》			
检验项目	1. 抗压强度(面外) 2. 抗拉极限强度			
	*经检验,送检样品的抗压。 符合标准 JC/T 940-2004 中喷射二			
检验结论			最 数款法	
54976		发日期: 2016年		
TA ALISA			Section 1	

备注:(此处空白)

批准是如2 审核: 近日

编制: 苏亮



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201606AW236 第 2 页 共 2 页

序号	检验项目	标准要求 [喷射エ艺(含 格品)]	检验结果	单项结论
第	抗压强度(面外),MPa	≥40	43	合格
2	抗拉极限强度, MPa			合格

(以下空白)

备注:(此处空白)

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com

