



检验报告

TEST REPORT

中心编号(No.): 201704DW005

DINIE

样品名称:	瓷砖粘结剂			
Sample Name		1		
委托单位: Client	北京合木粘合剂厂	THE		
检验类别:	委托检验			
Test Type				

建筑材料工业技术监督研究中心

建筑材料工业于混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201704DW005

第1页共2页

		和1以六人以			
瓷砖粘结剂	检验类别	委托检验			
北京合木粘合剂厂	商标	华鹏			
北京合木粘合剂厂	等 级				
	样品编号	1948E			
2017年04月19日	规格型号	CI			
20kg	样品状态	粉状			
JC/T 547-2005《陶瓷墙地砖胶粘》	N)				
1. 拉伸胶粘原强度 2. 浸水后的拉伸胶粘强度					
经检验,送检样品的拉伸胶验结果符合标准 JC/T 547-2005 中	粘原强度、浸水点 普通型胶粘剂 (后的拉伸胶粘强度的检 C1)的技术指标要求。			
	10-11-	ALL TO			
THE RESERVE THE PROPERTY OF THE PERSON OF TH	北京合木粘合剂厂 北京合木粘合剂厂 2017年04月19日 20kg JC/T 547-2005《陶瓷墙地砖胶粘料 1. 拉伸胶粘原强度 2. 浸水*经检验,送检样品的拉伸胶	北京合木粘合剂厂			

批 准:

制:

邮编: 100024

北京市朝阳区管庄中国建材院内北楼

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201704DW005

第2页 共2页

序号	检验项目	标准要求 (C1)	检验结果	单项结论
i	拉伸胶粘原强度/MPa	≥0.5	1.0	合格
2	浸水后的拉伸胶粘强度/MPa	≥0.5	0.9	合格

(以下空白)



备注: 配比: 粉:水=1.0:0.20。

说明

Notice

- 本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com

