





# 检验报告

TEST REPORT

中心编号(No.): 201303AW157

样品名称:	干混地面砂浆		
Sample Name			
委托单位: Client	福建省连江县新天地建材有限公司		
检验类别:	委托检验		
Test Type			

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





#### (国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201303AW157

第1页共2页

1 7 7 10 7 7	10.). <u>20130371W137</u>		1 1 1 1 1 1		
样品名称	干混地面砂浆	检验类别	委托检验		
委托单位	福建省连江县新天地建材有限公司	商标			
生产单位	福建省连江县新天地建材有限公司	等级	M25		
生产日期	2013年03月02日	样品编号	20130302		
来样日期	2013年03月08日	规格型号	50kg/袋		
样品数量	20kg	样品状态	粉状,无结块		
检验依据	JG/T 230-2007《预拌砂浆》				
检验项目	1. 强度等级 2. 凝结时间 3. 保水性				
检验结论	*经检验,送检样品的强度等级、标准 JG/T 230-2007 中 M25 干混地面签发 E	砂浆的技术指 到期: 2013 年			

备注: (此处空白)

批准: Story

审核: 子基奶

编制:

黄

检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



## (国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201303AW157

第2页共2页

序号	检验项目	标准要求 (M25 干混地面砂浆)	检验结果	单项结论
	强度等级/MPa	M25	26.9	合格
2	凝结时间度/h	3~8	4.75	合格
3	保水性/%	≥88	89	合格

(以下空白)

备注: 配比: 粉:水=1:0.12。

电话: 010-51164723

邮编: 100024

## 说明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
  This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期怨不 受理。

Any doubt should inform us within 15 days after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告采用防伪纸张,复印后应带有网络底纹。
This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164723 51164718

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): sj13146197542@126.com

