



2012003084M

存档

## TEST REPORT

(Report No.): 201412DW131(E)

201412DW131(E)

Sample Name: PVC Woven Carpet

Client: Shanghai Hanfei Industry Co., Ltd

Test Type: Authorized Testing

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



(国家) 建筑材料工业技术监督研究中心  
Technical Supervision and Research Center of the Building Materials Industry





(国家) 建筑材料工业技术监督研究中心

2012003084M

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## TEST REPORT

(Report No.): 201412DW131(E)

Page 1 of 2

Sample Name	PVC Woven Carpet	Test Type	Authorized Testing
Client	Shanghai Hanfei Industry Co.,Ltd	Trademark	G+
Manufacturer	Shanghai Hanfei Industry Co.,Ltd	Grade	—
Production Date	30 <sup>th</sup> November,2014	Sample No.	—
Sample Date	9 <sup>th</sup> December,2014	Specification	50cm×50cm
Sample Quantity	10	Sample Status	Block
Testing Standard	“Classification for burning behavior of building materials and products”,GB 8624-2012		
Test Content	I. Combustion Performance Grade		
Test Conclusion	<p>* The test result of combustion performance meets the technical requirements of flooring materials grade B<sub>1</sub>(C) in the standard of GB 8624-2012.*</p> <p>Reported Date: 4<sup>th</sup> January, 2015 (Test Stamp)</p>		
Remark: (blank area)			

Reported by: [Signature]

Checked by: [Signature]

Authorized by: [Signature]

Address: North building of China Building Materials Academy, GuanZhuang, ChaoYang district, Beijing  
Tel:010-51164723 Postcode:100024



(国家)建筑材料工业技术监督研究中心  
Technical Supervision and Research Center of the Building Materials Industry



(国家) 建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

### TEST REPORT

(Report No.): 201412DW131(E)

Page 2 of 2

No.	Test Content		Standard	Test	Single
			Request	Result	Conclusion
1	Combustion Performance	20s Flame Height /mm	$\leq 150$	124	Qualified
	Grade B <sub>I</sub> (C)	Critical Heat Flux /(kW/m <sup>2</sup> )	$\geq 4.5$	4.5	Qualified

(blank below)

Remark: Combustion performance test result is only related to the performance of the sample under the specific test conditions, which is not intended to serve as the sole evaluation criteria for the potential fire hazard in actual use.

Address: North building of China Building Materials Academy, GuanZhuang, ChaoYang district, Beijing  
Tel:010-51164723 Postcode:100024



(国家)建筑材料工业技术监督研究中心  
Technical Supervision and Research Center of the Building Materials Industry