

150002283084

验搜告

TEST REPORT

中心编号(No.): 201706AW206

样品名称: 树池口

Sample Name

委托单位: 北京市顺义区北小营仇家店水泥制品厂

Client

检验类别: 委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar









(国家)建筑材料工业技术监督研究中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201706AW206

第1页共2页

样品名称		检验类别	\$ 100 mm			
委托单位	北京市顺文区北小营仇家店水泥制品厂	商。标				
生产单位	北京市顺义区北小营仇家店水泥制品厂	等级	G30 B B B B B B B B B B			
生产日期	2017年04月03日	样品编号				
来样日期	2017年06月13日	规格型号	1400mm×160mm×120mm			
样品数量		样品状态				
检验依据	GB/T 50081-2002《普通混凝土力学性能试验方法标准》					
检验项目	できてきなっている。 1. 表に変を 1. までまれる。 1. までまたな。 1. までな。 1. までな。 1. までなる。 1. ま					
	依据标准 GB/T 50081-2002 规定的试验方法进行检验,送检样品的抗压强度的检验结果见第 2 页。					
检验结论	签发日期: 2017年 06 月 19 日 (检验测试章)					
备注。如此学的 中华中华中华中华中华中华中华中华中华中华中华中华中华中华中华中华中华中华中华						

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201706AW206

第2页共2页

4	序号	金项 自	标准要求	12 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2	结果。	单项结论
1		度,MPa			192	

(以下空白)

备注:(此处室自)

说 明

Notice

- 1、不报告无中心"检验测试章"和骑缝章无效。
 - This test report is invalid without the seal.
- 2、本报告无广编制、审核、批准"签字无效。
 - This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
 - This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起于五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托入提供,中心不对真实性负责,委托检验结 果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying autherficity of the supplied samples and information is out of our responsibility.
- 本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address),北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code):□100024

电话(Teld: (010) 51164723 51164718

传真(Fax):(010)51164724

报告真伪查询(Tel):(010)51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱(E-mail): dmtc2007@163.com



