





检验报告

TEST REPORT

中心编号(No.): 201209AW031

TIME

样品名称:	砌筑粘结剂		
Sample Name			
委托单位: Client	北京团河同心装饰材料厂		
检验类别:	委托检验		
Test Type			

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



MA

2009003084M 国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201209AW031

第1页共2页

アルン州った	(O.): <u>2012027111001</u>		STOR BUILDING CO.	
样品名称	砌筑粘绵剂	检验类别	委托检验	
委托单位	北京国河间心装饰材料厂	商标		
生产单位	北京团河周心装饰材料厂	样品状态	粉状	
生产日期		生产批号		
来样日期	2012年09月27日	样品编号		
样品数量	10kg	规格型号	干粉型	
检验依据	JG/T 230-2007《预拌·砂浆》			
检验项目	1. 强度等級 2. 凝结时间 3. 保水性			
检验结论	*经检验、送检样品的强度等级、凝结时间、保水性的检验等果符合标准 JG/T230-2007 中 M7.5 干混砌筑砂浆 (DM) 的技术推标要求。* 签发日期: 2012年。11.月 706日 (检验测试章)			

备注:(此处空台)

批准:分加了

审核: 最七新编制: 了的

检验单位地址:北京市朝阳区管庄中国建材院北楼

电话: 010-51164723

邮编: 10002

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201209AW031

第2页 共2页

序号	检验项目	标准要求	检验结果	单项结论
i	强度等级	M7.5	7.8MPa	合格
2	凝结时间/h	3~8	4.25	合格
3	保水率/%	>88	90	今 格

(以下空白)

备注: 配比: 粉: 水=1: 0.18.

说明

Notice

- 1、本报告无中心"检验测试量"和特缝章无效 This test report is invalid without the seal.
- 2、本报告光 "编制、审核、批准" 签字无效。
 This test report is invalid without the signatures of the related persons.
- 木报告涂改、部分复印无效。
 This test report is invalid if crased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五日内向木中心提出, 逾期恕不 受理。

Any doubt should inform us within 15 days after receiving the test report.

委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dengli, Chaoyang District, Beijing 100024, P.R. China.

即编 (Post Code): 100024

电话(Tel): (θ10) 51164723 51164718

传真 (Fax): (010) 51164723 51164718

网址: (Web): http://www.dmtc.org.cn/

电子邮箱-(F-mail): sj13146197542@126.com