



检验报

TEST REPORT

中心编号(No.): 201706BW002

样品名称:

内墙涂料

Sample Name

委托单位:

河北朗新月逸建筑工程有限公司

Client

检验类别:

委托检验

Test Type

(国家) 建筑材料工业技术监督研究中心

建筑材料工业于混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





15000228308(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

REPORT TEST

中心编号(No.): 201706BW002 第1页共2页 内墙涂料 样品名称 检验类别 委托检验 委托单位 河北朗新月透建筑工程有限公司 商 标 朗新月途 生产单位 河北朗新月速建筑工程有限公司 等 级 生产日期 样品编号 2017年06月02日 规格型号 来样日期 液体 样品状态 液态 样品数量 10kg 检验依据 GB/T 9756-2009《合成树脂乳液内墙涂料》 检验项目 1. 施工性 2. 干燥时间 3. 耐碱性 4. 耐洗刷性 5. 对比率 *经检验、送检样品的施工性、干燥时间、耐碱性、耐洗刷性、对比 率的检验结果符合标准 GB/F 9756-2009 中内墙面漆(合格品)的技术指 标要求。* 检验结论 签发日期: 2017年 06 月 22日 (检验测试章) 备注:(此处空台)

批

制:7

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201706BW002

第2页共2页

序号	检验项目	标准要求(含格品)	检验结果	单项结论
認		柳涂车道光障碍	劇涂上道泉障碍	
路	千燥时间 (表手) 心			
器	耐碱性 (24h)			
	耐洗剛性水	300	300	
	对比率(自色和浅色))%	0.90	0.90	

(以下空百)

备注: (此处空白)

说。可明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议?应于收到报告之日起十五个工作日内的本中心提出一逾一期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张、复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):。北京市朝阳区管压东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code): 100024

电话(Tel):(010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询(Tel):(010)51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



