

150002283084



验报

TEST REPORT

中心编号(No.): 201706AW258

样品名称: 蒸压加气混凝土砌块

Sample Name

委托单位: 一三河市华奥新型墙体材料有限公司

Client

检验类别: 0.7.7.0.套托格談

Test Type

(国家)建筑材料了业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Materia Industry Center for Quality Supervision and Test of Dry-mixed Mortar





15000228308(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201706AW258

ا د سد د .	100.): 201706AW258	第1页 共2页					
样品名称	蒸压加气混凝土砌块	检验类别	委托检验				
委托单位	三河市华奥新型墙体材料有限公司	商标	100mm				
生产单位	三河市华奥新型墙体材料有限公司	等级	B06 A3.5				
生产日期		样品编号					
来样日期	2017年06月22日	规格型号	B06 A3.5				
样品数量	30块	样品状态	块状。				
检验依据	GB/T 11968-2006 《蒸压加气混凝土砌块》						
检验项目	1. 干密度 2. 立方体抗压强度 3. 导热系数 4. 干燥收缩值 5. 抗冻性						
检验结论	*经检验,送检样品的干密度、导验结果符合标准 GB/T 11968-2006 中 I 方体抗压强度的检验结果符合标准 GE 标要求。*	306级-合格品的	的技术指标要书。六				
	まままままままままままままままままままままままままままままままままままま	期: 2017年	混频》、 07月17日				

备注: (此处空白)

电话: 010-51164723

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201706AW258

第2页共2页

THE THE		一人一人一人一个一个一个一个一个一个一个一个一个一个一个一个一个一个一个一个一				
	2验项目	标准要求 (B06 级-合格品) ≤625		检验结果 612		单项 结论
子会	吏/ (kg/m³)					合格
A CONTRACT OF THE PARTY OF THE	体抗压强度/MPa (A3.5 级)	平均值	单组 最小值	平均值	单组 最小值	合格
33336		≥3.5	≥2.8	3.8	3.5	
导热系数(千态)/[W/(m·k)]/	€0.16		0.15 (平均温度: 25.00℃)		合格
干燥收缩值(快速法)/ (mm/m)		≤0.80		0.77		合格
抗冻性	质量损失率/%	55.00 €		4.054		合格
融循环)	冻后强度/MPa	≥2.8		3.203.		合格
	干密 立方体(导热系数(干燥收缩(抗冻性 (15次冻	导热系数 (干态) / [W/(m·k)]/ 干燥收缩值 (快速法) / (mm/m) 抗冻性 (15 次冻	T密度/ (kg/m³) 本密度/ (kg/m³) 本物值 本物值 (A3.5 级) >3.5 字热系数 (干态)/[W/(m·k)]/ ★(mm/m) ★(mm/m) ★(15 次冻	1		極验项目

(以下空白)

备注: (此处空白)

说 明

Notice

- A、C世报告无中心"检验测试差平和特缝章无效。 This test report is invalid without the seal.
- 22、本报告无广编制。审核、批准广签字五效。 This test report is invalid without the signatures of the related persons.
- 3、本报告徐改、一部分复印无效。 This test report is invalid if erased, altered or copied partially
- 4、对本报告若有异议,应于收割报告之旦起中五个工作自内间本由心提出,户逾 期怨不受理

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托太是供上中心不对真实性负责工委托检验结 果仅对求样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张、复印后应带有网络底纹 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式,

地址广Address):北京市朝阳区管庄东里广与北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 XPost Code 2: -100024

电话(1761),176470至154164723(5)1764718

传真(Fax):(010)51164724

报告真伪查询工记过光0100~51164716

Web http://www.dmtc.org.en/

电子邮箱(E-mail),dinte2007在163 com



