



报

TEST REPORT

中心编号(No.): 201704AW203

是是有人的


	42044	
样品名称:	混凝土沟盖板	
Sample Name		
委托单位: Client	河市春霞达丰建材有限公司	The state of the s
检验类别:	委托检验	

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



Test Type



建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201704AW203

		The Table Victor	为1火 六4火			
样品名称	混凝土沟盖板	检验类别	委托检验			
委托单位	三河市春霞达丰建材有限公司	商标				
生产单位	三河市春霞达丰建材有限公司	等级	Cc30			
生产日期	的理想到	样品编号	認認語			
来样日期	2017年04月19日	规格型号	700mm×500mm×120mm			
样品数量	680000000000000000000000000000000000000	样品状态	***************************************			
检验依据	JC 899-2002《混凝土路缘石》					
检验项目	1. 抗压强度					
检验结论	*经检验,送检样品的抗压抗压强度等级 Cc30 的技术指标	要求。* [发日期: 20	17年04月25日			
	自己存在结算	HEEK!	(检验测试章)			
备注:(此处	建 的合品。		場が移動を乗りたする			

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201704AW203

第2页共2页

电话: 010-51164723

邮编: 100024

序号	检验项目	标准要求		检验结果		单项结论
	抗压强度/MPa (抗压强度等级	平均值	单块 最小值	平均值	单块 最小值	
	Cc30)	≥30.0	≥24.0	33.8	31.2	

(以下空白)

备注: (此处空白)

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com