

福潤

150002283084

| 10 | TAT |
|----|-----|
| 7  |     |
| 1  | 717 |
|    |     |

## 验

# 报

# 告

TEST REPORT

中心编号(No.): 201702AW015

样品名称:

粘结砂浆

Sample Name

委托单位:

北京立异创新工贸有限公司

Client

检验类别:

委托检验

Test Type

则技术经验

(国家)建筑材料工业技术监督研究中心

建筑材料工业于混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Drymixed Mortan



(国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 验报告

TEST REPORT

中心编号(No.): 201702AW015

第1页共2页

| 样品名称   | ***************************************   | 检验类别    | 秦林秦       |
|--------|---|---------|-----------|
| 委托单位   | 北京立异创新工贸有限公司                              | 商品标     |           |
| 生产单位   | 河南之垣节能料技有限公司                              | 等级      |           |
| 生产日期   |   | 样品编号    |           |
| 来样日期   | 2017年02月16日                               | 规格型号    |           |
| 样品数量   |   | 样品状态    |           |
| 检验依据   | JG149-2003《膨胀聚苯板薄抹灰外墙外保温系统》               |         |           |
| 检验项目   | 1、拉伸鞋接强度(与水泥砂浆)                           |         |           |
|        | *经检验,送检样品的拉伸粘接强度(标准)G149-2003 中胶粘剂的技术指标要求 |         | 的检验结果符合   |
| 检验结论   |   | 2017年03 | I AUT HOT |
| 备注:(此处 |   |         | 調         |

批准:

核:

编制:书意

检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024

### (国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

#### TEST REPORT

中心编号(No.): 201702AW015

第2页 共2页

| 序 检验项目                                    | 标准要求 (胶料剂) | 检验结果   | 单项结论 |
|---|------------|--|------|
| 拉伸粘接强度 原强度<br>(与水泥砂浆)                     | ≥0.60      | 2000 P. S. |      |
| MPa A A A A A A A A A A A A A A A A A A A | 0.40       | 0.66   |      |

备注:配比:粉:水=4:1。

#### 说。 明

#### Notice

- 八、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal,
- 2、本报告无广编制、审核、批准"一签字无效。 This test report is invalid without the signatures of the related persons.
- 3、一本报告涂改、一部分复印无效。 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之目起中五个工作目内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托太提供,中心不对真实性负责,委托检验结 果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伤纸张,复印后应带有网络底纹 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code):100024

电话(Tel):(010)51164723-51164718

传真(Fax):(010)51164724

报告真伪查询(Tel):(010) 51164716

Web): http://www.dmtc.org.cn/

电子邮箱(E-mail): dmtc2007@163.com