





检验报告

TEST REPORT

中心编号(No.): 2012CIDW078



 样品名称:
 抹灰砂浆

 Sample Name
 61:

 委托单位:
 三河市福山绿洲新型产品有限公司

 Client
 委托检验

 Test Type
 工作

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortan



2009003084(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201206DW078

第1页共2页

Calle 3 (1101); Doithean Hair		20.121			
样品名称	抹灰砂浆	检验类别	委托检验		
委托单位	三河市福山綠洲新型建材有限公司	商标			
生产单位	三河市福山绿洲新型建材有限公司	样品状态	无结块粉料		
生产日期	2012年05月28日	生产批号			
来样日期	2012年06月29日	样品编号			
样品数量	10kg	规格型 <mark>号</mark>			
检验依据	JG/T 230-2007《预拌砂浆》				
检验项目	 强度等级 凝结时间 1. 强度等级 3. 14d 拉伸粘結强度				
检验结论	*经检验,送检样品的强度等级、 结果符合标准 JG/T 230-2007 中干混抹。 签发日期	灰砂浆 M10 的技术	指标要求。* 7月30日		

备注: (此处空白)

检验单位地址: 北京市朝阳区管庄中国建材院内北楼 电话: 010-51164723



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201206DW078

第2页共2页

序号	检验项目	标准要求 (干混抹灰砂浆 M10)	检验结果	单项结论
1	程度等級/MPa	M10	12.2	合格
2	凝结时间/h	3~8	5.8	合格
3	14d 拉仲粘结强度/MPa	>0.20	0.21	合格

(以下空白)

备注: 配比: 粉:水=1:0.16。

说明

Notice

- 本报告无中心"检验测试章"和特缝章无效。
 This test report is invalid without the seal.
- 本报告元"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if crased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期恕不 受理。
 - Any doubt should inform us within 15 days after receiving the test report.
- 委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 本报告采用防伤纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China,

即為i (Post Code): 100024

电话(Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164723 51164718

With (Web): http://www.dmtc.org.cn/

电子邮箱(E-mail): sj13146197542@126.com

