



检验报告

TEST REPORT

中心编号(No.): 2017[1BW002



PORTAPYED	4444444444444444	4
样品名称:	高强无收缩灌浆料工	0
		1
Sample Name	1, 200 x	4

委托单位: 北京海普斯建材有限公司


Client

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业于混砂浆产品质量监督检验测试中心 China Building Material Industry Conten for Quality Supervision and Test of Dry-mixed Mortan







(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201711BW002

第1页 共2页

十八、細方(八	(0.): 201/11BW002	第一块 六人 火工				
样品名称	高强无收缩灌浆料	检验类别。委托检验				
委托单位	北京海普斯建材有限公司	商标海普斯				
生产单位	北京海普斯建林有限公司	等级				
生产日期	2017年10月30日	样品编号				
来样日期	2017年11月03日	规格型号				
样品数量	20kg 24 24 24 24 24 24 24 24 24 24 24 24 24	样品状态。粉末				
检验依据	JC/T 986-2005(2017)《米泥基灌浆材料》					
检验项目	1. 粒径 2. 凝结时间 4. 抗压强度 5. 竖向膨胀率	サウナナリナスマウトナリウトエックト エリカムケアリウト				
检验结论	*经检验,送检样品的粒径、凝结时间、流动度、抗压强度、竖向膨胀率、钢筋握裹强度的检验结果符合标准 JC/F 986-2005(2017)中水泥基灌浆材料的技术指标要求。* 签发日期: 2017 年 12 月 06 日					
		一位(检验测试算)				
备注:(此处						

批 准:

> 邮编: 100024 朝阳区管庄中国建材院内北楼 电话: 010-51164723

建筑材料工业技术监督研究中心

检验单位地址

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201711BW002

第2页共2页

序号	检验项目		标准要求 (水泥基灌浆 材料)	检验结果	单项结论
	粒径 (4.75mm 方孔筛筛余) /%		\$2.0	1200	1700
32	凝结时间(初凝)/min		≥120	2018	合格
	流动度/mm	初始流动度	≥260	280	合格
		30min 流动度 保留值	≥230	252	会格
能			≥22.0	27.0	2000
4 抗压强度AMPs	抗压强度/MPa	\$23d	≥40.0	48.0	A A A
認		28d	≥70.0	70.0	
	鉴向膨胀率 (14) /%		≥0.020	0.030	1000
6	钢筋提裏强度 (圆钢, 28d) /MPa		4.0		

(以下空白)

备注: 配比: 粉:水=1.0:0.14。

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话(Tel): (010) 51164723 51164718

传真 (Fax): (010) 5H64724

报告真伪查询(Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.en/

电子邮箱 (E-mail): dmtc2007@163.com



