



# 检验报告

TEST REPORT

中心编号(No.): 201708AW007

正川川广二

样品名称:	蒸压加气混凝土砌块	
Sample Name		
委托单位: Client	三河市宏峰新型建材有限公司	
检验类别:	委托检验	
Test Type		

(国家)建筑材料工业技术监督研究中心

建筑材料工业干湿砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







150002283084(国家)建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201708AW007

第1页 共2页

1 0 2 10 3 (	20170011W007	- 11	第1贝共2贝					
样品名称	蒸压加气混凝土砌块	检验类别	委托检验					
委托单位	三河市宏峰新型建材有限公司	商标						
生产单位	三河市宏峰新型建材有限公司	等 级	B06 A3.5					
生产日期		样品编号	2 5 7 7 7 7					
来样日期	2017年08月31日	规格型号						
样品数量	20 块	样品状态	块状					
检验依据	GB/T 11968-2006《蒸压加气混凝土砌块》 GB 6566-2010《建筑材料放射性核素限量》							
检验项目	1. 干密度 2. 立方体抗压强度 3. 干燥收缩值 4. 导热系数 5. 抗冻性 6. 放射性(放射性比活度)							
检验结论	*经检验,送检样品的干密度、干燥收缩值、导热系数、抗冻性的检验结果符合标准 GB/T 11968-2006 中 B06 级-合格品的技术指标要求;立方体抗压强度的检验结果符合标准 GB/T 11968-2006 中 A3.5 级的技术指标要求;放射性(放射性比活度)的检验结果符合标准 GB6566-2010 中A类节节装修材料的技术指标要求,产销与使用范围不受限制。*  签发日期: 2017 年 09 月 27 日本检验测试章)。							

备注:(此处空白)

批 准: 核: 34年

检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



### (国家)建筑材料工业技术监督研究中心

## 建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.): 201708AW007

第2页 共2页

						第 2 贝 共 2 贝			
序号	松	<b>边验项目</b>	标准要求 (B06 级-合格品)		检验结果		单项 结论		
1	千密度/ (kg/m³)		密度/ (kg/m³) ≤625		610		合格		
2	40.000	立方体抗压强度/MPa		单组 最小值	平均值	单组 最小值	合格		
	(A3.5 级)		≥3.5	≥2.8	3.8	3.6			
3	干燥收缩值(快速法)/ (mm/m)		≤0.80		0.77		合格		
4	导热系数 (干态)/[W/(m·k)]		≤(	0.16	0.15 (平均温度: 25.00℃)		合格		
5	(15 次冻	质量损失率/%	<	5.0	0 4.0		合格		
		冻后强度/MPa	≥2.8		3.0		合格		
6	放射性 (放射性比活度) (A 类)		内照射指数 (I <sub>Ra</sub> ) ≤1.0		0.3		合格		
			外照射指数 (I <sub>Y</sub> ) ≤1.3		0.5		合格		

(以下空白)

备注:(此处空白)

检验单位地址: 北京市朝阳区管庄中国建材院内北楼 筑材料工业技术监督研究中心

#### 说 明

#### Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
   This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
   This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



