



检验报告

TEST REPORT

中心编号(No.), 201705BW137

样品名称: 内墙乳胶漆

Sample Name

委托单位: 耀星(廊坊)建筑材料有限公司

Client

检验类别: 委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar







(国家) 建筑材料工业技术监督研究中心

150002283084

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201705BW137

第1页共2页

样品名称	内墙顶漆	检验类别	委托检验	
委托单位	耀星(廊坊)建筑材料有限公司	商标	羅星雕	
生产单位	糧星(麻坊)建筑材料有限公司	等。级		
生产日期		样品编号		
来样日期	2017年05月12日	规格型号		
样品数量	20kg	样品状态		
检验依据	GB/T-9756-2009《含成树脂乳液内墙涂料》			
检验项目	1. 施工性 2. 甲燥时间 3. 耐碱性	4. 耐洗剛性	5.416	
检验结论	*经检验,送检样品的施工性、干燥率的检验结果符合标准 GB/T 9756-2009标要求。*)中内墙面漆(到期: 2017 白	HI TON TON	
备注:(此处				

制:

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201705BW137

第2页共2页

	检验项目	标准要求(合格品)	检验结果	单项结论
路路		刷涂三道是障碍	刷涂二道无障碍	
55	一种 ()			
缩	研碱性 (24h)			15 A
	耐洗阿性浓	300	300	
路路	对比率 (自色和浅色) 7%。	\$0.90 2.90 2.90 2.90 3.90 3.90 3.90 3.90 3.90 3.90 3.90 3	0.90	

(以下空白)

备注:(此处空白)

说。明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
 This test report is invalid if crased, altered or copied partially.
- 4、对本报告若有异议。应于收到报告之目起十五个工作日内向本中心提出,逾期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编(Post Code): 100024

电话(Tel): (010) 51164723 51164718

传真(Fax)。(010)51164724

报告真伪查询(Tel):(010)51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱(E-mail): dmtc2007@163.com



