



# 检验报告

TEST REPORT

中心编号(No.): 201611DW133



样品名称:	了一个一个大砂砖了一个了一个
Sample Name	
委托单位:	三河市祥升新型建材有限公司
Client	24-62-74-62-74-62-72-6-72
THOTTOPT	17677467766776677677

检验类别:

Test Type

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



建筑材料工业技术监督研究中心 150002283084

#### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201611DW133

第1页共2页

来样日期     2016年11月21日     规格型号     表50mm       样品数量     10块     样品状态     块状       检验依据     GB 11945-1999《蒸压灰砂砖》       检验项目     1. 强度级别	生产日期	2016年10月01日	样品编号	200mm×100mm
	<del>110115</del>	2016年11月21日 10块	规格型号 样品状态	×50mm
检验项目 1. 强度级别	检验依据	GB 11945-1999《蒸压灰砂砖》	招起	
*经检验,送检样品的强度级别的检验结果符合标准 GB 11945-1 中强度级别 MU10 的技术指标要求。*	检验项目	*经检验,送检样品的强度级别		示准 GB 11945-199

准: ( 批

电话: 010-51164723

邮编: 100024

#### 建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201611DW133

第2页共2页

序号	00 检	验项目	标准	要求	检验	结果	单项结论
强度 1 级别 MU10	NE.	抗压强度, MPa	平均值	单块值	平均值	单块值	**************************************
	1.72		≥10.0	≥8.0	12.9	10.8	
	级别 MU10		平均值	单块值	平均值	单块值	<b>合格</b>
	塑		≥2.5	≥2.0	3.1	2.8	

(以下空白)

电话: 010-51164723

邮编: 100024

备注:(此处空白)

## 说明

#### **Notice**

- 本报告无中心"检验测试章"和骑缝章无效。
   This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
   This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
  - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
  The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
   This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询(Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com