





检验报告

TEST REPORT

中心编号(No.): 201109CW005

力力用質

样品名称:	瀚晶牌硅藻泥		
Sample Name			
委托单位: Client	北京天扬一方硅藻材料有限公司		
检验类别: Test Type	委托检验		

(国家) 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





(国家) 建筑材料工业技术监督研究中心

2009803084M

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201109CW005

第1页共2页

样品名称	瀚晶牌硅藻泥	检验类别	委托检验			
委托单位	北京天杨一方硅藻材料有限公司	商标	為品			
生产单位	北京天扬一方硅藻材料有限公司	样品状态	纷科			
生产日期	2011年9月12日	生产批号	2011年9月12日			
来样日期	2011年9月20日	样品编号	は記載			
样品数量	6kg	规格型号				
检验依据	GB8624-2006《建筑材料及制品燃烧性能分级》					
检验项目	1.燃烧性能					
经检验,送检样品燃烧性能检验结果符合标准 GB8 "建筑材料及制品燃烧性能分级"A1 级技术指标要求。						
检验结论						
	签发	日期: 2011年 (检验》	SA 300元 经上,工厂工程			

备注:(此处空白)

批准:

松果

审核: 王奘如

编制: 黄



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201109CW005

第2页共2页

序号		检验项目	标准要求 (A1 级)	检验结果	单项结论
	燃烧性能	温升,℃	≤30	18	合格
1		质量损失率,%	≤50	13	合格
		持续燃烧时间,s	0	0	合格
		恙热值,MJ/kg	€2.0	1.1	合格

(以下空白)

备注: 配合比: 粉: 水-1: 0.5



电话: 010-51164723

邮编: 100024



说 明 Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五日内向本中心提出,逾期恕不 受理。

Any doubt should inform us within 15 days after receiving the test report.

- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164723 51164718

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): si13146197542@126.com

