检验报告

TEST REPORT

中心编号(No.): 201712AW133

 样品名称:
 混凝土 (试块)

 Sample Name
 中铁五局集团有限公司

 Client
 查托检验

Test Type

(国家)建筑林料工业技术监督研究中心

建筑材料工业干湿砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar









(国家)建筑材料工业技术监督研究中心 150002283084

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT


中心编号(No.): 201712AW133

第1页共2页

			第1页六2页		
样品名称	混凝土(试块)	检验类别	委托检验		
委托单位	中铁五局集团有限公司	商标			
生产单位	安徽昌茂建材科技开发有限公司	等 级	C40		
生产日期	2017年11月25日	样品编号			
来样日期	2017年12月27日	规格型号	600mm × 500mm × 40mm 800mm × 500mm × 40mm		
样品数量	6块	样品状态	块状		
检验依据检验项目					
检验结论	*依据标准 GB/T 50081-2002 劈裂抗拉强度、抗压强度的检验组	·果见第2页。	*		
	签	A STATE OF THE STA	8年01月03日		
备注:(此	处空白)	1	(2005年)		

制: 苏. 亮







(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201712AW133

第2页共2页

序号	检验项目	标准要求	检验结果	单项结论
1	劈裂抗拉强度, MPa		3.79	
2	抗压强度, MPa		46.2	_

(以下空白)

备注: 由委托方提供成型日期: 2017年11月25日。

建筑材料工业技术监督研究中心

说 明

Notice

- 本报告无中心"检验测试章"和骑缝章无效。
 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询(Tel):(010)51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>dmtc2007@163.com</u>



