



# 检验报告

TEST REPORT

中心编号(No.): 201701AW125

TIME

样品名称:	建筑结构胶(植筋型)
Sample Name	
委托单位: Client	北京中北辰业科技开发有限公司
检验类别:	委托检验
Test Type	entropic de la contraction del

国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201701AW125

第1页 共2页

		7	1 火 六 2 火		
样品名称	建筑结构胶 (植筋型)	检验类别	委托检验		
委托单位	北京中北辰业科技开发有限公司	商标	中北辰业		
生产单位	北京中北辰业科技开发有限公司	等级	A级		
生产日期	2017年01月03日	样品编号			
来样日期	2017年01月06日	规格型号	ZBCY-1		
样品数量	5 块	样品状态	混凝土块上植入 直径18mm 钢筋		
检验依据	MT 146.1-2011《树脂锚杆》				
检验项目	1. 拉拔力				
	*依据标准 MT 146.1-2011 规定的 拔力的检验结果见第 2 页。*	的试验方法进行检	<b>企验,送检样品的</b> 拉		
检验结论					
	签发日期: 2017年01月18日				
Z \$	·注:(此处空白)				
11:(此处	空白)	於於於	別主田幸		

#### (国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

### 检验报告

TEST REPORT

中心编号(No.): 201701AW125

第2页 共2页

序号	检验项目	标准要求	检验结果	单项结论
1	拉拔力/kN		118, 基材破坏	

(以下空白)

备注: 委托方提供:

(1) 基材 C40 混凝土、钻孔直径 26mm、螺纹钢直径 18mm、锚固深度 270mm;

电话: 010-51164723

邮编: 100024

(2) 试件龄期为 3 天且经受焊接热影响。

#### 说明

#### Notice

- 本报告无中心"检验测试章"和骑缝章无效。
  This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
  This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
  - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告的法律责任由建筑材料工业技术监督研究中心承担。

The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.

本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com