



检验报告

TEST REPORT

中心编号(No.): 201709CW111

IJI/JIF'S

-	1	

样品名称: 索田硅藻泥

Sample Name

委托单位: 深圳市索田环保科技有限公司

Client

检验类别: 委托检验

Test Type

建筑材料工业技术监督研究中心
Technical Supervision and Research Center of the Building Materials Industry





15000228308建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

检验报告

TEST REPORT

中心编号(No.): 201709CW111

第1页 共2页

1.10 Stat 2 (1	(0.): 201709C W111		第1页 共 4 页		
样品名称	索田硅藻泥	检验类别	委托检验		
委托单位	深圳市索田环保科技有限公司	商 标	索田		
生产单位	吉林省索田涂料有限公司	等 级	一级		
生产日期	2017年04月30日	样品编号			
来样日期	2017年09月06日	规格型号			
样品数量	5kg	样品状态	粉状		
检验依据	JC/T 2177-2013 (2017)《硅藻泥装饰壁材》				
检验项目	1. 甲醛净化性能 2. 甲醛净化效果持久性				
	*经检验,送检样品的甲醛净金果符合标准 JC/T 2177-2013 (201				
检验结论	签发日期: 201	日期: 2017年	应测试章 中		
备注:(此处	:空白)		检测专用章 PCANA A TO		

核萧瑛

制:

检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

检验报告

TEST REPORT

中心编号(No.): 201709CW111

第2页 共2页

序号	检验项目	标准要求	检验结果	单项结论
1	甲醛净化性能(%)	≥80	86.0	合格
2	甲醛净化效果持久性(%)	≥ 60	73.5	合格

(以下空白)

IJAKE C

备注: (1) 配比; 粉:水=1:1;

(2)涂刷量: 500g/m²;

(3) 样品测试期间,不开启日光灯。

检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



说 明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated, Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



