



检验报告

TEST REPORT

中心编号(No.): 201710AW103

立山山山

样品名称:	阻燃草帘被	
Sample Name		
委托单位: Client	涿州市国庆建材有限公司	
检验类别:	委托检验	

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Materia Undustry Center for Quality Supervision and Test of Dry-mixed Mortar







(国家)建筑材料工业技术监督研究中心

15000建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201710AW103

第1页共2页

1	the state of the s				
样品名称	阻燃草帘被	检验类别	委托检验		
委托单位	涿州市国庆建材有限公司	商标			
生产单位	涿州市国庆建材有限公司	等 级			
生产日期		样品编号			
来样日期	2017年10月11日	规格型号			
样品数量	$2m^2$	样品状态	块状		
检验依据	GB/T 10294-2008《绝热材料稳态热阻及有关特性的测定 防护热板法》 GB/T 2406.2-2009《塑料 用氧指数法测定燃烧行为 第 2 部分:室温试验				
检验项目	1. 导热系数 2. 氧指数				
检验结论	*依据标准 GB/T 10294-200 行检验,送检样品的导热系数、	氧指数的检验结 签发日期: 2017	果见第2页。*		
备注:(此处	空白)	45	型型が の で		

批 准: 核: 班利

制:苏高

检验单位地址: 北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): <u>201710AW103</u>

第2页共2页

序号	检验项目	标准要求	检验结果	单项结论
1	导热系数, W/(m·K)		0.060 (平均温 度: 25.00℃)	
2 氧指数,%			42.3	

(以下空白)

备注:(1) 导热系数试验依据标准 GB/T 10294-2008 规定的试验方法进行检验;

(2) 氧指数试验依据标准 GB/T 2406.2-2009 规定的试验方法进行检验。

说 明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



