



# 检验报告

TEST REPORT

中心编号(No.): 201707BW150

THE

样品名称:	玻化砖和石材专用粘合剂
Sample Name	
委托单位:	江苏雄鹰建材科技有限公司
Client	
检验类别:	委托检验
Test Tyne	

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验则试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





#### 150002283084国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

# 检验报告

TEST REPORT

中心编号(No.)	:	201	70	7B	W	150
-----------	---	-----	----	----	---	-----

第1页共2页

生产日期 来样日期 样品数量	2017年07月15日 25kg	样品编号 规格型号 样品状态	C2 型 粉状
检验依据检验项目	JC/T 547-2005(2017)《陶瓷墙地砖 1. 拉伸胶粘原强度 2.	浸水后的拉伸胶料	5强度 5届的拉伸胶粘强度
检验结论	3. 热老化后的拉伸胶粘强度 *经检验,送检样品的拉伸胶; 化后的拉伸胶粘强度、冻融循环 JC/T 547-2005(2017)中 C2 型的技	粘原强度、浸水后 后的拉伸胶粘强。 术指标要求。*	的拉伸胶粘强度、热力

备注:(此处空白)

批准: 加工 核: 近年 编

编制:黄素面



### (国家)建筑材料工业技术监督研究中心

### 建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

## 检验报告

TEST REPORT

中心编号(No.): 201707BW150

第2页共2页

序号	检验项目	标准要求 (C2型)	检验结果	单项结论
1	拉伸胺粘原强度/MPa	≥1.0	1.8	合格
2	浸水后的 拉伸胶粘强度/MPa	≥1.0	1.4	合格
3	热老化后的 ≥1.0		1.0	
4	冻融循环后的 拉伸胶粘强度/MPa	≥1.0	1.3	合格

(以下空白)

备注: 配比: 粉:水=1.0:0.25。

电话: 010-51164723

邮编: 100024

#### 说 明

#### **Notice**

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
   This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.

本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

#### 本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com



