



150002283084

存档

检 验 报 告

TEST REPORT

中心编号(No.): 201705DW130

QINTEC

样品名称: 界面处理剂

Sample Name

委托单位: 北京金星永兴涂料厂

Client

检验类别: 委托检验

Test Type

建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar



建筑材料工业技术监督研究中心
Technical Supervision and Research Center of the Building Materials Industry





150002283084 建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检 验 报 告

TEST REPORT

中心编号(No.): 201705DW130

第 1 页 共 2 页

样品名称	界面处理剂	检验类别	委托检验
委托单位	北京金星永兴涂料厂	商 标	—
生产单位	北京金星永兴涂料厂	等 级	—
生产日期	—	样品编号	—
来样日期	2017 年 05 月 15 日	规格型号	—
样品数量	2kg	样品状态	液态
检验依据	JC/T 907-2002 《混凝土界面处理剂》		
检验项目	1. 剪切粘结强度 2. 拉伸粘结强度（未处理）		
检验结论	<p>*经检验，送检样品的剪切粘结强度、拉伸粘结强度（未处理）的检验结果符合标准 JC/T 907-2002 中界面剂 I 型的技术指标要求。*</p> <p>签发日期：2017 年 06 月 02 日 (检验测试章)</p>		
备注：（此处空白）			

批 准：

审 核：

编 制：

检验单位地址：北京市朝阳区管庄中国建材院内北楼

电话：010-51164723

邮编：100024



建筑材料工业技术监督研究中心
Technical Supervision and Research Center of the Building Materials Industry

检 验 报 告

TEST REPORT

中心编号(No.): 201705DW130

第 2 页 共 2 页

序号	检验项目		标准要求 (I 型)	检验结果	单项结论	
1	剪切粘结强度/ MPa	7d	≥ 1.0	1.4	合格	
		14d	≥ 1.5	1.6	合格	
2	拉伸粘结强度/ MPa	未处理	7d	≥ 0.4	0.7	合格
			14d	≥ 0.6	0.8	合格
(以下空白)						
备注：配比：水泥：砂：界面剂=1.0：1.0：0.50。						

说 明 Notice

- 1、本报告无中心“检验测试章”和骑缝章无效。
This test report is invalid without the seal.
- 2、本报告无“编制、审核、批准”签字无效。
This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。
This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议，应于收到报告之日起十五个工作日内向本中心提出，逾期恕不受理。
Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供，中心不对真实性负责，委托检验结果仅对来样负责。
The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律責任由建筑材料工业技术监督研究中心承担。
The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张，复印后应带有网络底纹。
This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): <http://www.dmtc.org.cn/>

电子邮箱 (E-mail): dmte2007@163.com

