





检验报告

TEST REPORT

中心编号(No.): 201202AW314

THYLL

样品名称:	内墙耐水腻子粉
Sample Name	建起到 的特色的结合和
委托单位: Client	北京博奥宏达科贸有限责任公司
检验类别:	委托检验
Test Type	

(国家) 建筑材料工业技术监督研究中心

建筑材料工业于混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortan





建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201202AW314

第1页共2页

7. 9.10 2.75	20.222.1	THE RESERVE			
样品名称	内特耐水腻子粉	检验类别	委托检验		
委托单位	北京博奠宏达科贸有限责任公司	商标	宏奥		
生产单位	北京博與宏达科質有限責任公司	样品状态	粉状		
生产日期	2012年01月	生产批号	西斯		
来样日期	2012年02月24日	样品编号	35,435		
样品数量	20kg	规格型号	千粉型		
检验依据	JG/T 298-2010《建筑室内用腻子》				
检验项目	1. 打磨性 2. 粘结强度				
检验结论	*经检验,送检样品的打磨性、粘结强度的检验结果符合标准 JG/T 298-2010 中耐水型 (N) 的技术指标要求。* 签发目期: 2012 年 05 月 25 日				
	(检验测试章)				

备注:(此处空句)

批准: 核:



(国家)建筑材料工业技术监督研究中心

建筑材料工业于混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201202AW314

第2页 共2页

序号	检验项目		标准要求 耐水型(N)	检验结果	单项结论
i,	5. 10 may 15. 15. 15. 15. 15. 15. 15. 15. 15. 15.		手工可打磨	手工可力磨	合格
2	粘结强度,MPa	标准状态	>0.50	0.70	合格
		浸水后	- > 0.30 ¹	0.50	合格

(以下空白)

备注: 配比: 粉: 水=1: 0.40.

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告徐改、部分复印无效。

This test report is invalid if crased, altered or copied partially.

4、对本报告若有异议。应于收到报告之日起十五日内向本中心提出。逾期忽不 受理。

Any doubt should inform us within 15 days after receiving the test report.

委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 -51164718

传真 (Fax): (010) 51164723 51164718

阿拉 (Web): http://www.dmtc.org.cn/

电子邮新 (E-mail): sj13146197542@126.com

