



检验 报告

TEST REPORT

中心编号(No.): 201710EW101



样品名称:	轻集料混凝土		
Sample Name			
委托单位: Client	北京腾龙正利防水保温工程材料有限公司		
检验类别:	委托检验		
Test Type			

建筑材料工业技术监督研究中心 Technical Supervision and Research Center of the Building Materials Industry







建筑材料工业技术监督研究中心

150002283084 Technical Supervision and Research Center of the Building Materials Industry

检验报告

TEST REPORT

中心编号(No.): 201710EW101

第1页共2页

ST. CHARLES WAS STREET,	(0.). <u>201710EW101</u>		22 2 2 2					
样品名称	轻集料混凝土	检验类别	委托检验					
委托单位	北京腾龙正利防水保温工程材料有限 公司	商标	腾龙正利					
生产单位	河北腾龙辉煌再生资源利用有限公司	等 级						
生产日期	2017年09月02日	样品编号						
来样日期	2017年10月17日	规格型号	A型					
样品数量	34块	样品状态	自成型块状					
检验依据	JG/T 266-2011《泡沫混凝土》							
检验项目	1. 干密度 2. 导热系数 3. 强度等级							
检验结论	*经检验,送检样品的干密度、导JG/T 266-2011 中 A04 级的技术指标要求JG/T 266-2011 中 C1 级的技术指标要求。	强度等级的标						

批 准: (核: 14水1

编制:





检验单位地址:北京市朝阳区管庄中国建材院内北楼

电话: 010-51164723

邮编: 100024

建筑材料工业技术监督研究中心

Technical Supervision and Research Center of the Building Materials Industry

检验报告

TEST REPORT

中心编号(No.): 201710EW101

第2页 共2页

序号	检验项目	标准要求 ≤400 (容许误差+5%) ≤0.10		检验结果 405 0.098 (平均温度: 25.00℃)		单项结论 合格 合格
	干密度(A04 级)/(kg/m³)					
2	导热系数(A04 级) /[W/(m·K)]					
3	强度等级(C1 级)/MPa	每组 平均值	单块 最小值	毎组 平均値	单块 最小值	合格
		≥1.00	≥ 0.850	1.58	1.456	

(以下空白)

备注: (此处空白)



检验单位地址: 北京市朝阳区管庄中国建材院内北楼 建筑材料工业技术监督研究中心

说 明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。

This test report is invalid if erased, altered or copied partially.

4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

6、本报告的法律责任由建筑材料工业技术监督研究中心承担。

The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.

本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): <u>dmtc2007@163.com</u>



