



检验报告

TEST REPORT

中心编号(No.): 201704AW201



样品名称:	混凝土U型水槽
Sample Name	
委托单位:	三河市春霞达丰建材有限公司
Client	
检验类别:	委托检验
Test Type	253457565756525655

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心 China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告


TEST REPORT

中心编号(No.): 201704AW201

			为100 六40				
样品名称	混凝土U型水槽	检验类别	委托检验				
委托单位	三河市春霞达丰建材有限公司	商标					
生产单位	三河市春霞达丰建材有限公司	等 级	Cc30				
生产日期		样品编号	認認語				
来样日期	2017年04月19日	规格型号	宽 600mm、长 500mm、 高 400mm、壁厚 100mm				
样品数量	6块	样品状态	块张 己,己,己				
检验依据	JC 899-2002《混凝土路缘石》						
检验项目	1. 抗压强度						
	*经检验,送检样品的抗压抗压强度等级 Cc30 的技术指标		果符合标准 JC 899-2002 9				
检验结论							
	签发日期: 2017年 04月 25日						
是在1000000000000000000000000000000000000							

备注: (此处空白)

制、书、亮



(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201704AW201

第2页共2页

序号	检验项目	标准要求		验项目标准要求检验结果		结果	单项结论
	抗压强度/MPa (抗压强度等级	平均值	单块 最小值	平均值	单块 最小值		
懿	Cc30)	≥30.0	≥24.0	36.2	35.0		

(以下空白)

备注:(此处空白)

说明

Notice

- 1、本报告无中心"检验测试章"和骑缝章无效。 This test report is invalid without the seal.
- 2、本报告无"编制、审核、批准"签字无效。
 This test report is invalid without the signatures of the related persons.
- 本报告涂改、部分复印无效。
 This test report is invalid if erased, altered or copied partially.
- 4、对本报告若有异议,应于收到报告之日起十五个工作日内向本中心提出,逾 期恕不受理。
 - Any doubt should inform us within 15 workdays after receiving the test report.
- 5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结果仅对来样负责。
 - The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.
- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担。
 The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印后应带有网络底纹。
 This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址 (Address): 北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

邮编 (Post Code): 100024

电话 (Tel): (010) 51164723 51164718

传真 (Fax): (010) 51164724

报告真伪查询 (Tel): (010) 51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱 (E-mail): dmtc2007@163.com