

150002283084

检验损告

TEST REPORT

中心编号(No.): 201706AW283

样品名称:

浮雕骨料

Sample Name

委托单位: 北京航学保温建材有限公司

Client

检验类别:

委托检验

Test Type

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar





150002283084(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

验报告

TEST REPORT

中心编号(No.): 201706AW283

04-05-04-06-04-40-04-40-04-40-04-04-04-04-04-04-04-		たしているとなっている。		
样品名称		检验类别	委托检验	
委托单位	北京航宇保温建材有限公司	商品标		
生产单位	北京航字保温建林有限公司	等。级		
生产日期		样品编号		
来样日期	2017年06月29日	规格型号		
样品数量		样品状态		
检验依据	1G/T/157-2009《建筑外墙用献子》			
检验项目	①初期于燥荒裂胜 2、耐水性 3、粘结强度 (标准块态)			
检验结论	*经检验、送检样品的初期于燥抗裂性、耐水性、粘结强度(标准状态)的检验结果符合标准 IG/T 157-2009 中柔性 (R) 的技术指标要求。			
		: 2017年07 (检验测)	T Humber T	
备注:				

制、苏亮

(国家)建筑材料工业技术监督研究中心

建筑材料工业干混砂浆产品质量监督检验测试中心

China Building Material Industry Center for Quality Supervision and Test of Dry-mixed Mortar

检验报告

TEST REPORT

中心编号(No.): 201706AW283

第2页共2页

景	松岭域	标准要求 [柔性(R)]	检验结果	单项结论
	初期干燥机 单道施工厚度 製性 (6h) ≤1.5mm 的产品	lmm 无裂纹	Imm 无裂线	
	神水性 (96h)			
	料结强度 MPa	0.60	0.75	

(以下空白)

备注: 配比: 粉: 水=1.0: 0.40。

说 明

Notice

- 口、本报告无由心"检验测试章一和骑缝章无效。 This test report is invalid without the seal.
- 本报告无口编制(审核、批准")签字无效。 This test report is invalid without the signatures of the related persons.
- 3、本报告涂改、部分复印无效。 This test report is invalid if erased, altered or copied partially.
- 去。对本报告若有异议,应于收到报告之口起中五个工作日内向本中心提出,逾 期恕不受理。

Any doubt should inform us within 15 workdays after receiving the test report.

5、委托检验样品和委托信息由委托人提供,中心不对真实性负责,委托检验结 果仅对宋样负责。

The commissioned testing samples and commission information are provided by the applicant. The results shown in the test report refer only to the sample(s) tested unless otherwise stated. Identifying authenticity of the supplied samples and information is out of our responsibility.

- 6、本报告的法律责任由建筑材料工业技术监督研究中心承担, The legal responsibility of this test report is charged with Technical Supervision and Research Center of the Building Materials Industry.
- 7、本报告采用防伪纸张,复印启应带有网络底纹, This test report is printed on anti-counterfeiting paper. Its copy should have grid shading.

本中心联系方式:

地址(Address):北京市朝阳区管庄东里一号北楼

No.1 Guanzhuang Dongli, Chaoyang District, Beijing 100024, P.R. China.

即编(Post Code):□100024

电话(Teld: (010) 51164723 51164718

传真(Fax)。(010)51164724

报告真伪查询(Tel):(010)51164716

网址 (Web): http://www.dmtc.org.cn/

电子邮箱(E-mail): dmtc2007@163.com



