# B 270<sup>®</sup> Flat Glass

SCHOTT offers B 270® crown glass in sheet glass form suitable for a variety of different market demands.

B 270°, manufactured by a SCHOTT specific up-draw method, offers high stability with respect to solarization in combination with high transmission in the visible wavelength range. It has a fire-polished surface and high chemical stability.

B 270® is available in a wide range of thicknesses and various in-stock formates. Customized formates (e.g. rounds) and processing can be offered upon request.



### **Application**



## CD/DVD Pick up Digital Projection

- High transmittance
- Cost efficient processing due to wide thickness range



# Surface acoustic wave type touch panel

- Low acoustic attenuation
- High transmittance



### **CRT Door Phone**

- High solarization stability
- Fire-polished surface for use without polishing



### Monitor glass for coaters

- High transmittance
- Cost efficient process monitoring

Technical Data	
Dimensions	406 mm x 258 mm, 840 mm x 800-920 mm, 1680 mm x 800-920 mm (16.0 in x 10.1, 33 in x 31.5-36.2 in, 66.1 in x 31.5-36.2 in) other formats upon request
Thicknesses	0.8 mm up to 10.0 mm
Luminous transmittance $\tau_{vD65}$ (d = 2.0 mm)	91.7 %
Coefficient of mean linear thermal expansion $\alpha$ (20 °C; 300 °C) (static measurement)	$9.4 \cdot 10^{-6} \; \text{K}^{-1}$
Transformation temperature Tg	536 °C
Dielectric constant $\varepsilon_r$ at 1MHz	7.0
Refractive index n <sub>D</sub>	1.5229
Density ρ	2.56 g/cm <sup>3</sup>

### For more information please contact:

Advanced Optics **SCHOTT North America, Inc.** 400 York Avenue Duryea, PA 18642 USA

Phone +1 570/457-7485 Fax +1 570/457-7330 info.optics@us.schott.com www.us.schott.com/advanced\_optics

