

Table 1

Contact angles of water on aged surfaces.

Test section surface	Average contact angle (Average $\pm$ standard deviation) [$^{\circ}$]
Polished	78 ± 4
Roughened	85 ± 3
LbL	52 ± 7
CuO	122 ± 24
nanoFLUX	161 ± 16