

Table 2

Nucleation site density of surfaces in R-245fa at 20 °C (p_r of 0.086) at 20 kW/m².

Surface	Nucleation site density, n [sites/m ²]	Nucleation sites relative to polished surface, n/n_{pol} [-]
Polished	1.4×10^5	1
Roughened	6.9×10^5	4.9
LbL	1.7×10^5	1.2
CuO	8.0×10^4	0.57
nanoFLUX	2.8×10^5	2.0