

Table 3
Measured CHF values of the tested surfaces.

Si. no	Tested surface	CHF (kW/m ²)
1	CNT coated Cu	1.416
2	Sandblasted copper	1.114
3	Bare copper	1.027