

Table 5

Heat flux exponents of uncoated and nanocoated tubes.

Saturation Temperature [°C]	Tube	Uncoated	Coated
		n_q	n_q
5	EHPII	0.06	0.29
	GEWA-B5	−0.10	−0.04
	GEWA-KS	0.57	0.69
	Roughened	0.61	0.78
25	EHPII	−0.02	0.23
	GEWA-KS	0.48	0.66