

Table 1
Roughness parameters for all nine surfaces tested.

Sample	Roughness [μm]			
	R_a	R_q	R_z	S_m
Compound	0.041	0.055	0.438	20.9
2000 grit #1	0.061	0.080	0.699	15.1
2000 grit #2	0.057	0.076	0.699	13.1
600 grit #1	0.169	0.231	1.93	16.3
600 grit #2	0.114	0.157	1.41	14.7
220 grit #1	0.590	0.787	5.47	24.8
220 grit #2	0.997	1.31	8.57	27.2
80 grit #1	1.95	2.49	13.8	40.7
80 grit #2	2.36	3.01	16.3	44.5