


Table 2

Receding contact angles of FC-72 on ITO were measured for all surfaces by: (a) imaging with a backlit goniometer, (b) absolute differencing of the image with a clean reference frame, and (c) fitting a spherical cap to the upper surface of the thresholded droplet image.

	(a)	(b)	(c)	
Surface 1 polished no anneal				$\theta_r = 11.4^\circ$ $\pm 0.4^\circ$
Surface 2 $d_p = 15\ \mu\text{m}$ 998 K $\times$ 5 min. anneal				$\theta_r = 10.9^\circ$ $\pm 0.7^\circ$
Surface 3 $d_p = 30\ \mu\text{m}$ 1013 K $\times$ 15 min.				$\theta_r = 9.5^\circ$ $\pm 0.4^\circ$
Surface 4 $d_p = 100\ \mu\text{m}$ 998 K $\times$ 5 min.				$\theta_r = 5.6^\circ$ $\pm 0.6^\circ$
Surface 5 $d_p = 250\ \mu\text{m}$ 998 K $\times$ 5 min.				$\theta_r = 4.7^\circ$ $\pm 1.0^\circ$
Surface 6 $d_p = 100\ \mu\text{m}$ 1013 K $\times$ 15 min.				$\theta_r = 5.4^\circ$ $\pm 0.5^\circ$
Surface 7 $d_p = 100\ \mu\text{m}$ 1023 K $\times$ 45 min.				$\theta_r = 6.3^\circ$ $\pm 0.7^\circ$