




	(111) size	(200) size
Cu, pH 0	34.9 nm	14.6 nm
Cu, pH 10	16.9 nm	8.5 nm
Cu, pH 12	14.9 nm	7.3 nm

Fig. 3. (a) XRD measurements of the (111) and (200) peaks of the nickel foil substrate, copper powder, and electrodeposited dendritic copper foams at pH 0, pH 10, and pH 12. Ni foil was used as a substrate to study the deposited copper dendrites without being obscured by the copper substrate. (b) Debye-Scherrer crystallite size along the (111) and (200) orientations in electrodeposited dendritic copper foams at pH 0, pH 10, and pH 12.

3. Results and discussion