

Table 1

Summary of the wicking flux, critical heat flux, and heat transfer coefficient of polished copper and copper foam structures used in the present work.

Heater surface	Wicking flux (mm/s)	AE-wicking (dB)	CHF (W/cm ²)	Max. HTC (W/(cm ² K))	AE-CHF (dB)
Polished copper	–	–	102.6	6.4	58.2
Copper foam at pH 0	30.7	65.5	183.9	7.8	62.0
Copper foam at pH 10	41.8	39.2	218.6	10.7	59.6
Copper foam at pH 12	47.3	38.2	202.1	9.3	59.8

