

Table 1
 Test matrix showing weight, thickness, and porosity of the free and sintered particle layers investigated at each particle size.

Particle size [μm]	Free particles			Sintered particles		
	Weight [g]	δ/d	Porosity [%]	Weight [g]	δ/d	Porosity [%]
850–1000	22.44	4.8	40.2 ± 0.5	15.03	4.2	32.9 ± 0.5
180–212	4.47	4.8	39.9 ± 0.4	3.03	4.2	36.3 ± 1.5
90–106	2.41	4.8	43.1 ± 0.5	1.68	4.1	27.3 ± 1.5
45–53	1.18	4.8	44.4 ± 0.5	0.84	4.1	27.3 ± 3.0