

# From Dust to Bio-Infrastructure: A Mechanistic Review of Sintered Regolith Ceramics for Lunar Biogenerative Life Support Systems

First Author<sup>1,\*</sup>, Second Author<sup>1,2</sup>, Collaborator Three<sup>3</sup>, and Lead Author<sup>1,4,†</sup>

<sup>1</sup>Advanced Life Support and Space Bio-Engineering Group, Planetary Exploration Directorate

<sup>2</sup>Department of Materials Science and Engineering, Institute of Technology

<sup>3</sup>Division of Plant Biology and Microgravity Omics, Aerospace Biological Sciences

<sup>4</sup>In-Situ Resource Utilization and Planetary Infrastructures Center

\*Equal contribution; †Corresponding author: [author@organization.edu](mailto:author@organization.edu)

September 17, 2026

## Abstract

Establishing a permanent human presence on the Moon requires closing habitat life-support loops through Biogenerative Life Support Systems (BLSS). Terrestrial resupply imposes prohibitive launch costs, while direct agricultural cultivation in unrefined lunar regolith is severely constrained by submicroscopic nanophase metallic iron (npFe<sup>0</sup>), abiotic generation of reactive oxygen species (ROS) via modified Fenton cascades, broken silicate dangling bonds, and sharp mineral shards that induce physical shearing and plant root apical growth arrest. Furthermore, fractional lunar gravity ( $1/6g$ ) alters the Bond number, resulting in capillary entrapment, erratic nutrient transport, and pervasive root hypoxia in polydisperse regolith beds. Here, we review an alternative in-situ bio-infrastructure paradigm: transforming unrefined regolith into engineered porous ceramics via thermal sintering. High-temperature processing ( $> 1050^{\circ}\text{C}$ ) passivates reactive geochemical interfaces by solid-solubilizing npFe<sup>0</sup> into stable augite and olivine matrices, rounds grain boundaries, and enables precise control over pore throat diameters (30–60  $\mu\text{m}$ ). This pore architecture stabilizes matric potential (–2.5 to –5.0 kPa), ensuring continuous capillary nutrient wicking while maintaining air-filled porosity above 25–30%. Equivalent System Mass (ESM) lifecycle modeling reveals that the initial launch-mass investment of a sintering plant reaches parity with direct regolith cultivation within 18–22 months, driven by  $> 98.5\%$  water recovery efficiency and the elimination of chemical buffers. When integrated with fungal mycoponics, microbial bioweathering, and cyclic  $500^{\circ}\text{C}$  pyrolytic substrate regeneration, sintered regolith ceramics provide a closed-loop substrate foundation for sustainable extraterrestrial habitation.

**Keywords:** Lunar regolith, Biogenerative Life Support Systems (BLSS), In-Situ Resource Utilization (ISRU), Porous ceramics, Microwave sintering, Nanophase iron, Microgravity hydrodynamics, Equivalent System Mass (ESM).

---

## 1. Introduction: The In-Situ Resource Utilization Imperative in Lunar Life Support

Establishing an enduring human presence on the lunar surface requires transitioning from open-loop, resupply-dependent life support architectures to closed-loop, regenerative Biogenerative Life Support Systems (BLSS)<sup>1–3</sup>. Terrestrial logistics impose an unsustainable launch mass burden for multi-year surface missions, where crew metabolic requirements for water, oxygen, and fresh nutrition scale linearly with crew complement and mission duration<sup>4,5</sup>. Higher-plant bioregenerative architectures address this vulnerability by using photoautotrophic crop canopies to scrub atmospheric carbon dioxide (CO<sub>2</sub>), generate metabolic oxygen (O<sub>2</sub>), purify greywater via foliar transpiration, and produce fresh, nutrient-dense biomass<sup>1,3,5</sup>.

Historically, space mission trade studies evaluated two distinct edaphic paradigms for planetary crop production: importing prefabricated hydroponic hardware from Earth, or cultivating crops directly in untreated, in-situ planetary regolith<sup>2,3,6</sup>. Importing inert root-support matrices (such as mineral rockwool, polyurethane foams, or expanded clay) and prefabricated polymeric fluid channels from Earth imposes launch-mass penalties that severely restrict the deployable agricultural footprint during early outpost establishment<sup>3,4,6</sup>. Conversely, direct edaphic cultivation in raw lunar regolith—often termed “direct regolith agriculture”—operates under the premise that lunar dust can serve as a functional analog to terrestrial soil once augmented with water and soluble fertilizers<sup>3,6,7</sup>.

However, pioneering botanical experiments utilizing returned Apollo specimens and high-fidelity lunar simulants demonstrate that raw regolith imposes severe physiological penalties<sup>2,3</sup>. Planetary-scale exposure to unattenuated solar wind protons, galactic cosmic rays, and hypervelocity micrometeorite comminution has produced a geochemically hostile matrix characterized by submicroscopic zero-valent metallic iron (npFe<sup>0</sup>), unweathered razor-sharp mineral edges, and volatile abiotic surface reactivity<sup>2,3,8,9</sup>. Furthermore, single-particle wettability determinations on returned Chang’e-5 samples reveal pronounced intrinsic hydrophobicity across pristine lunar dust grains<sup>10</sup>. In parallel, the reduction of gravitational acceleration to one-sixth terrestrial gravity ( $1/6g$ ) drastically lowers the dimensionless Bond number, causing capillary retention forces to dominate over gravitational drainage<sup>3,11,12</sup>. As demonstrated by recent suborbital centrifuge flight experiments simulating lunar gravity ( $1.76\text{ m/s}^2$ ), fluid menisci exhibit rounded curvatures and boundary film thickening, while hydrophobic surface dust severely impedes water infiltration and liquid-gas equilibration<sup>13</sup>. Mitigating root-zone hypoxia under fractional gravity requires coarse, well-aerated aggregates (0.5–2.0 mm)<sup>13,14</sup>; however, core stratigraphy from Apollo and Chang’e-5 drill cores confirms that such millimeter-scale fractions dominate only at depths of several meters<sup>15,16</sup>, imposing prohibitive mechanical excavation and sifting burdens on early human outposts.

To overcome both the launch-mass penalty of imported hardware and the biological toxicity of raw regolith, life-support engineering is converging toward an in-situ bio-infrastructure paradigm<sup>3,17,18</sup>. Rather than attempting to adapt plant genetics to an inherently hostile mineral substrate, In-Situ Resource Utilization (ISRU) thermal consolidation processes can transform raw regolith into engineered porous ceramics<sup>3,17,19</sup>. High-temperature sintering passivates reactive geochemical interfaces, rounds abrasive grain morphology, and enables the precision fabrication of hydroponic troughs, multiphase fluid-delivery wicks, and mycoponic scaffolds<sup>3,19,20</sup>. This review analyzes the physicochemical, toxicological, fluid-mechanical, and systems-engineering principles


that govern the transition from raw regolith farming to sintered ceramic bio-infrastructure for sustained lunar settlement.

## 2. Physicochemical and Toxicological Interfaces of Pristine Lunar Regolith


### 2.1 Nanophase Iron and Abiotic Reactive Oxygen Species Generation

The Moon's hyper-vacuum environment and absence of a global dipolar magnetosphere expose surface minerals to unattenuated space weathering<sup>2,3,8,9</sup>. Solar wind proton bombardment reduces ferrous silicates, while episodic micrometeorite impacts induce localized shock melting and vapor-phase condensation<sup>3,21</sup>. These energetic processes generate nanophase metallic iron (npFe<sup>0</sup>), consisting of zero-valent iron blebs (1–100 nm in diameter) embedded within mineral rims and dispersed throughout the amorphous silicate matrices of agglutinitic glasses<sup>2,3,22</sup>.

When pristine regolith or reduced lunar simulants contact oxygenated aqueous solutions within a pressurized habitat, these surface-accessible metallic blebs trigger abiotic oxidation cascades<sup>3,8,9</sup>. Solvated divalent ferrous ions (Fe<sup>2+</sup>) dissolve from mineral interfaces in the presence of dissolved oxygen, initiating modified Fenton-like catalytic cycles<sup>3,8,9</sup>:



Subsequent electron transfer between the released ferrous iron and ambient oxidants drives the generation of hydroxyl free radicals ( $\cdot\text{OH}$ ) and superoxide radical anions ( $\text{O}_2^-$ ):



Electron paramagnetic resonance (EPR) spectroscopy with spin-trapping adducts, alongside chemical terephthalate hydroxylation assays, confirms that reduced lunar materials generate hydroxyl radical concentrations 5-fold to 100-fold higher than unreduced terrestrial basaltic analogs<sup>8,9,23</sup>. Furthermore, mechanical impact crushing on the airless lunar surface cleaves covalent bonds in silicates, plagioclase, and pyroxenes without atmospheric passivating agents, leaving surface dangling bonds such as broken silicon radicals ( $\equiv\text{Si}\cdot$ ) and silicon-peroxyl radicals ( $\equiv\text{Si}-\text{O}\cdot$ )<sup>9,24</sup>. Upon hydration, these radicals homolytically split water molecules, generating sustained bursts of oxidizing species<sup>24,25</sup>. Direct contact with this abiotic interface subjects plant root cell membranes to rapid lipid peroxidation, disrupting transmembrane electrochemical gradients, destroying transport proteins, and inducing root apical growth arrest<sup>3,9</sup>.

### 2.2 Transcriptomic Reprogramming, Genomic Lesions, and Morphological Impedance

The biological consequences of these reactive interfaces were demonstrated empirically by Paul et al.<sup>2</sup> using authentic lunar soils returned by Apollo 11, 12, and 17. Seeds of *Arabidopsis thaliana* germinated uniformly across Apollo regolith samples and volcanic controls; however, post-germination ontogeny diverged sharply<sup>2</sup>. Seedlings cultivated directly in Apollo regoliths exhibited severe stress phenotypes, including arrested primary root elongation, stunted rosette expansion, retarded leaf development, and dark purple pigmentation driven by anthocyanin hyperaccumulation<sup>2,26</sup>.

High-throughput RNA sequencing revealed that plants grown in raw lunar regolith execute a systemic transcriptomic reprogramming, shifting metabolic resources from vegetative biomass accumulation to protective defense cascades<sup>2,22</sup>. Differentially expressed genes are dominated by pathways associated with heavy metal toxicity, osmotic shock, and oxidative burst defense<sup>2,22</sup>. Plants significantly upregulate transcripts encoding glutathione S-transferases (GSTs), class III secretory cell-wall peroxidases, heat shock transcription factors, and antioxidant enzymes<sup>2,22</sup>. Concurrently, signaling cascades mediated by jasmonic acid (JA) and abscisic acid (ABA) are chronically induced, repressing cell-wall loosening and cellular expansion<sup>2,3</sup>. The magnitude of transcriptomic stress correlates positively with regolith maturity, quantified by the ferromagnetic resonance (FMR) maturity index ( $I_s/\text{FeO}$ )<sup>2,26,27</sup>. Mature regoliths (e.g., Apollo 11 sample 10084 and Apollo 17 sample 70051), possessing high agglutinitic glass and npFe<sup>0</sup> contents, trigger significantly more intense stress responses than immature sub-surface samples (e.g., Apollo 12 sample 12070)<sup>2,26</sup>.

Beyond immediate physiological stress, continuous root exposure to raw regolith compromises long-term genomic stability<sup>28,29</sup>. Multi-generational cultivation experiments utilizing regolith simulants demonstrate progressive accumulation of 8-oxoguanine (8-oxoG) DNA lesions induced by oxidative stress<sup>28</sup>. Because chromosomal telomeres contain repetitive guanine-rich motifs, they act as primary targets for oxidative damage<sup>28,30</sup>. In regolith simulant environments, telomerase catalytic activity becomes uncoupled from telomere length maintenance, culminating in accelerated telomere shortening, genome instability, and loss of multi-generational fitness<sup>3,28</sup>.

These biochemical challenges are compounded by particle morphometry<sup>2,3,31</sup>. Lacking atmospheric tumbling or aqueous rounding regimes, lunar particles retain razor-sharp edges with extreme aspect ratios<sup>2,3,31</sup>. As expanding root tips penetrate these interlocking angular grains, the abrasive surfaces micro-shear the root cap, strip mucilage-secreting border cells, and tear epidermal tissues<sup>3,8</sup>. Plants must continuously expend metabolic energy repairing damaged epidermal barriers, resulting in a systemic physiological penalty that curtails edible crop yields<sup>3,31</sup>.


### 3. Materials Science and In-Situ Manufacturing Modalities for Bio-Infrastructure

#### 3.1 Solid-State Sintering and Surface Passivation Mechanisms

Thermal sintering between 1050°C and 1250°C transforms loose, biologically reactive lunar regolith into chemically passivated, structurally coherent porous ceramics<sup>3,19,25</sup>. Within this thermal envelope, consolidation initiates via solid-state diffusion and localized liquid-phase sintering<sup>3</sup>. Agglutinitic impact glasses and low-melting-point pyroxenes soften and undergo viscous flow, wetting adjacent refractory mineral grains—primarily anorthitic plagioclase—and creating consolidated neck boundaries across particle contact zones<sup>3,19</sup>.

This thermal restructuring passivates the biological hazards of pristine regolith through two coordinated transformations<sup>3</sup>:

1. **Geochemical Passivation of Metallic Iron:** Thermal processing in controlled atmospheres oxidizes the submicroscopic zero-valent iron blebs<sup>3</sup>. Above 1000°C, metallic npFe<sup>0</sup> oxidizes and diffuses into softening aluminosilicate melts, solid-solubilizing into thermodynamically stable crystalline phases, principally clinopyroxenes (such as augite,  $(\text{Ca}, \text{Mg}, \text{Fe})\text{SiO}_3$ ) and olivines  $((\text{Mg}, \text{Fe})_2\text{SiO}_4)$ <sup>3,24,34</sup>. Once immobilized within silicate



**Figure 1. Physicochemical and toxicological interfaces of raw versus sintered lunar regolith.** (a) Raw lunar regolith contains reactive nanophase metallic iron ( $\text{npFe}^0$ ), broken silicate dangling bonds, and razor-sharp mineral shards that generate chronic oxidative stress via modified Fenton reactions ( $\text{Fe}^0 \rightarrow \text{Fe}^{2+} \rightarrow \cdot\text{OH}, \text{O}_2^-$ ), damaging plant root membranes and inducing 8-oxoG genomic lesions. (b) Thermal sintering above  $1050^\circ\text{C}$  passivates these hazards by oxidizing  $\text{npFe}^0$  into stable augite and olivine crystal matrices, rounding abrasive grain boundaries, and restoring plant transcriptomic homeostasis.

crystal lattices, iron ions can no longer undergo redox cycling in aqueous solution, quenching Fenton-mediated free radical cascades<sup>2,3</sup>.

2. **Morphological Rounding and Quenching of Dangling Bonds:** Viscous sintering smooths razor-sharp mineral edges<sup>3</sup>. High interfacial surface energies drive atomic mass transfer from convex surfaces into concave neck junctions, transforming jagged grain edges into rounded, smooth pore walls<sup>3</sup>. This atomic rearrangement quenches reactive surface dangling bonds ( $\equiv\text{Si}\cdot$ ,  $\equiv\text{Si}-\text{O}\cdot$ ) and eliminates the micro-shearing geometries that damage root apical meristems<sup>3,9,19</sup>. The resulting ceramic matrix is non-abrasive, chemically passivated, and biocompatible with root systems and beneficial rhizosphere microflora<sup>3,8</sup>.

### 3.2 Advanced Manufacturing Modalities

Fabricating functional bio-infrastructure from raw regolith requires thermal consolidation techniques matched to lunar surface environmental and power constraints<sup>3,18,20</sup>. Three primary modalities have been validated through terrestrial laboratory testing and planetary analog campaigns (Figure 2 and Table 2):

#### 3.2.1 Microwave Sintering

Microwave processing at frequencies of 2.45 GHz and 5.8 GHz provides rapid, volumetric dielectric heating of the regolith bulk<sup>17,19,35</sup>. The absorbed electromagnetic power per unit volume ( $P_v$ ,

**Table 1. Comparative physicochemical, toxicological, and agronomic properties of raw lunar regolith versus sintered regolith ceramics.**

| Parameter / Property                         | Raw Lunar Regolith (Direct Cultivation)                                                              | Sintered Regolith Ceramic (Engineered Substrate)                                     |
|----------------------------------------------|------------------------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------|
| Nanophase Metallic Iron (npFe <sup>0</sup> ) | Surface-accessible blebs across grain rims (1–100 nm) <sup>2,3,22</sup>                              | Oxidized and incorporated into stable crystalline silicates <sup>3,17</sup>          |
| Aqueous ROS Generation Potential             | High; sustained ·OH and O <sub>2</sub> <sup>·−</sup> generation via Fenton pathways <sup>2,8,9</sup> | Negligible; passivated, hydrothermally inert interface <sup>3,9,25</sup>             |
| Grain / Pore Morphometry                     | Highly angular, sharp, micro-shearing shards <sup>3,8,31</sup>                                       | Rounded, smooth, consolidated neck boundaries <sup>3,19,20</sup>                     |
| Plant Transcriptomic Profile                 | Chronic upregulation of GSTs, peroxidases, JA, and ABA stress pathways <sup>2,22,26</sup>            | Homeostatic baseline; standard vegetative and reproductive allocation <sup>2,3</sup> |
| Chromosomal & Telomeric Integrity            | Elevated 8-oxoG lesions, accelerated telomere erosion, fitness decline <sup>28–30</sup>              | Protected genome; absence of mineral-derived radical stress <sup>3,28</sup>          |
| Interfacial Contact Angle                    | Initially hydrophobic; prone to liquid beading and bypass channeling <sup>2,11,26</sup>              | Tailored hydrophilic wettability; continuous capillary wicking <sup>3,32</sup>       |
| Aqueous Solution Chemistry                   | Uncontrolled dissolution; alkaline spikes (pH 9.0–11.0), P-fixation <sup>3,8,33</sup>                | Stable pH control (pH 5.8–6.2); predictable nutrient stoichiometry <sup>3</sup>      |

$W/m^3$ ) is governed by:


$$P_v = 2\pi f \varepsilon_0 \varepsilon'' |E|^2 \quad (4)$$

where  $f$  is the electromagnetic frequency (Hz),  $\varepsilon_0$  is the permittivity of free space ( $8.854 \times 10^{-12}$  F/m),  $\varepsilon''$  is the relative dielectric loss factor of the regolith, and  $E$  is the root-mean-square electric field strength (V/m)<sup>17,19,35</sup>.

Lunar regolith couples strongly with microwave radiation because its dielectric loss tangent ( $\tan \delta = \varepsilon''/\varepsilon'$ ) is elevated by the presence of distributed npFe<sup>0</sup>, ilmenite (FeTiO<sub>3</sub>), and structural defects in agglutinitic glasses<sup>17,36</sup>. This strong coupling allows pristine regolith to heat volumetrically from within, reaching sintering temperatures with lower specific energy consumption ( $\sim 1.2$  kWh/kg) than surface heating methods<sup>17,35</sup>. However, multiphysics modeling coupling electromagnetic radiation, heat transfer, and mechanical stress shows that non-uniform field distributions create steep thermal gradients<sup>19</sup>. To avoid tensile stress exceeding the rupture modulus of sintered regolith ceramics, cooling rates must be strictly constrained to  $< 15^\circ\text{C}/\text{min}$ , preventing thermal microcracking and loss of fluid containment integrity<sup>19</sup>.

### 3.2.2 Concentrated Solar Sintering

Concentrated solar sintering uses parabolic mirrors, heliostats, or Fresnel concentrators to direct ambient solar irradiance ( $I_0 \approx 1361$  W/m<sup>2</sup>) directly onto the regolith bed<sup>3,18</sup>. As demonstrated by projects such as the European Space Agency's RegoLight initiative, solar concentrators can achieve focal temperatures above  $1400^\circ\text{C}$  in a vacuum without consuming habitat electrical power<sup>3,18,37,38</sup>.



**Figure 2. Multi-attribute engineering trade-off comparison of lunar regolith sintering modalities.** Normalized performance radar chart (scale 1–10) comparing Microwave Sintering (2.45/5.8 GHz), Concentrated Solar Sintering (ALM), and Selective Laser Melting (SLM) across energy efficiency, mass throughput, geometric precision, thermal stress safety, and volumetric heating capability.

Because concentrated radiative flux deposits energy purely at the material boundary, inward heat transfer relies on thermal conduction, which is constrained by the extremely low thermal conductivity of porous regolith in vacuum<sup>19,35</sup>. Consequently, effective thermal penetration depth is restricted to  $< 10$  mm per pass<sup>19</sup>. Concentrated solar sintering is therefore executed via Additive Layer Manufacturing (ALM), fusing successive thin powder layers to build large structural elements such as heavy-walled hydroponic troughs, drainage channels, and bulk radiation shielding during the 14-day lunar day<sup>3,37,39</sup>.

### 3.2.3 Selective Laser Melting (SLM)

Selective Laser Melting (SLM) and Selective Laser Sintering (SLS) direct a continuous-wave laser beam (typically near-infrared,  $\lambda = 1064$  nm) across a pre-spread powder bed of classified regolith<sup>3,20,40</sup>. The focused beam generates a localized melt pool that completely liquefies and vitrifies the silicate minerals, offering dimensional feature tolerances below  $50\text{--}100\ \mu\text{m}$ <sup>19,20</sup>.

While SLM requires higher specific electrical energy ( $\sim 3.5$  kWh/kg) and exhibits lower volumetric build throughput than bulk microwave or solar sintering, its precision makes it indispensable for fabricating intricate fluid-handling bio-infrastructure<sup>3,20</sup>. These include two-phase aeration nozzles, non-clogging porous irrigation emitters, internal capillary manifolds, and sensor-integration ports for monitoring the root-zone microenvironment<sup>3,20,41</sup>.

## 4. Multiphase Fluid Dynamics and Root Zone Aeration in Lunar Gravity

### 4.1 Fractional Gravity and Capillary Dominance

Fluid dynamics in terrestrial soils reflect a dynamic equilibrium between gravitational drainage and capillary matric suction<sup>11,12</sup>. On the lunar surface, gravitational acceleration drops to

**Table 2.** Key operational and technological parameters of lunar regolith additive manufacturing modalities for bio-infrastructure.

| Modality                           | Heating Mechanism                                                                           | Operating Temp.            | Specific Power Foot-print                                        | Geometric Resolution                                | Primary BLSS Application                                                  |
|------------------------------------|---------------------------------------------------------------------------------------------|----------------------------|------------------------------------------------------------------|-----------------------------------------------------|---------------------------------------------------------------------------|
| Microwave Sintering (2.45/5.8 GHz) | Volumetric dielectric loss coupling with npFe <sup>0</sup> and ilmenite <sup>17,19,36</sup> | 1050°C–1200°C <sup>3</sup> | Electrical (Magnetron/State); ~ 1.2 kWh/kg <sup>3</sup>          | Moderate (5–15 mm feature size) <sup>17,19</sup>    | Volumetric growth blocks, filter media, structural pavers <sup>3,42</sup> |
| Concentrated Solar Sintering (ALM) | Concentrated radiative flux and surface thermal conduction <sup>3,18,37</sup>               | 1100°C–1400°C <sup>3</sup> | Direct solar; zero electrical draw during lunar day <sup>3</sup> | Coarse-to-Moderate (2–10 mm layer) <sup>18,39</sup> | Hydroponic troughs, drainage gutters, perimeter shielding <sup>3</sup>    |
| Selective Laser Melting (SLM/SLS)  | Focused optical absorption, local melt pool fusion <sup>3,20</sup>                          | 1200°C–1500°C <sup>3</sup> | High electrical draw; laser diodes (~ 3.5 kWh/kg) <sup>3</sup>   | High (50–200 μm resolution) <sup>3,20</sup>         | Aeration nozzles, porous wicking pins, fluid manifolds <sup>3,20,41</sup> |

$g_L \approx 1.62 \text{ m/s}^2$ , approximately one-sixth of terrestrial gravity ( $g_E \approx 9.81 \text{ m/s}^2$ )<sup>3</sup>. This reduction fundamentally alters the dimensionless Bond number (Bo), which defines the ratio of gravitational body forces to interfacial capillary surface tension forces within a porous medium<sup>3,43</sup>:

$$\text{Bo} = \frac{\Delta\rho \cdot g \cdot d^2}{\gamma} \quad (5)$$

where  $\Delta\rho$  is the density difference between the liquid nutrient solution and the habitat atmosphere ( $\text{kg/m}^3$ ),  $g$  is the local gravitational acceleration ( $\text{m/s}^2$ ),  $d$  is the characteristic pore-throat diameter (m), and  $\gamma$  is the liquid-gas surface tension ( $\text{N/m}$ )<sup>3,12</sup>.

Because lunar gravity is reduced by a factor of 6 while fluid surface tension remains intrinsically fluid-dependent, the Bond number decreases by nearly an order of magnitude<sup>3,43,44</sup>. Consequently, the hydraulic regime transitions from gravity-driven drainage to capillary-dominated retention<sup>3,44</sup>. The characteristic length scale governing this balance is the capillary length ( $L_c$ ):

$$L_c = \sqrt{\frac{\gamma}{\rho g}} \quad (6)$$

For pure bulk water ( $\gamma \approx 0.072 \text{ N/m}$ ,  $\rho = 1000 \text{ kg/m}^3$ ), the theoretical capillary length expands from 2.71 mm on Earth to approximately 6.5–6.6 mm under lunar gravity ( $1.62\text{--}1.76 \text{ m/s}^2$ ).

Correspondingly, the classical Young-Laplace equilibrium height of capillary rise ( $h_c$ ):

$$h_c = \frac{2\gamma \cos \theta}{\rho g r} \quad (7)$$

(where  $\theta$  is the fluid contact angle and  $r$  is the effective pore radius) predicts a six-fold vertical expansion of the capillary fringe compared to Earth for identical pore geometries<sup>3,11</sup>.

## 4.2 Empirical Suborbital Flight Validation: Microscale Topography and Film Thickening

While classical continuum models assume idealized smooth surfaces and unconstrained bulk fluid properties, groundbreaking empirical data gathered aboard Blue Origin's New Shepard 29 (NS-29) suborbital mission by Hasenstein, Kiss, and McKay (2026) reveals that boundary interactions in fractional gravity diverge markedly from textbook theory<sup>13</sup>. Conducting flight experiments under sustained centrifugal lunar acceleration ( $a = 1.76 \pm 0.02 \text{ m/s}^2$  for 2.3 minutes), Hasenstein et al. imaged fluid menisci across pure water, 30% (w/w) glycerol ( $\eta = 2.5 \text{ cP}$ ), and 0.8% (w/w) saline solutions in 3D-printed chambers with wall angles of  $90^\circ$ ,  $75^\circ$ , and  $70^\circ$ , fitting interface geometries using the nonlinear Young-Laplace differential formulation<sup>13</sup>:

$$\frac{d^2 z}{dx^2} = \frac{\rho g}{\gamma} (z - z_0) \left[ 1 + \left( \frac{dz}{dx} \right)^2 \right]^{3/2} \quad (8)$$

with the wall slope constrained by the apparent interface contact angle  $\theta_{\text{app}} = \theta_{\text{wall}} - \theta_{\text{contact}}$  through  $dz/dx = \tan(\theta_{\text{app}})$ .

Crucially, the empirical capillary length measured for water under lunar gravity was  $L_c = 4.2 \pm 0.1 \text{ mm}$  (yielding an apparent fitted surface tension  $\gamma \approx 30.0\text{--}30.6 \text{ mN/m}$ ), representing a striking  $\sim 35\%$  suppression relative to theoretical bulk values ( $6.5 \text{ mm}$ )<sup>13</sup>. Hasenstein et al. established that in reduced gravity, microscale surface topography, wall roughness, and contact angle hysteresis override bulk fluid behavior<sup>13</sup>. Fluids form significantly thicker wetting films along container boundaries, while menisci exhibit pronounced curvature and flatter central zones compared to terrestrial gravity<sup>13</sup>. Furthermore, the addition of 30% glycerol enhanced apparent surface tension ( $\gamma \approx 43.9\text{--}50.1 \text{ mN/m}$ ) and increased capillary length to  $L_c = 4.8\text{--}5.2 \pm 0.9 \text{ mm}$  across all wall angles<sup>13</sup>. This demonstrates that biocompatible wetting agents can overcome microscale boundary pinning, dramatically improving fluid wicking along textured porous surfaces in fractional gravity<sup>13</sup>.

## 4.3 The Raw Regolith Hydrology Dilemma vs. Sintered Pore Architecture

These empirical flight findings illuminate the severe, multifaceted hydraulic failure modes of raw lunar regolith farming. Natural lunar regolith is intrinsically hydrophobic at the individual particle scale, as recently demonstrated by single-particle contact angle analyses on returned Chang'e-5 grains<sup>10</sup>. In unsorted, polydisperse regolith beds, sub-micrometer dust particles create an uncontrolled, chaotic pore network spanning from  $< 0.1 \mu\text{m}$  to  $> 250 \mu\text{m}$ <sup>2,9</sup>. Under  $1/6 g$ , capillary forces trap water in fine micropores ( $< 10 \mu\text{m}$ ), establishing an expansive saturated zone that suffocates aerobic root respiration<sup>2,3,14</sup>. Simultaneously, the combined effects of dust hydrophobicity, low gravitational driving head, and contact-angle pinning severely impede water

percolation, leading to erratic bypass channels and dry zones<sup>10,13</sup>.

To prevent hypoxia in fractional gravity, microgravity plant cultivation systems (such as NASA's Veggie and Advanced Plant Habitat) rely on coarse, sieved aggregates (1–2 mm arcillite)<sup>11,13,14</sup>. Hasenstein et al. estimate that an aggregate diameter of 0.5–1.0 mm would be required to maintain aeration under lunar gravity<sup>13</sup>. However, Apollo core stratigraphy<sup>15</sup> and Chang'e-5 drill core depth profiles<sup>16</sup> prove that millimeter-scale regolith fragments dominate only at depths of several meters, whereas surface regolith is overwhelmingly dominated by fine, sub-75  $\mu\text{m}$  dust. Sourcing coarse regolith on the Moon therefore requires extensive deep excavation and heavy sifting plants, imposing prohibitive launch-mass and energy burdens on early outposts<sup>13</sup>.

Engineered thermal sintering resolves this dilemma by transforming the abundant, hazardous fine surface dust (45–75  $\mu\text{m}$ ) into structured porous ceramic matrices with monodisperse pore throat diameters concentrated precisely between 30 and 60  $\mu\text{m}$ , and open porosities of 35–42%<sup>3</sup>. High-temperature processing ( $> 1050^\circ\text{C}$ ) destroys surface organic/radiation defect layers, rounds angular particle edges, and vitrifies the aluminosilicate matrix into an intrinsically hydrophilic substrate<sup>3,17,19</sup>.

The resulting pore network stabilizes the substrate's soil-water retention curve, formulated via the van Genuchten constitutive relation<sup>45,46</sup>:

$$\Theta(h) = \frac{\theta(h) - \theta_r}{\theta_s - \theta_r} = [1 + (\alpha|h|)^n]^{-m} \quad (9)$$

where  $\Theta(h)$  is normalized volumetric water content,  $\theta(h)$  is volumetric moisture content,  $\theta_r$  and  $\theta_s$  are residual and saturated moisture contents,  $h$  is matric suction head (cm or kPa), and  $\alpha, n$ , and  $m = 1 - 1/n$  are empirical pore-geometry parameters<sup>45,46</sup>.


By eliminating both ultra-fine micropores ( $< 5 \mu\text{m}$ ) that trigger capillary waterlogging and macropores ( $> 150 \mu\text{m}$ ) that cause premature draining, sintered ceramics constrain matric suction to an optimal operating window of  $-2.5$  to  $-5.0$  kPa (Figure 3 and Table 3)<sup>3</sup>. This suction is sufficient to wick nutrient solutions across the root zone against fractional gravity, even when factoring in boundary film thickening and micro-roughness pinning<sup>13</sup>, while allowing plant roots to extract water with minimal metabolic energy expenditure<sup>3</sup>. Crucially, this pore architecture maintains air-filled porosity above 25–30% at field capacity under  $1/6 g$ <sup>3,32,44</sup>, supporting continuous diffusive oxygen transport to root cell boundaries and preventing hypoxia without requiring deep regolith excavation<sup>13,14</sup>.

## 5. Life Support Systems Integration and Equivalent System Mass Analysis

### 5.1 Equivalent System Mass Accounting Framework

To evaluate the flight viability of life-support hardware, space systems architects employ the Equivalent System Mass (ESM) metric, formalized in NASA's *Advanced Life Support Baseline Values and Assumptions Document* (BVAD)<sup>4,47</sup>. ESM converts physical mass, pressurized volume, operational power, thermal rejection, and crew maintenance labor into a single standardized mass figure (kg)<sup>4,48</sup>:

$$\text{ESM} = M + (V \cdot C_V) + (P \cdot C_P) + (C \cdot C_C) + (T \cdot C_T) \quad (10)$$



**Figure 3. Multiphase fluid dynamics and root zone aeration in fractional lunar gravity ( $1/6g$ ).** Relationship between pore throat diameter ( $\mu\text{m}$ ), air-filled porosity (%), and matric suction head ( $-\text{kPa}$ ). Below  $30\mu\text{m}$ , capillary trapping induces waterlogging and severe hypoxia risk ( $< 15\%$  air porosity). Above  $60\mu\text{m}$ , weak capillary suction leads to dry channeling. The engineered  $30\text{--}60\mu\text{m}$  pore window balances capillary liquid wicking with  $> 25\text{--}30\%$  air-filled porosity for aerobic root respiration, fully accommodating empirical boundary film thickening observed in suborbital flight data<sup>13</sup>.

where  $M$  is hardware and consumable mass ( $\text{kg}$ ),  $V$  is pressurized habitat volume ( $\text{m}^3$ ),  $P$  is operational electrical power demand ( $\text{kWe}$ ),  $C$  is thermal cooling rejection load ( $\text{kWth}$ ), and  $T$  is routine crew maintenance time (crew-hours/year)<sup>4,47</sup>. The infrastructure equivalency factors— $C_V$  ( $\text{kg}/\text{m}^3$ ),  $C_P$  ( $\text{kg}/\text{kWe}$ ),  $C_C$  ( $\text{kg}/\text{kWth}$ ), and  $C_T$  ( $\text{kg}/\text{crew-hour}$ )—quantify the launch mass required to supply an incremental unit of that resource on the lunar surface<sup>4,48</sup>.

On the Moon, these equivalency factors depend heavily on the outpost power architecture<sup>49,50</sup>. For photovoltaic arrays paired with regenerative fuel cells or lithium-ion batteries ( $200\text{ Wh}/\text{kg}$ ), the 14-day lunar night drives  $C_P$  to  $\sim 237\text{ kg}/\text{kWe}$ <sup>50,51</sup>. Surface fission reactors reduce  $C_P$  to approximately  $54\text{--}100\text{ kg}/\text{kWe}$ <sup>51</sup>. Meanwhile, radiating waste heat into a lunar vacuum remains challenging, maintaining high thermal infrastructure factors ( $C_C \approx 85\text{--}145\text{ kg}/\text{kWth}$ )<sup>50,52</sup>. Consequently, agricultural systems with high recurring consumable resupply or extensive crew maintenance quickly incur severe lifecycle mass penalties<sup>3,4,52</sup>.

## 5.2 Comparative Lifecycle Assessment: Direct Agriculture versus Sintered Infrastructure

Comparing direct regolith agriculture against sintered ceramic bio-infrastructure reveals fundamental trade-offs between initial deployment mass and long-term operational sustainability<sup>3,4</sup> (Table 4 and Figures 6a–6b):

### 5.2.1 Water Recovery Efficiency

Water recycling is a dominant driver of lifecycle ESM<sup>4,48</sup>. In direct regolith cultivation, water loop closure is severely compromised<sup>3</sup>. Due to the immense specific surface area of sub-micrometer dust and tortuous pore networks,  $15\text{--}20\%$  of applied irrigation water becomes immobilized in

**Table 3.** Comparison of hydraulic, physical, and transport parameters in raw lunar regolith versus sintered engineered ceramics under 1/6 *g*.

| Hydraulic / Physical Parameter              | Raw Lunar Regolith Bed                                                   | Re- | Sintered Engi-<br>neered Ceramic                                                         | Physiological & Systemic Impact                                                 |
|---------------------------------------------|--------------------------------------------------------------------------|-----|------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------|
| Grain Size Distribution                     | Polydisperse ( $< 1 \mu\text{m}$ to $1000 \mu\text{m}$ ) <sup>3,22</sup> | to  | Classified, sorted fraction ( $45\text{--}75 \mu\text{m}$ ) <sup>3</sup>                 | Eliminates packing collapse and avoids multi-meter excavation <sup>15,16</sup>  |
| Pore Throat Diameter ( $d_{\text{pore}}$ )  | Uncontrolled ( $0.1 \mu\text{m}$ to $250 \mu\text{m}$ ) <sup>2,3</sup>   | to  | Monodisperse control ( $30\text{--}60 \mu\text{m}$ ) <sup>3</sup>                        | Stabilizes capillary wicking without fluid entrapment <sup>3</sup>              |
| Effective Capillary Length ( $L_c$ )        | Variable / pinned by surface roughness <sup>13</sup>                     |     | $4.2\text{--}5.2 \text{ mm}$ (Empirically verified in 1/6 <i>g</i> flight) <sup>13</sup> | Predictable meniscus curvature and film stability <sup>13</sup>                 |
| Wettability / Contact Angle                 | Hydrophobic grains ( $\theta > 70^\circ$ ) <sup>10</sup>                 |     | Hydrophilic vitrified silicate ( $\theta < 30^\circ$ ) <sup>3</sup>                      | Rapid fluid imbibition; eliminates dry bypass channels <sup>13</sup>            |
| Matric Potential Window ( $\psi_m$ )        | Unstable ( $-0.1$ to $< -100 \text{ kPa}$ ) <sup>3,8</sup>               |     | Controlled ( $-2.5$ to $-5.0 \text{ kPa}$ ) <sup>3</sup>                                 | Matches root water uptake with minimal plant energy expenditure <sup>3,45</sup> |
| Air-Filled Porosity at Field Capacity       | $< 8\text{--}12\%$ (Severe hypoxia risk) <sup>2,3,14</sup>               |     | $> 25\text{--}30\%$ (Continuous aeration) <sup>3</sup>                                   | Maintains aerobic root respiration; prevents root decay <sup>13,14</sup>        |
| Hydraulic Conductivity ( $K_{\text{sat}}$ ) | Spatially erratic; causes stagnant zones <sup>2,44</sup>                 |     | Isotropic; stable convective mass transfer <sup>3</sup>                                  | Prevents localized fertilizer salt accumulation <sup>3,33</sup>                 |

fine micropores at matric potentials below the permanent wilting point ( $\psi_m < -1.5 \text{ MPa}$ )<sup>2,3,8</sup>. This water cannot be extracted by plant roots and resists passive evaporation into habitat dehumidification systems<sup>3,8</sup>. Consequently, direct regolith farming achieves only 78–82% water recovery efficiency, requiring hundreds of kilograms of annual makeup water resupplied from Earth or energy-intensive polar ice extraction<sup>3,49</sup>. In contrast, sintered ceramics feature open, interconnected pore channels that allow both root uptake and negative-pressure recovery<sup>3</sup>. Coupled with condensing heat exchangers capturing foliar transpiration, sintered systems achieve water recovery efficiencies  $> 98.5\%$ , drastically lowering ongoing logistics mass<sup>3,5</sup>.

### 5.2.2 Chemical Nutrient Solution Stability

Direct cultivation in raw regolith destabilizes hydroponic chemistry<sup>3,24</sup>. Exposure to aqueous solutions (pH 5.5–6.5) induces uncontrolled dissolution of plagioclase, olivines, and pyroxenes, releasing excess divalent and alkali cations ( $\text{Ca}^{2+}$ ,  $\text{Mg}^{2+}$ ,  $\text{Na}^+$ ) that trigger rapid alkaline spikes (pH 9.0–11.0)<sup>3,8,24</sup>. This alkaline environment precipitates essential orthophosphate ions ( $\text{PO}_4^{3-}$ ) as insoluble calcium phosphates, while iron, zinc, and manganese precipitate as insoluble hydroxides<sup>3,7,33</sup>. Maintaining plant viability requires continuous buffering with concentrated nitric ( $\text{HNO}_3$ ) and sulfuric ( $\text{H}_2\text{SO}_4$ ) acids and synthetic chelating agents (EDTA/EDDHA), consuming

$\sim 145$  kg/year of chemical consumables for a nominal 6-person habitat<sup>3,7,22</sup>. Conversely, regolith sintered above  $1050^{\circ}\text{C}$  forms a vitrified aluminosilicate ceramic that resists aqueous dissolution, providing hydrothermal stability across multi-year operational regimes with stable pH (5.8–6.2) and minimal buffer resupply ( $< 8$  kg/year)<sup>3</sup>.

### 5.2.3 Habitat Dust Mitigation and Crew Maintenance

Direct regolith agriculture necessitates excavating, transporting, and managing large inventories of abrasive dust inside or adjacent to pressurized modules<sup>2,3</sup>. Fugitive airborne dust erodes environmental control and life support system (ECLSS) mechanical seals, fouls air filters, and presents toxicological risks to crew respiratory health<sup>2,3,8,23</sup>. Sintered bio-infrastructure locks loose particles into monolithic ceramic components, eliminating particulate hazards from the habitat atmospheric loop<sup>3</sup>.


### 5.2.4 ESM Breakeven Horizon

Direct regolith cultivation exhibits a lower initial launch mass ( $\sim 420$  kg for containment bins and basic tools for a 6-crew module)<sup>2,3</sup>. However, its steep recurring consumables slope—driven by water loss, acid buffers, and crew labor—causes cumulative ESM to escalate rapidly<sup>3,4,31</sup>. Sintered bio-infrastructure requires a higher upfront launch investment ( $\sim 1850$  kg for an automated microwave/solar sintering manufacturing plant)<sup>3,34</sup>. Systems-level parametric modeling demonstrates that cumulative ESM curves cross within 18–22 months under conservative power assumptions (and as early as 9–15 months under surface nuclear power)<sup>3,42,53</sup>. For mission durations exceeding two years, sintered ceramics yield compounding mass savings, establishing them as the superior edaphic strategy for permanent lunar settlements.

### 5.2.5 Operational Phase-In and ESM Breakeven Timeline

The operational transition from outpost landing to net-positive logistics returns is tracked in the 60-month ISRU manufacturing and deployment Gantt schedule (Figure 4) and rendered in photorealistic 3D architectural phasing on the Shackleton Crater rim (Figure 5):

- **Phase I: Logistics and Beneficiation (Months 0–6, Fig. 5a):** Touchdown of cargo landers delivers the 1850 kg sintering facility and surface power systems (e.g., 40 kWe Kilopower FSP). Tele-operated excavation rovers extract raw lunar regolith, executing magnetic separation to remove native  $\text{npFe}^0$  spherules and sieving feedstock to  $< 100 \mu\text{m}$  to ensure uniform dielectric coupling.
- **Phase II: Serial Sintering Manufacturing (Months 3–15, Fig. 5b):** The automated microwave sintering plant conducts vacuum thermal consolidation under strict thermal-stress cooling control ( $< 15^{\circ}\text{C}/\text{min}$ ). Modular porous ceramic trays and fluidic distribution manifolds are produced and given a hydrothermal passivation rinse, alongside sintered regolith blast berms and landing pads, building the complete substrate inventory for a 6-person habitat within 12 months.
- **Phase III: Canopy Phasing and ESM Breakeven (Months 12–24, Fig. 5c):** Sintered trays are mounted into vertical habitat growth racks, plumbed into closed nutrient loops, and seeded under PAR LED grow lighting within pressurized Artemis inflatable/rigid



**Figure 4. Autonomous ISRU habitat outfitting, manufacturing phase-in, and Equivalent System Mass (ESM) breakeven timeline.** Phased progression over a 60-month lunar surface mission: Phase I logistics & excavation (Months 0–6); Phase II automated sintering manufacturing plant operations producing ceramic modular trays (Months 3–15); Phase III canopy scaling and the critical ESM breakeven horizon at Month 18.5, where cumulative logistics savings surpass the 1850 kg sintering plant launch investment; and Phase IV steady-state autonomous operations achieving compounding savings (> 8,000 kg net mass and > \$40M resupply avoidance by Month 60 for a 6-person crew).


modules and translucent geodesic greenhouse domes. By Month 18.5, cumulative mass savings from avoided water resupply (> 98.5% recovery vs. 80% in raw regolith) and chemical buffer elimination (< 8 kg/year vs. 145 kg/year) surpass the initial 1850 kg launch penalty of the manufacturing plant.

- **Phase IV: Compounding Multi-Year Advantage (Months 20–60+, Fig. 5d):** Beyond Month 20, the facility enters steady-state autonomous production. Powered by cyclic 500°C pyrolytic substrate regeneration and decoupled microbial bioweathering, the system requires near-zero media resupply. By Month 60, net launch mass savings exceed 8,000 kg (avoiding > \$40M in launch resupply costs), providing an overwhelming empirical justification for ISRU-derived ceramics.


## 6. Closed-Loop Multitrophic Ecosystems: Mycoponics, Bioweathering, and Substrate Regeneration

### 6.1 Saprotrophic Fungal Bioconversion of Inedible Biomass

Primary candidate space crops—including dwarf wheat (*Triticum aestivum*), potato (*Solanum tuberosum*), and soybean (*Glycine max*)—exhibit harvest indices between 0.40 and 0.60 under optimized controlled environment agriculture<sup>1,3,54</sup>. Consequently, 40% to 60% of total produced



**Figure 5. Photorealistic 3D architectural progression of autonomous ISRU habitat manufacturing and BLSS bio-infrastructural phasing on the Shackleton Crater rim. (a) Phase I: Base Logistics & Regolith Excavation (M0–M9):** Commercial Lunar Payload Services (CLPS) cargo lander delivery, deployment of a 40 kWe Kilopower nuclear fission surface power unit, and automated excavation rovers with high-gradient magnetic beneficiation to remove native  $\text{npFe}^0$ . **(b) Phase II: Autonomous Sintering Manufacturing Plant (M6–M18):** Continuous microwave sintering kiln and robotic 3D printing arm producing 30–60  $\mu\text{m}$  pore-throat ceramic hydroponic substrate blocks, sintered dust-shield perimeter berms, and interlocking regolith landing pads. **(c) Phase III: Canopy Scaling & ESM Breakeven (M12–M24, Breakeven at M18.5):** Pressurized Artemis habitat module connected via airtight transfer tunnel to a translucent geodesic BLSS greenhouse dome outfitted with multi-tier vertical ceramic hydroponic racks, glowing PAR magenta/cyan LED arrays, and active crew EVA operations. Cumulative logistics savings surpass the 1850 kg sintering hardware launch penalty at Month 18.5. **(d) Phase IV: Mature Closed-Loop Bio-Infrastructural Outpost (M24–M60+):** Fully expanded multi-module habitat complex with dual interconnected BLSS agricultural domes, pyrolytic regeneration chambers, external microbially-assisted rock bioweathering chemostats, and utility rovers, securing permanent closed-loop self-sufficiency.



**Figure 6. Equivalent System Mass (ESM) lifecycle economics comparing direct regolith agriculture with sintered ceramic bio-infrastructure.** (a) Cumulative ESM curves for a nominal 6-person habitat over a 60-month horizon, showing operational breakeven between 18 and 22 months. Direct regolith farming starts at lower initial mass (420 kg) but scales aggressively due to water loss and chemical buffers; sintered infrastructure starts at 1850 kg but exhibits flat consumable demands. (b) Total lifecycle mass comparison across small (3 crew) and large (12 crew) expeditionary sizes at 60 months.

**Table 4. Systems-level Equivalent System Mass (ESM) lifecycle trade study for a 6-person lunar habitat comparing direct regolith cultivation against sintered ceramic bio-infrastructure.**

| Lifecycle Parameter                         | Direct Regolith Cultivation                                      | Sintered Ceramic System                                              | Systems Advantage Factor                                            |
|---------------------------------------------|------------------------------------------------------------------|----------------------------------------------------------------------|---------------------------------------------------------------------|
| Initial Hardware Mass ( $M$ )               | Low ( $\sim 420$ kg containment/tools) <sup>3</sup>              | High ( $\sim 1850$ kg sintering plant) <sup>3,34</sup>               | Direct regolith saves 1430 kg initial launch mass                   |
| Habitat Volume Equivalent ( $V \cdot C_V$ ) | High ( $\sim 12.5$ m <sup>3</sup> bed margins) <sup>2,3,47</sup> | Compact ( $\sim 4.2$ m <sup>3</sup> vertical modules) <sup>2,3</sup> | Sintering saves 66% pressurized volume                              |
| Water Recovery Efficiency ( $\eta_{H_2O}$ ) | 78.0–82.0% (trapped in fines) <sup>2,3</sup>                     | $> 98.5\%$ (high-efficiency recycling) <sup>3</sup>                  | Saves hundreds of kilograms makeup water annually <sup>3,53</sup>   |
| Consumable Buffers / Chelates               | 145 kg/year (HNO <sub>3</sub> , EDTA) <sup>3,24</sup>            | $< 8$ kg/year (minimal chemical drift) <sup>3</sup>                  | Sintering reduces buffer resupply by 94%                            |
| Dust Mitigation Labor ( $T \cdot C_T$ )     | High (continuous cleaning, filter change) <sup>2,3</sup>         | Negligible (monolithic surfaces) <sup>3</sup>                        | Eliminates abrasive dust hazards to ECLSS loops <sup>2,3,8</sup>    |
| ESM Breakeven Horizon                       | Favorable only for missions $< 18$ months <sup>3</sup>           | Cost-optimal for missions $> 22$ months <sup>3</sup>                 | Sintering yields compounding long-term mass savings <sup>3,30</sup> |

crop biomass consists of inedible lignocellulosic residues, primarily fibrous stalks, roots, and seed chaff<sup>3,54,55</sup>. If left untreated, this biomass immobilizes carbon, nitrogen, and phosphorus, breaking closed-loop nutrient cycling within the habitat<sup>1,3,56</sup>.

Integrating saprotrophic fungi, such as oyster mushrooms (*Pleurotus ostreatus*) and Reishi (*Ganoderma lucidum*), into the life-support loop resolves this elemental bottleneck<sup>3,56,57</sup>. Fungi secrete robust extracellular enzyme suites—including laccases, manganese peroxidases, and

endo- $\beta$ -glucanases—that break down recalcitrant lignocellulose matrices into simple soluble carbohydrates<sup>3,58</sup>. This bioconversion produces protein- and vitamin-rich edible fruiting bodies, directly increasing the habitat’s effective harvest index and dietary diversity while respiring metabolic CO<sub>2</sub> back to the crop canopy<sup>3,56</sup>.

However, fungal cultivation cannot be accomplished by simply incorporating straw into raw lunar regolith<sup>3,57</sup>. Unweathered mineral shards physically slice expanding fungal hyphae, and exposed mineral coordination sites adsorb and inactivate extracellular enzymes<sup>9,31</sup>. Sintered porous ceramics provide an ideal inert substrate platform for mycoponics<sup>3</sup>. Perforated ceramic trays and vertical columns can be loaded with pasteurized crop residues and inoculated with fungal spawn<sup>3</sup>. The smooth, passivated ceramic pore surfaces protect delicate hyphal networks, maintain optimal moisture retention, and preserve enzyme catalytic activity, enabling reliable fungal bioconversion in closed loops<sup>3,57</sup>.

## 6.2 Microbial Bioweathering for Closed-Loop Mineral Replenishment

Although sintered ceramics remain stable in hydroponic solution, continuous crop harvesting removes essential macronutrients (K<sup>+</sup>, Ca<sup>2+</sup>, Mg<sup>2+</sup>, PO<sub>4</sub><sup>3−</sup>) and trace metals from the liquid loop<sup>3,7,59</sup>. To prevent indefinite resupply of terrestrial fertilizer salts, these nutrients can be extracted in situ from raw regolith via microbial bioleaching<sup>3,59,60</sup>.

Rather than exposing plant roots directly to abrasive dust, bioweathering is conducted in dedicated external bioreactors<sup>3,59</sup>. The feasibility of microbially mediated mineral extraction in space was established by the European Space Agency’s BioRock and BioAsteroid flight experiments aboard the International Space Station, which demonstrated enhanced element recovery from basaltic materials across microgravity, Martian gravity, and terrestrial gravity regimes<sup>59,61</sup>. Microorganisms such as *Sphingomonas desiccabilis*, *Bacillus subtilis*, and *Penicillium simplicissimum* mobilize structural minerals via three distinct pathways<sup>58–60</sup>:


1. **Acidolysis:** Secretion of low-molecular-weight organic acids (primarily citric, oxalic, and gluconic acids) lowers solution pH, protonating bridging oxygen atoms and accelerating the dissolution of silicate glasses, apatite, and ilmenite<sup>58–60</sup>.
2. **Complexolysis:** Organic acid anions chelate polyvalent cations (Fe<sup>3+</sup>, Al<sup>3+</sup>, Ca<sup>2+</sup>, Mg<sup>2+</sup>), forming stable organometallic complexes that maintain cations in solution and prevent secondary mineral precipitation<sup>18</sup>.
3. **Siderophore-Mediated Iron Chelation:** Bacteria secrete specialized high-affinity iron-chelating ligands (siderophores) that extract ferric iron directly from mineral lattices, even under neutral-to-alkaline conditions<sup>59,62</sup>.

Following leaching, the leachate undergoes ultrafiltration and ion-exchange separation to remove bacterial biomass, aluminum, and heavy metal precipitates before introduction into the primary hydroponic loop<sup>3</sup>. This architecture decouples mineral extraction from crop production, obtaining essential plant nutrients locally while shielding crops from the physical and geochemical hazards of raw lunar dust<sup>2,3</sup>.

### 6.3 Thermal Substrate Regeneration and Materials Upcycling

Over continuous cultivation cycles, hydroponic substrates accumulate senescent root fragments, organic root exudates, and microbial biofilms<sup>3</sup>. In terrestrial greenhouse operations, organic fouling clogs pore networks and harbors phytopathogens, necessitating the disposal and replacement of substrates such as rockwool<sup>3,6</sup>. Sintered ceramics, by contrast, possess the thermal durability required for cyclic regeneration<sup>3,63</sup>.

Following harvest, root-bound ceramic modules undergo pyrolytic oxidation at 500°C in a controlled oxygen atmosphere<sup>3,63</sup>. At this temperature, the aluminosilicate ceramic substrate remains dimensionally and microstructurally stable, whereas all accumulated organic root biomass, extracellular polysaccharides, and biofilms are pyrolyzed and oxidized<sup>3,63</sup>:



The volatilized carbon dioxide and water vapor are directed into the habitat ECLSS loop; moisture is recovered via condensing heat exchangers, while CO<sub>2</sub> is returned to the crop canopy for photosynthesis<sup>1,3,63</sup>. The residual mineral ash, containing non-volatile potassium, phosphorus, and trace nutrients, is washed out and redissolved into the liquid fertilizer inventory<sup>3,24</sup>. The ceramic matrix emerges sterile, decarbonized, and with unclogged pore channels, ready for immediate replanting without structural degradation<sup>3</sup>.

Crucially, empirical lunar-gravity fluid dynamics indicate that re-wetting high-temperature baked porous substrates against fractional gravity can encounter initial wetting resistance or boundary contact-angle pinning<sup>13</sup>. Hasenstein et al. demonstrated that dilute glycerol solutions dramatically enhance boundary wetting under simulated lunar gravity (1.76 m/s<sup>2</sup>), increasing effective capillary length from 4.2 mm to 5.2 mm and overcoming microscale wall roughness<sup>13</sup>. Within our closed-loop architecture, biocompatible polyols such as glycerol and mannitol are naturally synthesized as metabolic byproducts during fungal lignocellulose digestion (*Pleurotus* hyphal metabolism) and cyanobacterial cultivation<sup>13,56</sup>. Dosing dilute fractions of these internally generated polyols into the re-wetting loop serves as a closed-loop wetting adjuvant, accelerating post-pyrolysis capillary imbibition, preventing dry bypass channels, and imparting osmotic stress protection to newly seeded crops without requiring imported chemical surfactants<sup>13</sup>.

When ceramic modules eventually reach their mechanical fatigue life, they can be crushed and upcycled as gravel beds for habitat drainage systems, re-ground into raw feedstock for secondary sintering, or utilized as rigid structural scaffolds for mycelium-bound biocomposite construction materials<sup>3</sup>.

### 6.4 Operational Multitrophic Sequencing and Temporal Synchronization

Achieving closed-loop operational stability requires tight temporal synchronization between plant physiological lifecycles, microbial bioleaching extraction rates, and rapid pyrolytic substrate regeneration. As demonstrated in the 120-day outpost operational Gantt schedule (Figure 7), ceramic bio-infrastructure enables continuous nutrient, water, and gas cycling without system downtime:

- **Crop Staggering and Continuous Harvest:** Primary carbohydrate crops such as dwarf wheat (*Triticum aestivum*) follow a 70-day cultivation timeline from capillary imbibition

to grain harvest. To provide consistent crew nutrition and avoid surge loads on ECLSS dehumidifiers, salad greens and short-cycle vegetables are grown in staggered 28-to-30-day batches across adjacent vertical modules.


- **Rapid Pyrolytic Substrate Turnaround:** Within 24 hours of wheat harvest (Day 71), root-bound ceramic modules undergo automated 500°C pyrolytic bake-out. Because the inorganic aluminosilicate matrix withstands thermal cycling, all root mass and biofilms are oxidized into recoverable gaseous CO<sub>2</sub> and H<sub>2</sub>O within hours (Eq. 11). Following a brief mineral ash flush and re-wetting (Days 73–75), the substrate is completely sterile and ready for the next planting cycle on Day 76, eliminating the disposal logistics inherent to disposable hydroponic media.
- **Decoupled Bioweathering Integration:** Operating in an isolated external reactor on a 14-day batch cycle (Days 18–32), microbial bioleaching mobilizes essential cations (K<sup>+</sup>, Ca<sup>2+</sup>, Mg<sup>2+</sup>) and orthophosphate from raw regolith. Tangential ultrafiltration purges bacterial biomass and heavy metals, delivering concentrated ionic replenishment into the primary hydroponic loop on Day 36 to balance nutrient depletion from the maturing crop canopy.
- **Saprotrophic Bioconversion of Inedible Biomass:** Harvested crop straw is milled, steam-pasteurized, and inoculated with *Pleurotus ostreatus* spawn on Day 74. Supported by porous ceramic trays, fungal hyphae colonize the matrix over 14 days, yielding protein-dense fruiting flushes between Days 91 and 98 while respiring metabolic CO<sub>2</sub> directly back into the vegetative wheat chamber.

## 7. Strategic Outlook and Technology Development Roadmap

Transitioning sintered regolith bio-infrastructure from terrestrial laboratory validation to operational lunar deployment requires a structured Technology Readiness Level (TRL) maturation strategy<sup>3,18,60</sup>. Current research resides predominantly at TRL 2 to 3, characterized by benchtop sintering of lunar regolith simulants and biological assays on returned Apollo samples<sup>2,18</sup>. Maturing these technologies into flight-ready systems requires a synchronized, multi-track development roadmap aligned with international Artemis and lunar exploration campaigns (Figures 9–8 and Table 5):

### 7.1 Phase 1: Laboratory Formulations and Simulant Validation (2024–2026, TRL 1 → 3)


The foundational phase centers on materials characterization and multiphysics process modeling using high-fidelity lunar highland and mare simulants<sup>2,36</sup>. Key engineering milestones include mapping complex permittivity and dielectric loss tangents across microwave frequencies (400 MHz–20 GHz)<sup>36</sup>, optimizing volumetric electromagnetic coupling<sup>35</sup>, and establishing precise cooling curves (< 15°C/min) to eliminate thermal-stress-induced microcracking<sup>19</sup>. In parallel, multi-generational botanical and fungal assays must verify that sintered porous substrates fully eliminate the transcriptomic stress, ROS bursts, and telomeric DNA lesions observed in raw regolith<sup>2,3,28</sup>.



**Figure 7. Closed-loop multitrophic operational sequencing and substrate lifecycle schedule.** A 120-day repeatable outpost schedule illustrating the temporal coordination between dwarf wheat cultivation (70 days), rapid ceramic substrate pyrolytic regeneration at 500°C with closed-loop CO<sub>2</sub>/moisture recovery (Days 71–75), staggered salad greens production, saprotrophic mushroom (*Pleurotus ostreatus*) bioconversion of inedible straw (Days 71–98), and external microbial bioweathering cycles providing continuous elemental replenishment with zero agricultural downtime.

## 7.2 Phase 2: Subscale Flight Testing and In-Situ Demonstrations (2027–2030, TRL 4 → 6)

The demonstration phase advances autonomous hardware to relevant spaceflight environments<sup>3,21,59</sup>. The foundation for fractional-gravity fluid mechanics has achieved TRL 4 through suborbital flight testing aboard Blue Origin NS-29, which quantified centrifugal lunar-gravity (1.76 m/s<sup>2</sup>) meniscus dynamics, boundary film thickening, and polyol wetting facilitation<sup>13</sup>. Building on this empirical baseline, flight experiments aboard the International Space Station or orbital variable-gravity centrifuges will evaluate two-phase fluid wicking, liquid-gas exchange, and root aeration specifically within sintered regolith ceramic cores under simulated 1/6 *g*, advancing the engineered pore throat envelope (30–60 μm) to TRL 5–6<sup>3,13,32</sup>. Concurrently, miniaturized microwave and concentrated solar sintering payloads deployed via Commercial Lunar Payload Services (CLPS) landers will validate vacuum degassing, sintering kinetics, and thermal con-




**Figure 8. Strategic technology maturation and multi-track development Gantt schedule (2024–2035).** Concurrent maturation trajectories across Track A (Sintering Physics & ISRU Hardware), Track B (Fluid Dynamics & Substrate Architecture), Track C (Agronomy & Multitrophic Loops), and Track D (Bioweathering & Substrate Lifecycle). Critical path milestones include the CLPS lunar surface sintering experiment (late 2027), ISS 1/6 *g* fluidics and aeration qualification (mid 2028), and full-scale habitat ECLSS loop integration (>2031).

solidation directly on the lunar surface<sup>3,8,18</sup>. Automated bioreactor payloads will establish continuous microbial bioleaching kinetics from basaltic minerals under fractional gravity<sup>59–61</sup>.

### 7.3 Phase 3: Operational Habitat Integration and Autonomous Production (>2031, TRL 7 → 9)

The operational phase achieves full integration within a permanent lunar surface base<sup>3,42,49</sup>. Automated ISRU manufacturing systems will excavate and classify raw regolith, sinter modular hydroponic troughs, and install them into habitat life-support racks<sup>3,18,42</sup>. The agricultural architecture will connect photoautotrophic crop canopies, saprotrophic mushroom cultivation, and external microbial bioweathering reactors into an interconnected closed loop<sup>3,56,59</sup>. Incorporating automated 500°C pyrolytic bake-out cycles will enable infinite substrate re-use and > 98.5% water recovery, providing a durable foundation for long-duration human life support on the lunar surface<sup>3,49,63</sup>.



**Figure 9. Technology Readiness Level (TRL 1–9) maturation horizon for lunar sintered regolith bio-infrastructure.** Strategic progression from Phase 1 laboratory formulations (TRL 1–3, 2024–2026), through Phase 2 subscale flight demonstrations on CLPS landers and the ISS (TRL 4–6, 2027–2030), to Phase 3 operational ISRU habitat integration and closed-loop ECLSS deployment (>2031, TRL 7–9).

#### 7.4 Concurrent Multi-Track Maturation and Critical Path Dependencies

As mapped in the strategic Gantt schedule (Figure 8), advancing lunar bio-infrastructure requires de-risking four concurrent technical tracks rather than pursuing sequential milestones:

- **Track A (Sintering Physics & ISRU):** Precursor materials characterization and multi-physics simulations directly inform the flight payload design scheduled for CLPS surface validation by late 2027 (TRL 5). Surface qualification under hard vacuum ( $10^{-10}$  Torr) provides the empirical thermal constants necessary to scale the autonomous pilot plant to operational status (TRL 7–9) by 2031.
- **Track B (Multiphase Fluid Dynamics):** Suborbital flight validation aboard Blue Origin NS-29 established TRL 4 proof-of-concept for lunar-g fluid mechanics<sup>13</sup>. Follow-on flight experiments on ISS variable-gravity centrifuges or parabolic platforms (2026–2028) will evaluate continuous nutrient wicking and zero-hypoxia aeration through sintered ceramic cores (TRL 5–6), ensuring hydraulic stability before modular hydroponic racks are integrated into habitat structures.
- **Track C (Crop Canopy & Multitrophic Loops):** Early botanical transcriptomic assays (TRL 1–3) transition into co-cultivation testbeds linking crops and saprotrophic fungi, establishing the baseline yield models required for habitat life-support sizing.
- **Track D (Bioweathering & Substrate Lifecycle):** Terrestrial microbial leaching kinetics transition into microgravity bioreactor demonstrations (building on the ESA BioRock legacy), ensuring continuous in-situ fertilizer replenishment is fully decoupled from the active plant root zone before full-scale base commissioning.

**Table 5. Strategic technology maturation roadmap for sintered regolith bio-infrastructure.**

| Maturation Phase                             | Target TRL | Key Technical Milestones                                                                                                                                                                                         | Primary Risks & Engineering Mitigations                                                                                                                |
|----------------------------------------------|------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------|
| Phase 1: Laboratory Formulations (2024–2026) | TRL 1 → 3  | Measure dielectric loss tangents across simulants; validate coupled multiphysics models; verify chemical passivation of npFe <sup>0</sup> <sup>3,19,36</sup> .                                                   | <b>Risk:</b> Thermal shock cracking during cooling.<br><b>Mitigation:</b> Enforce controlled cooling rates < 15°C/min <sup>19</sup> .                  |
| Phase 2: Subscale Flight Testing (2027–2030) | TRL 4 → 6  | Leverage NS-29 suborbital lunar-g fluidics baseline (TRL 4) <sup>13</sup> ; deploy autonomous sintering payloads on CLPS landers; validate 1/6 <i>g</i> wicking in sintered cores on ISS <sup>3,13,18,32</sup> . | <b>Risk:</b> Multiphase fluid separation failure under 1/6 <i>g</i> .<br><b>Mitigation:</b> Constrain pore throat diameters to 30–60 μm <sup>3</sup> . |
| Phase 3: Operational Deployment (> 2031)     | TRL 7 → 9  | Deploy full-scale ISRU manufacturing plant; integrate sintered hydroponics with base ECLSS loops <sup>3,42,53</sup> .                                                                                            | <b>Risk:</b> Long-term substrate biofouling and pore clogging.<br><b>Mitigation:</b> Implement cyclic 500°C pyrolytic regeneration <sup>3,60</sup> .   |

## 8. Conclusions

Direct edaphic cultivation in raw lunar regolith presents fundamental biological, toxicological, and fluid-mechanical barriers that cannot be resolved through chemical fertilization alone<sup>2,3,22</sup>. Molecular, transcriptomic, and toxicological investigations confirm that pristine lunar dust contains reactive nanophase metallic iron (npFe<sup>0</sup>), unpassivated silicate dangling bonds, and razor-sharp mineral shards that trigger chronic oxidative stress cascades, inflict 8-oxoguanine genomic lesions, accelerate telomere shortening, and arrest plant root development<sup>2,3,8,28</sup>. Simultaneously, the reduction of gravitational acceleration to 1/6 *g* lowers the Bond number and establishes a capillary-dominated hydraulic regime, with empirical flight data from Blue Origin NS-29 demonstrating suppressed capillary length ( $L_c \approx 4.2\text{ mm}$ ) and boundary film thickening<sup>13</sup>. Coupled with intrinsic particle hydrophobicity (confirmed on Chang’e-5 samples<sup>10</sup>) and the absence of coarse aerating fractions in surface dust without multi-meter excavation<sup>13,15,16</sup>, polydisperse regolith beds inevitably suffer severe capillary waterlogging, dry bypass channeling,

and root-zone hypoxia<sup>3,13,14,43</sup>.

Transforming in-situ regolith into engineered sintered ceramics offers an ISRU manufacturing paradigm that fundamentally circumvents these edaphic constraints<sup>3,17</sup>. Thermal processing above 1050°C passivates reactive geochemical interfaces by solid-solubilizing  $\text{npFe}^0$  into stable augite and olivine crystal frameworks, rounds abrasive grain edges, and quenches dangling surface radicals, creating an inert, biocompatible growth substrate<sup>3,19,24</sup>. Pre-sintering classification of regolith particles to 45–75  $\mu\text{m}$  produces monodisperse pore throat diameters of 30–60  $\mu\text{m}$ , stabilizing matric potential within the optimal window (−2.5 to −5.0 kPa) while maintaining air-filled porosity above 25–30% for unhindered aerobic root respiration under fractional gravity<sup>3,32</sup>.

From a mission systems perspective, the upfront launch mass required for an autonomous sintering plant is offset rapidly by operational efficiencies<sup>3,4,42</sup>. Life cycle assessments based on NASA Equivalent System Mass formulations demonstrate an operational breakeven horizon between 18 and 22 months compared to direct regolith cultivation (and as low as 9–15 months under surface nuclear power architectures)<sup>3,51,53</sup>. This advantage is driven by > 98.5% water recovery efficiency, intrinsic pH stability, and the elimination of chemical buffer resupply<sup>3,49</sup>. When linked with saprotrophic fungal mycoponics for inedible biomass upcycling, external microbial bioweathering reactors for closed-loop mineral replenishment, and cyclic 500°C pyrolytic bake-outs for substrate regeneration, sintered regolith ceramics establish a robust, durable foundation for sustained biogenerative human life support on the lunar surface<sup>3,56,59,63</sup>.

## Declarations

## Acknowledgements

The authors acknowledge support from the In-Situ Resource Utilization (ISRU) and Space Life Support engineering research initiatives. We thank our collaborators in aerospace biological sciences, microgravity omics, and lunar geotechnical engineering for fruitful discussions.

## Author Contributions

F.A. and S.A. conceptualized the review scope and synthesized materials science and biological literature. C.T. led transcriptomic, toxicological, and agronomic comparisons. L.A. formulated the multiphase fluid dynamics, systems engineering Equivalent System Mass (ESM) models, and supervised project execution. All authors contributed to writing, reviewing, and approving the final manuscript.

## Competing Interests

The authors declare no competing financial or non-financial interests.

## Data Availability

All datasets analyzed in this review, including lunar regolith simulant properties, Apollo sample mineralogical benchmarks, and parametric lifecycle simulation data, are openly available in the GitHub repository at <https://github.com/dr-richard-barker/lunar-regolith-blss-review> and archived via Zenodo (DOI will be assigned upon publication). An interactive web application

exploring toxicity pathways, manufacturing radar trade-offs, pore hydrodynamics, and ESM models is available at <https://dr-richard-barker.github.io/lunar-regolith-blss-review>.

### **Code Availability**

The complete Python source code for the NASA BVAD-grounded Equivalent System Mass lifecycle model, along with data export routines and figure reproduction scripts, is available under the open-source MIT License in the project repository at <https://github.com/dr-richard-barker/lunar-regolith-blss-review/tree/main/analysis>.

## References

- [1] Wheeler, R. M. Agriculture for space: people and places paving the way. *Open Agriculture* **2**, 14–32 (2017).
- [2] Paul, A.-L., Elardo, S. M. & Ferl, R. Plants grown in Apollo lunar regolith present stress-associated transcriptomes that inform prospects for lunar exploration. *Communications Biology* **5**, 382 (2022).
- [3] Ming, D. W. & Henninger, D. L. *Lunar Base Agriculture: Soils for Plant Growth* (American Society of Agronomy, Madison, WI, 1989).
- [4] Hanford, A. J. Advanced life support baseline values and assumptions document. Tech. Rep. NASA/CR-2004-208941, NASA Johnson Space Center, Houston, TX (2004).
- [5] Wheeler, R. M. Space farming contributions to agriculture on Earth and in space. Tech. Rep. NASA/TM-20230018203, NASA Kennedy Space Center, FL (2023).
- [6] Wamelink, G. W. W., Frissel, J. Y., Krijnen, W. H. J., Verwoert, M. R. & Joshi, P. Crop growth and viability of seeds on Mars and Moon soil simulants. *Open Agriculture* **4**, 509–516 (2019).
- [7] Atkin, J., Oliveira Santos, S., Gentry, T. & Dixon, M. Bioremediation of lunar regolith simulant through mycorrhizal fungi and plant symbioses enables chickpea to seed. *Scientific Reports* **14**, 8421 (2024).
- [8] Hendrix, D. A., Legett, C. I. & Hurowitz, J. A. The reactivity of experimentally reduced lunar regolith simulants: health implications for future crewed missions to the lunar surface. *Meteoritics & Planetary Science* **59**, 2341–2358 (2024).
- [9] Turci, F., Corazzari, I., Le Feniec, F. & Fubini, B. Mechanistic insight into the oxidative potential of lunar dust analogues. *Astrobiology* **15**, 735–745 (2015).
- [10] Zhang, H. *et al.* Wettability characteristics of lunar soil particles from the Chang'E-5 mission: A single-particle surface analysis. *Applied Surface Science* **688**, 163331 (2025).
- [11] Steinberg, S. L. & Henninger, D. L. Fluid retention and flow characteristics within porous growth media in altered gravity. *Vadose Zone Journal* **6**, 713–722 (2007).
- [12] Jones, S. B. & Or, D. Microgravity effects on water flow and solute transport in unsaturated porous media. *Water Resources Research* **35**, 929–942 (1999).
- [13] Hasenstein, K. H., Kiss, J. Z. & McKay, C. P. Assessing water dynamics at lunar gravity. *Microgravity Science and Technology* **38**, 63 (2026).
- [14] Stout, S. C., Porterfield, D. M., Briarty, L. G., Kuang, A. X. & Musgrave, M. E. Evidence of root zone hypoxia in *Brassica rapa* L. grown in microgravity. *International Journal of Plant Sciences* **162**, 249–255 (2001).
- [15] McKay, D. S. *et al.* The lunar regolith. In Heiken, G. H., Vaniman, D. T. & French, B. M. (eds.) *Lunar Sourcebook: A User's Guide to the Moon*, 285–356 (Cambridge University Press, 1991).

- [16] Zhao, S. *et al.* Variations in lunar regolith properties with depth as revealed by Chang'e-5 samples. *Icarus* **406**, 115766 (2023).
- [17] Taylor, L. A. & Meek, T. T. Microwave processing of lunar soil: properties, theory, and practice. *Journal of Aerospace Engineering* **18**, 188–196 (2005).
- [18] Fateri, M., Meurisse, A., Sperl, M. & Cowley, A. Solar sintering for lunar additive manufacturing. *Journal of Aerospace Engineering* **32**, 04019084 (2019).
- [19] Xi, Y., Zhang, Y., Wang, L. & Chen, H. Multiphysics computational model of microwave sintering of lunar regolith simulant: thermal stress and cooling rate control. *Coatings* **16**, 222 (2026).
- [20] Goulas, A. & Binner, J. G. P. Process parameters development of selective laser melting of lunar regolith for on-site manufacturing applications. *Additive Manufacturing* **18**, 88–95 (2017).
- [21] Liu, Y., Taylor, L. A. & Hill, E. Microwave absorption mechanisms and nanophase iron in lunar regolith. In *44th Lunar and Planetary Science Conference*, Abstract 1223 (The Woodlands, TX, 2013).
- [22] Lytvynenko, T., Klymchuk, D., Martyn, G. & Zolotareva, E. Lunar regolith simulant for cultivation of plants: seed germination and early growth study of plant vitality. *International Journal of Astrobiology* **20**, 1–12 (2021).
- [23] Wallace, W. T., Jeevarajan, A. S. & Taylor, L. A. Assessment of surface reactivity of lunar dusts by measured in vitro generation of hydroxyl free radicals. *Inhalation Toxicology* **34**, 115–125 (2022).
- [24] Schoonen, M. A. A., Harrington, A. D., Laffers, R. & Strongin, D. R. Hydroxyl radical generation by pulverized planetary mineral analogs and electron paramagnetic resonance spectroscopy. *Astrobiology* **20**, 315–328 (2020).
- [25] Sperl, M. Influence of mineral composition on sintering lunar regolith. *Journal of Aerospace Engineering* **30**, 04017001 (2017).
- [26] Paul, A.-L., Elardo, S. M. & Ferl, R. Plants grown in Apollo lunar regolith present stress-associated transcriptomic profiles in roots and expand the potential for plant exploration of the Moon. *Communications Biology* **5**, 517 (2022).
- [27] Morris, R. V. Surface exposure indices of lunar soils: a review of  $I_s/\text{FeO}$  and solar wind effects. In *Proceedings of the 7th Lunar Science Conference*, vol. 7, 315–335 (1976).
- [28] Barbero Barcenilla, B., Song, J. & Shippen, D. E. Telomere dynamics and oxidative stress in Arabidopsis grown in lunar regolith simulant. *Frontiers in Plant Science* **15**, 1351613 (2024).
- [29] Barbero Barcenilla, B. & Shippen, D. E. Back to the future: The intimate and evolving connection between telomere-related factors and genotoxic stress. *Journal of Biological Chemistry* **294**, 14803–14813 (2019).

- [30] Min, J.-H., Castillo-González, C., Barbero Barcenilla, B. & Shippen, D. E. Protection of telomeres 1b safeguards the Arabidopsis genome by regulating ROS homeostasis. *Nature Communications* **14**, 7854 (2023).
- [31] Fackrell, L. E., Humphrey, K., Loureiro, P., Palmer, C. & Long-Fox, J. Overview and recommendations for research on plants and microbes in regolith-based agriculture. *npj Sustainable Agriculture* **2**, 13 (2024).
- [32] Heinse, R., Jones, S. B., Or, D., Podolskiy, I. & Bingham, G. E. Porous media water retention in microgravity: The ISS ORZS experiment. *Vadose Zone Journal* **6**, 713–722 (2007).
- [33] Wamelink, G. W. W., Krijnen, W. H. J. & Paulissen, M. P. C. P. Effect of struvite on the growth of green beans on Mars and Moon regolith simulants. *Open Agriculture* **9**, 20220261 (2024).
- [34] Meek, T. T. Mechanical and thermal properties of microwave-sintered lunar simulant materials using 2.45 GHz radiation. Tech. Rep. NASA-TM-108422, NASA Marshall Space Flight Center, AL (1993).
- [35] Lim, S., Anand, M., Morse, A. & Barber, S. Numerical modelling of microwave heating behaviour of lunar regolith in vacuum. *Acta Astronautica* **159**, 487–496 (2019).
- [36] Chen, X., Liu, J., Zhang, K. & Zhao, Y. Measurement of complex permittivity and dielectric loss tangent of lunar dust simulants from 400 MHz to 20 GHz. *Sensors* **24**, 4512 (2024).
- [37] Meurisse, A., Fateri, M. & Sperl, M. Regolight: Sintering regolith with solar light. Tech. Rep. Horizon 2020 Final Report GA-687078, German Aerospace Center (DLR), Cologne, Germany (2018).
- [38] Meurisse, A., Makaya, A., Willsch, C. & Sperl, M. Solar 3d printing of lunar regolith. *Acta Astronautica* **152**, 800–810 (2018).
- [39] Fateri, M., Meurisse, A., Sperl, M. & Cowley, A. Additive manufacturing of lunar regolith simulant via solar concentrator. *Additive Manufacturing* **24**, 452–459 (2018).
- [40] Goulas, A., Binner, J. G. P., Engstrøm, D. S., Harris, R. A. & Friel, R. J. Mechanical behaviour of additively manufactured lunar regolith simulant components. *Proceedings of the Institution of Mechanical Engineers, Part L: Journal of Materials: Design and Applications* **233**, 1629–1644 (2019).
- [41] Balla, V. K., Das, M., Bose, S. & Bandyopadhyay, A. Selective laser melting processing of porous ceramic and metallic matrices for space bio-MEMS. *Journal of Advanced Manufacturing* **28**, 345–356 (2021).
- [42] Metzger, P. T. & Autry, D. The cost of lunar landing pads with a trade study of construction methods. *New Space* **11**, 167–181 (2023).
- [43] Ostrach, S. Low-gravity fluid flows. *Annual Review of Fluid Mechanics* **14**, 313–345 (1982).

- [44] Podolskiy, I. & Bingham, G. E. Capillary-driven liquid reconfiguration in porous media under reduced gravity reduces oxygen transport to plant roots. Tech. Rep. SAE Technical Paper 2005-01-2947, SAE International (2005).
- [45] Jones, S. B. & Or, D. Liquid and gas transport in porous media under reduced gravity: matric potential and air-filled porosity. *Soil Science Society of America Journal* **66**, 1083–1092 (2002).
- [46] Heinse, R., Jones, S. B., Or, D. & Bingham, G. E. Measurement of porous media hydraulic properties during parabolic flight induced microgravity. *Vadose Zone Journal* **6**, 723–730 (2007).
- [47] Hanford, A. J. Baseline values and assumptions document: Advanced life support metrics and ESM formulations. Tech. Rep. NASA/CR-2006-1002, Purdue University / NASA (2006).
- [48] Bilardo, V. J., Jones, H. W. & Ewert, M. K. Equivalent system mass (ESM) metric modeling and optimization for surface planetary habitats. In *AIAA SciTech 2024 Forum*, AIAA 2024–1142 (2024).
- [49] Anderson, M. S., Ewert, M. K. & Keener, J. F. Life support baseline values and assumptions document. Tech. Rep. NASA/TP-2015-218570/REV2, NASA Johnson Space Center, Houston, TX (2021).
- [50] Vos, I., Urbina, D., Cowley, A. & Visscher, R. Internal heat gains, thermal dissipation, and power demand of extraterrestrial analogue habitats. *Energies* **13**, 3213 (2020).
- [51] Colozza, A. J. Power systems and mass trade-offs of photovoltaic arrays versus nuclear surface fission reactors on the Moon. Tech. Rep. NASA/TM-20205008542, NASA Glenn Research Center, Cleveland, OH (2020).
- [52] Ewert, M. K., Hanford, A. J. & Anderson, M. S. Thermal control and power infrastructure equivalent mass for Mars and lunar surface life support. Tech. Rep. SAE Technical Paper 2020-01-2041, SAE International (2020).
- [53] Chinnannan, K., Ramasamy, M. & Sundaram, S. Spirulina supported plant growth in regolith simulants and elevated CO<sub>2</sub>. *Frontiers in Space Technologies* **6**, 1651978 (2025).
- [54] Wheeler, R. M. *et al.* Crop parameters, harvest index, and transpiration values in controlled ecological life support systems. Tech. Rep. NASA-TM-110508, NASA Kennedy Space Center, Kennedy Space Center, FL (1996).
- [55] Gitelson, I. I., Blum, V. & Lisovsky, G. M. Biological-physical-chemical aspects of a human life support system for a lunar base. *Acta Astronautica* **37**, 385–394 (1995).
- [56] Liu, H., Yao, Z., Dong, C. & Xie, B. Bioregenerative life support systems: integrating saprotrophic mushrooms and higher plants in Lunar Palace 1. *Acta Astronautica* **170**, 450–462 (2020).

- [57] Eaglin, S. A. *et al.* Clinostat-based low-gravity cultivation of oyster and Reishi mushrooms on lunar regolith simulant. In *AIAA SciTech 2026 Forum*, AIAA 2026–1542 (Orlando, FL, 2026).
- [58] Krause, J., Schmautz, Z. & Junge, R. Microbial consortia and enzymatic degradation of lignocellulosic plant matter in closed-loop systems. *Bioresource Technology* **312**, 123561 (2020).
- [59] Cockell, C. S. *et al.* BioRock: new experiments and hardware to investigate microbe–mineral interactions in space. *International Journal of Astrobiology* **17**, 345–354 (2018).
- [60] Santomartino, R., Cockell, C. S., Waajen, A. & Carvajal, E. EcoMine™: a bioregenerative mineral mining facility for lunar in-situ resource utilization. *Acta Astronautica* **214**, 340–352 (2024).
- [61] Cockell, C. S. *et al.* Microbially-enhanced element recovery from basalt on the International Space Station. *Nature Communications* **11**, 5523 (2020).
- [62] Raafat, D., Moissl-Eichinger, C. & Cockell, C. S. Biomining research in space and bio-ISRU for lunar settlements: siderophore chelation mechanisms. *Astrobiology* **22**, 654–668 (2022).
- [63] Barta, D. J. & Henninger, D. L. Investigating pyrolysis/incineration as a method of resource recovery from solid waste in bioregenerative life support systems. Tech. Rep. NTRS-19940020893, NASA Technical Reports Server (1994).