

**ASSESSMENT OF RAILROAD BALLAST DEGRADATION  
UNDER MODIFIED  
DROP-WEIGHT IMPACT LOADING CONDITIONS AND  
IMAGE-BASED  
MORPHOLOGICAL ANALYSIS**

*A Thesis*

Submitted to the School of Technology

by

**DURGESH KUMAR LEGHA**

(Roll No. 2270007)

**SANDEEP PATEL**

(Roll No. 2280043)

In Partial Fulfilment of the Requirements for the Degree of

**Bachelor of Technology in Civil Engineering**

(Specialisation: Rail Engineering)



**Gati Shakti Vishwavidyalaya**

(A Central University under the Ministry of Railways, Government of India)

Lalbag, Vadodara 390004, Gujarat, India

**April 2026**

# Candidate's Declaration

We hereby certify that

- (i) The work contained in this thesis is original and has been carried out by us jointly under the guidance of our supervisor, Dr. Dinesh Gundavaram, Gati Shakti Vishwavidyalaya, Vadodara.
- (ii) The work has not been submitted in whole or in part to any other institute or university for the award of any degree, diploma, or certificate.
- (iii) We have followed the academic guidelines and ethical code of conduct provided by Gati Shakti Vishwavidyalaya in preparing this thesis.
- (iv) Wherever we have used materials (data, experimental results, theoretical analyses, figures, tables, or text) from other sources, we have given due credit to them by citing them in the text of the thesis and by giving full bibliographic details in the reference list. Where required, permission from the copyright owners has been obtained.
- (v) The experimental programme reported in this thesis was conducted by both candidates jointly at Gati Shakti Vishwavidyalaya.

---

**Durgesh Kumar Legha**  
(2270007)

---

**Sandeep Patel**  
(2280043)

# Certificate of Thesis Supervisor

This is to certify that the thesis entitled “*Assessment of Railroad Ballast Degradation under Modified Drop-Weight Impact Loading Conditions and Image-Based Morphological Analysis*”, submitted by Durgesh Kumar Legha (Roll No. 2270007) and Sandeep Patel (Roll No. 2280043) to Gati Shakti Vishwavidyalaya, is a record of bonafide research work carried out jointly by them under my supervision. The work embodied in this thesis has not been submitted, in whole or in part, for the award of any degree, diploma, or certificate at any other institute or university. In my opinion, this thesis is of the standard required for the degree of Bachelor of Technology in Civil Engineering (Specialisation: Railway Engineering), and I consider it worthy of consideration for the said degree.

---

**Dr. Dinesh Gundavaram**

Thesis Supervisor

Assistant Professor

School of Civil Engineering,

Gati Shakti Vishwavidyalaya,

Vadodara, Gujarat – 390004.

Date: \_\_\_\_\_

Place: Vadodara

# Certificate of Approval

Certified that the thesis entitled “*Assessment of Railroad Ballast Degradation under Modified Drop-Weight Impact Loading Conditions and Image-Based Morphological Analysis*” submitted by Durgesh Kumar Legha (Roll No. 2270007) and Sandeep Patel (Roll No. 2280043) to Gati Shakti Vishwavidyalaya for the award of the Degree of Bachelor of Technology in Civil Engineering (Specialisation: Railway Engineering) has been accepted by the B.Tech. project committee members. The project presentation by the candidates was held on 23<sup>rd</sup> April 2026.

---

**Dr. Dinesh Gundavaram**  
Thesis Supervisor and  
B.Tech. Project Coordinator

---

**Dr. Dinesh Gundavaram**  
B.Tech. Project Coordinator

---

**Dr. Pradeep**  
B.Tech. Programme Coordinator



# Acknowledgement

We wish to place on record our deep sense of gratitude to all those without whose guidance, encouragement, and support this work would not have reached its present form.

Our foremost and most profound thanks are due to our supervisor, Dr. Dinesh Gundavaram, Assistant Professor at Gati Shakti Vishwavidyalaya. Across every stage of this project—from the first conversation about the limitations of the conventional Aggregate Impact Value test, through the careful re-conception of the large-scale drop-weight apparatus, the design of the nine-configuration factorial matrix, the painstaking three-dimensional scanning work, and finally the writing of this thesis—he has been a patient and rigorous mentor. The intellectual standards he holds and the clarity with which he insisted on first-principles reasoning are reflected in every chapter that follows. Any errors or shortcomings that remain are our own.

We express our sincere gratitude to the Hon’ble Vice Chancellor of Gati Shakti Vishwavidyalaya for fostering an academic environment that encourages research, innovation, and critical thinking. We are also thankful to the Programme Coordinator and all faculty members for their structured guidance, timely reviews, and valuable feedback, which helped keep this work on track.

We extend our appreciation to the laboratory technicians and technical staff of Gati Shakti Vishwavidyalaya for their assistance and cooperation during the experimental phases of this project. We also acknowledge the support extended by other departments and faculty members whose indirect contributions and institutional support facilitated the smooth execution of this work.

On a personal note, we thank our families whose belief in the value of this work was never conditional on the stage of its results, and our batchmates in the Civil Engineering programme, whose conversations sharpened many of the mechanistic interpretations that appear in the discussion chapter. In particular we are grateful to the friends who kept us company through late laboratory evenings on more occasions than we care to count.

Finally, we acknowledge the broader community of railway geotechnics researchers whose published work we have cited in this thesis. The scientific literature is a cumulative enterprise, and every modest contribution in this document rests on decades of careful experimentation and thought by others.

**Durgesh & Sandeep**

# Abstract

The thesis focuses on addressing the critical issue of railway ballast degradation, which significantly impacts the safety, stability, and operational efficiency of railway tracks. Tailored specifically to the unique conditions of Indian Railways, this research aims to develop a deeper understanding of ballast behaviour under impact loading and to predict the quantum of ballast degradation using 3D image processing as well as machine-learning models.

At the core of the study is the modification of the European-standard drop-weight impact test apparatus to better align with Indian railway ballast specifications and operational conditions. The modified setup accurately replicates on-field stress conditions experienced by ballast in the Indian context, providing a more relevant and reliable framework for analysis. The modified apparatus serves as a critical tool for evaluating ballast degradation under controlled yet realistic conditions, delivering nominal contact stresses of 275 kPa (at a 300 mm drop height) and 523 kPa (at a 450 mm drop height) corresponding to the 22.5-tonne axle load characteristic of Indian Railways.

A significant innovation in this study is the use of advanced 3D image processing techniques to evaluate morphological changes in ballast particles before and after impact testing. High-resolution 3D meshes are captured to analyse changes in particle shape, size, and texture, providing a detailed and quantitative understanding of ballast degradation. A paired-particle protocol applied to 45 marked tracer particles across nine experimental configurations enables precise measurement of deterioration, allowing identification of critical thresholds and damage modes (diffuse abrasion vs. catastrophic fracture) that are not detectable through traditional sieve analysis.

The outcomes of this study contribute to railroad ballast degradation assessment using image-based morphology and machine learning, delivering a scalable and accurate alternative to conventional physical testing, with substantial implications for railway safety and maintenance planning.

**Keywords:** Railway ballast; drop-weight impact loading; RDSO gradation; Fouling Index; 3D structured-light scanning; particle morphology; under-ballast mats; ballast degradation.

# Outcomes of This Project

## Journals

1. Legha D. and Gundavaram D., *Composite Railway Sleepers: A Review of Mechanical Performance, Durability and Adoption Challenges*, *Railw. Eng. Sci.* (2026) (Under Review). (IF = 5.4)
2. Legha Durgesh K., Gundavaram Dinesh, Patel Sandeep, *A large-scale drop-weight impact testing apparatus for assessment of Indian Railway ballast: influence of stress level and subgrade–interlayer configuration on settlement and particle degradation*, *Construction and Building Materials* (2026) (Under Review). (IF = 7.2)

## Patents

1. Gundavaram D., Legha D., (2026), *Assessment of railroad ballast degradation under modified drop-weight impact loading conditions*. (Indian Utility Patent) (Draft Prepared).

## Conference Papers

1. Legha D.K., Patel S., Gundavaram D., (2026) *Optimization of Bitumen Content in Bitumen-Stabilized Ballast Using Flowability Characteristics*, Recent Research on Environmental Earth Sciences, MedGU 2025, Springer (Accepted, In Press).
2. Legha D., Gundavaram D., Mishra G., (2026) *Global Practices of Railway Drainage Systems with Emphasis on India and Emerging Innovation*, Geotechnical Practices for Innovations and Sustainability, Proceedings of the Indian Geotechnical Conference (IGC 2025), Lecture Notes in Civil Engineering, Springer (Accepted, In Press).



Scan QR code for project video.

# Contents

|                                                                           |            |
|---------------------------------------------------------------------------|------------|
| <b>Candidate's Declaration</b>                                            | <b>i</b>   |
| <b>Certificate of Thesis Supervisor</b>                                   | <b>ii</b>  |
| <b>Certificate of Approval</b>                                            | <b>iii</b> |
| <b>Acknowledgement</b>                                                    | <b>iv</b>  |
| <b>Abstract</b>                                                           | <b>v</b>   |
| <b>Outcomes of This Project</b>                                           | <b>vi</b>  |
| <b>List of Abbreviations</b>                                              | <b>xiv</b> |
| <b>List of Symbols</b>                                                    | <b>xvi</b> |
| <b>1 Introduction</b>                                                     | <b>1</b>   |
| 1.1 Background: the central role of ballast in railway track . . . . .    | 1          |
| 1.2 Problem Statement . . . . .                                           | 3          |
| 1.3 Objectives of the Thesis . . . . .                                    | 3          |
| 1.4 Scope . . . . .                                                       | 4          |
| <b>2 Literature Review</b>                                                | <b>6</b>   |
| 2.1 The ballast layer in the railway track system . . . . .               | 6          |
| 2.1.1 Functional requirements . . . . .                                   | 6          |
| 2.2 Ballast Degradation . . . . .                                         | 7          |
| 2.2.1 Fouling and its engineering consequences . . . . .                  | 7          |
| 2.2.2 Fouling Index . . . . .                                             | 8          |
| 2.2.3 Factors affecting ballast breakage and its propagation . . . . .    | 9          |
| 2.3 Laboratory characterisation of ballast under impact loading . . . . . | 10         |
| 2.3.1 Impact-loading studies and the size-of-mould problem . . . . .      | 10         |
| 2.4 Ballast Reinforcement Methods . . . . .                               | 12         |
| 2.5 Three-dimensional morphological characterisation of ballast . . . . . | 13         |
| 2.5.1 From sieve-based to shape-based descriptors . . . . .               | 13         |
| 2.5.2 The rise of structured-light scanning . . . . .                     | 14         |
| 2.5.3 Paired before-after protocols . . . . .                             | 15         |
| 2.6 Synthesis and identification of gaps . . . . .                        | 15         |
| 2.6.1 Synthesising observations . . . . .                                 | 15         |

|          |                                                                                  |           |
|----------|----------------------------------------------------------------------------------|-----------|
| <b>3</b> | <b>Materials and Methodology</b>                                                 | <b>17</b> |
| 3.1      | Basalt ballast . . . . .                                                         | 17        |
| 3.1.1    | Source and parent rock . . . . .                                                 | 17        |
| 3.1.2    | Particle size distribution and the RDSO envelope . . . . .                       | 18        |
| 3.1.3    | Physical and mechanical properties . . . . .                                     | 18        |
| 3.2      | Reinforcement Conditions . . . . .                                               | 18        |
| 3.2.1    | Unreinforced (UR) control . . . . .                                              | 19        |
| 3.2.2    | Rubber Under-Ballast Mat (RUBM) . . . . .                                        | 19        |
| 3.2.3    | Polyurethane Under-Ballast Mat (PUBM) . . . . .                                  | 19        |
| 3.2.4    | Base conditions (FB / RB) . . . . .                                              | 20        |
| 3.3      | Particle scanning . . . . .                                                      | 20        |
| 3.3.1    | Rationale for the paired-particle design . . . . .                               | 20        |
| 3.3.2    | Selection criteria . . . . .                                                     | 21        |
| 3.3.3    | Pre-test structured-light scanning . . . . .                                     | 21        |
| 3.4      | The modified drop-weight impact apparatus . . . . .                              | 22        |
| 3.4.1    | Comparison with the conventional Aggregate Impact Value ap-<br>paratus . . . . . | 22        |
| 3.5      | Stress and energy calibration to Indian Railways field loading . . . . .         | 23        |
| 3.5.1    | Field stress estimation . . . . .                                                | 23        |
| 3.5.2    | Apparatus stress and energy . . . . .                                            | 24        |
| 3.6      | Sample preparation and test protocol . . . . .                                   | 24        |
| 3.6.1    | Specimen assembly . . . . .                                                      | 24        |
| 3.6.2    | Blow-by-blow test protocol . . . . .                                             | 25        |
| 3.6.3    | Test matrix and nomenclature . . . . .                                           | 26        |
| 3.6.4    | Post-test sieve analysis . . . . .                                               | 26        |
| 3.6.5    | Bulk degradation indices . . . . .                                               | 26        |
| 3.7      | Image-based three-dimensional morphological analysis . . . . .                   | 27        |
| 3.7.1    | Scan protocol and mesh quality control . . . . .                                 | 27        |
| 3.7.2    | Twenty-two morphological descriptors . . . . .                                   | 27        |
| 3.7.3    | Python script . . . . .                                                          | 27        |
| <b>4</b> | <b>Results of Impact Test Analysis</b>                                           | <b>37</b> |
| 4.1      | Axial settlement . . . . .                                                       | 37        |
| 4.2      | Peak hammer force per test . . . . .                                             | 37        |
| 4.3      | Indian Railway Fouling Index $FI_{IN}$ . . . . .                                 | 38        |
| 4.4      | Settlement–fouling correlation . . . . .                                         | 41        |
| 4.5      | Discussion . . . . .                                                             | 42        |

|          |                                                                          |           |
|----------|--------------------------------------------------------------------------|-----------|
| <b>5</b> | <b>Results of Morphological Analysis</b>                                 | <b>44</b> |
| 5.1      | Per-particle volume change and outlier identification . . . . .          | 44        |
| 5.2      | Shape evolution: sphericity, convexity, angularity and roundness . . . . | 45        |
| 5.2.1    | Angularity . . . . .                                                     | 45        |
| 5.2.2    | Sphericity . . . . .                                                     | 46        |
| 5.2.3    | Convexity . . . . .                                                      | 47        |
| 5.2.4    | Roundness . . . . .                                                      | 47        |
| 5.3      | Discussion: heat-map synthesis . . . . .                                 | 48        |
| <b>6</b> | <b>Conclusions and Recommendations</b>                                   | <b>52</b> |
| 6.1      | Conclusions . . . . .                                                    | 52        |
| 6.2      | Novel contributions . . . . .                                            | 53        |
| 6.2.1    | Apparatus and method . . . . .                                           | 53        |
| 6.2.2    | Scientific findings . . . . .                                            | 53        |
| 6.3      | Limitations of the study . . . . .                                       | 54        |
| 6.4      | Recommendations for future work . . . . .                                | 54        |
|          | <b>References</b>                                                        | <b>56</b> |
| <b>A</b> | <b>Tabulated Data Excerpts</b>                                           | <b>62</b> |
| A.1      | Test matrix — full specification . . . . .                               | 62        |
| A.2      | Per-particle paired morphology — summary table . . . . .                 | 63        |
| A.3      | Complete post-test sieve data . . . . .                                  | 63        |
| <b>B</b> | <b>Python Morphological Analysis Script</b>                              | <b>64</b> |
| B.1      | Software environment . . . . .                                           | 64        |
| B.2      | Pipeline script — <code>ballast_analyzer.py</code> . . . . .             | 64        |

# List of Figures

|      |                                                                                                                                                                                                                                                               |    |
|------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----|
| 1.1  | Indian Railways ballasted track in service showing the sleeper–ballast system. . . . .                                                                                                                                                                        | 2  |
| 1.2  | Comparison of the modified impact-testing apparatus designed and commissioned at GSV. . . . .                                                                                                                                                                 | 5  |
| 2.1  | Established falling height through the impact loading test for implementing the characterised stress levels on ballast (Koohmishi & Guo, 2023). . . . .                                                                                                       | 12 |
| 2.2  | Morphological parameters and the $S$ , $I$ , $L$ bounding-box dimensions of a ballast particle. . . . .                                                                                                                                                       | 14 |
| 3.1  | Experimental methodology flowchart (10-stage programme). . . . .                                                                                                                                                                                              | 29 |
| 3.2  | Pre-test particle size distribution of the basalt ballast used in the experimental programme, plotted against the upper and lower envelope curves of the RDSO specification. . . . .                                                                          | 30 |
| 3.3  | Pile of the RDSO-gradation basalt ballast used in the experimental programme (Civil Lab, GSV). . . . .                                                                                                                                                        | 30 |
| 3.4  | Rubber Under-Ballast Mat (RUBM) disc, 12 mm thick natural rubber, cut to 300 mm diameter. . . . .                                                                                                                                                             | 31 |
| 3.5  | Polyurethane Under-Ballast Mat (PUBM, commercial Getzner product), cut to 300 mm diameter. . . . .                                                                                                                                                            | 31 |
| 3.6  | Test mould prepared with the 100 mm flexible base sand cushion (FB condition), photographed immediately before placement of the pad and the ballast fill. . . . .                                                                                             | 32 |
| 3.7  | Marked tracer particles showing the white acrylic paint patch and the hand-written numeric identifier code. . . . .                                                                                                                                           | 33 |
| 3.8  | EinScan structured-light scanner (Shining 3D) in operation with a marked tracer particle mounted on the automatic turntable. . . . .                                                                                                                          | 34 |
| 3.9  | Modified drop-weight impact apparatus designed and commissioned at GSV. (a) Overall view of the apparatus and its frame. (b) Close-up of the load-transfer assembly (bearing plate, 5 t load cell, striker plate) and the digital peak-force display. . . . . | 34 |
| 3.10 | Assembling the test specimen in the mould (photograph without load-cell assembly). . . . .                                                                                                                                                                    | 34 |
| 3.11 | Post-impact-test sieve analysis. . . . .                                                                                                                                                                                                                      | 35 |
| 3.12 | Three-dimensional particle scanning workflow used in the present study.                                                                                                                                                                                       | 35 |
| 3.13 | Particle aligning for multiple scans to ensure complete surface coverage.                                                                                                                                                                                     | 35 |



|      |                                                                                                                                                                                                                                                                                          |    |
|------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----|
| 3.14 | Screenshot of the running morphological-analysis script. . . . .                                                                                                                                                                                                                         | 36 |
| 4.1  | Cumulative net axial settlement of the ballast specimen as a function of hammer-blow count $N$ for the four monitored tests. The shaded band at high $N$ marks the shake-down (steady-state) regime within which incremental settlement per blow falls below approximately 0.5 mm. . . . | 38 |
| 4.2  | Incremental settlement per blow within each five-blow interval, for the four monitored tests. The fall in the per-blow rate from the 0–5 interval to the 15–20 interval defines the transition from active densification to the shake-down regime. . . . .                               | 39 |
| 4.3  | Mean peak hammer force recorded by the in-line 5 t load cell for each of the nine tests, grouped by drop height. . . . .                                                                                                                                                                 | 40 |
| 4.4  | Indian Railway Fouling Index $FI_{IN} = P_{0.075} + P_{20}$ (full bar) and the $P_{0.075}$ fines contribution (orange overlay) for each of the nine tests. . . .                                                                                                                         | 41 |
| 4.5  | Indian Railway Fouling Index $FI_{IN}$ plotted against the net cumulative settlement at $N = 20$ for the four monitored tests. . . . .                                                                                                                                                   | 42 |
| 5.1  | Per-particle relative volume change $\% \Delta V$ (horizontal axis) plotted against per-particle relative sphericity change $\% \Delta \Psi$ (vertical axis), for all 45 tracer particles, with outliers (Mode B) identified by the Tukey $1.5 \times IQR$ fence. . . . .                | 45 |
| 5.2  | Angularity index before vs. after the impact-loading test for all 45 tracer particles. The angularity values reported here are negative scalars; less-negative (closer to zero) values indicate smoother corners. . . . .                                                                | 47 |
| 5.3  | Sphericity before vs. after the impact-loading test, for all 45 tracer particles. . . . .                                                                                                                                                                                                | 48 |
| 5.4  | Convexity $C = V/V_{ch}$ before vs. after the impact-loading test, for all 45 tracer particles. Layout and statistics as for Figure 5.3. . . . .                                                                                                                                         | 49 |
| 5.5  | Roundness before vs. after the impact-loading test, for all 45 tracer particles. . . . .                                                                                                                                                                                                 | 50 |
| 5.6  | Heat maps of mean per-particle $\%$ -change in fourteen morphological descriptors across the nine tests, with outlier particles removed. Panel (a): size and primary shape descriptors. Panel (b): roundness and shape-ratio descriptors. . . . .                                        | 51 |

# List of Tables

|     |                                                                                                                                                                                                                                                                                                 |    |
|-----|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----|
| 2.1 | Representative drop-weight impact studies on railway ballast: apparatus and method comparison. . . . .                                                                                                                                                                                          | 13 |
| 3.1 | Physical and mechanical properties of the basalt ballast used in the experimental programme. . . . .                                                                                                                                                                                            | 18 |
| 3.2 | Principal specification of the modified apparatus in comparison to the conventional IS:2386 Part IV Aggregate Impact Value apparatus. Only the headline parameters are listed; the full specification is in the patent documentation (Appendix B). . . . .                                      | 23 |
| 3.3 | The nine test configurations of the experimental programme. . . . .                                                                                                                                                                                                                             | 26 |
| 4.1 | Indian Railway Fouling Index $FI_{IN}$ , the fines fraction $P_{0.075}$ , and the 20 mm-passing fraction $P_{20}$ for the nine test configurations. Values computed per the $FI_{IN}$ definition of Section 3.6.5 from the post-test sieve data archived in the laboratory spreadsheet. . . . . | 39 |
| 5.1 | Per-test summary of the volume-change response. $n_{in}$ = inlier count, $n_{out}$ = outlier count, mean $\% \Delta V$ and median $\% \Delta V$ computed on the Mode A (inlier) population. . . . .                                                                                             | 46 |
| A.1 | Complete nine-configuration test matrix with measured peak force, kinetic energy, specimen mass, ballast-column height at 1200 kg/m <sup>3</sup> reference density, and the legacy $\rightarrow$ systematic test-number mapping. .                                                              | 62 |
| A.2 | Per-configuration Mode A summary of the principal morphological change descriptors. Mode B outliers excluded. $\Delta V$ , $\Delta \Psi$ , $\Delta C$ in %-relative change. $n$ = Mode A sample size in each configuration. . . .                                                               | 63 |
| A.3 | Percentage retained on each sieve, post-test, for the nine configurations. Rows are sieve sizes; columns are tests. Values in weight percent of the post-test specimen mass. . . . .                                                                                                            | 63 |

# List of Abbreviations

| Abbreviation     | Full form / Description                                                   |
|------------------|---------------------------------------------------------------------------|
| AAV              | Aggregate Abrasion Value                                                  |
| AIV              | Aggregate Impact Value                                                    |
| ANOVA            | Analysis of Variance                                                      |
| BIS              | Bureau of Indian Standards                                                |
| BTP              | B.Tech. Project                                                           |
| CAD              | Computer-Aided Design                                                     |
| $D/d_{\max}$     | Ratio of mould diameter to maximum particle size (boundary criterion)     |
| DEM              | Discrete Element Method                                                   |
| EN               | European Norm / European Standard                                         |
| FB               | Flexible Base (100 mm compacted sand layer, present study)                |
| FI               | Fouling Index (after Selig & Waters, 1994)                                |
| $FI_{\text{IN}}$ | Indian Railway Fouling Index                                              |
| GSV              | Gati Shakti Vishwavidyalaya                                               |
| HH               | High Height (450 mm drop) — legacy laboratory label                       |
| IPO              | Indian Patent Office                                                      |
| IQR              | Inter-Quartile Range                                                      |
| IRJ              | Insulated Rail Joint                                                      |
| IS               | Indian Standard                                                           |
| LAA              | Los Angeles Abrasion                                                      |
| LH               | Low Height (300 mm drop) — legacy laboratory label                        |
| Mode A           | Diffuse corner abrasion (present-study classification)                    |
| Mode B           | Catastrophic single-particle bulk fracture (present-study classification) |
| PUBM             | Polyurethane Under-Ballast Mat (Getzner, present study)                   |
| $P_{0.075}$      | Percentage finer than 0.075 mm sieve                                      |
| $P_{20}$         | Percentage finer than 20 mm sieve                                         |
| PSD              | Particle Size Distribution                                                |
| RB               | Rigid Base (concrete mould floor, present study)                          |

---

| Abbreviation | Full form / Description                                 |
|--------------|---------------------------------------------------------|
| RDSO         | Research Designs and Standards Organisation             |
| RUBM         | Rubber Under-Ballast Mat (12 mm, present study)         |
| SciPy        | Scientific Python library                               |
| SEM          | Scanning Electron Microscopy                            |
| SL           | Structured-Light (scanning)                             |
| STL          | Stereolithography (triangular surface-mesh file format) |
| UBM          | Under-Ballast Mat                                       |
| UIC          | Union Internationale des Chemins de Fer                 |
| UR           | Unreinforced (no pad, present study)                    |
| USP          | Under-Sleeper Pad                                       |

---

# List of Symbols

| Symbol           | Meaning (units)                                                  |
|------------------|------------------------------------------------------------------|
| $A$              | Surface area of a particle ( $\text{mm}^2$ )                     |
| $A_{\text{ch}}$  | Convex-hull surface area ( $\text{mm}^2$ )                       |
| $a, b, c$        | Semi-axes of best-fit ellipsoid (mm), $a \geq b \geq c$          |
| $C$              | Convexity = $V/V_{\text{ch}}$ (dimensionless)                    |
| $D$              | Mould internal diameter (mm)                                     |
| $D_{\text{eq}}$  | Equivalent spherical diameter = $(6V/\pi)^{1/3}$ (mm)            |
| $d_{\text{max}}$ | Maximum particle size in a gradation (mm)                        |
| $E$              | Elongation = $I/L$ (dimensionless)                               |
| $F$              | Flatness = $S/I$ (dimensionless)                                 |
| $g$              | Gravitational acceleration, $9.81 \text{ m/s}^2$                 |
| $h$              | Drop height of hammer (mm or m)                                  |
| $I$              | Intermediate bounding-box dimension (mm)                         |
| $K_e$            | Kinetic energy of hammer at impact = $mgh$ (J)                   |
| $L$              | Long bounding-box dimension (mm)                                 |
| $L/S$            | Aspect ratio (dimensionless)                                     |
| $(L + I)/(2S)$   | Flatness index (dimensionless)                                   |
| $m$              | Hammer mass (kg)                                                 |
| $N$              | Number of blows (dimensionless)                                  |
| $n$              | Sample size (dimensionless)                                      |
| $p$              | Statistical $p$ -value (dimensionless)                           |
| $R$              | Roundness descriptor (dimensionless, scanner-specific)           |
| $S$              | Short bounding-box dimension (mm)                                |
| $t$              | Student's $t$ -statistic (dimensionless)                         |
| $V$              | Volume of a particle ( $\text{mm}^3$ )                           |
| $V_{\text{ch}}$  | Convex-hull volume ( $\text{mm}^3$ )                             |
| $\sigma$         | Nominal contact stress at specimen surface (kPa)                 |
| $\Delta X$       | Change in descriptor $X = X_{\text{after}} - X_{\text{before}}$  |
| $\% \Delta X$    | Percentage change in $X = \Delta X/X_{\text{before}} \times 100$ |
| $\Psi$           | Sphericity = $\pi^{1/3} (6V)^{2/3}/A$ (Wadell, 1932)             |

# Chapter 1

## Introduction

### 1.1 Background: the central role of ballast in railway track

Railway ballast is a fundamental component of conventional track structures, consisting of coarse, angular aggregates—typically crushed stone—placed beneath and around sleepers to ensure track stability and performance. Its primary functions include distributing train loads from the sleepers to the underlying subgrade, providing lateral and longitudinal resistance to track movement, and facilitating effective drainage to prevent water accumulation and loss of strength in the track foundation. The mechanical behaviour of ballast is governed by factors such as particle size, shape, gradation, and strength, which influence its load-bearing capacity and resistance to degradation under repeated train loading. Over time, ballast experiences fouling and particle breakage, which can reduce its drainage capability and stiffness, leading to track settlement and increased maintenance requirements. Recent studies emphasise the importance of understanding ballast’s geomechanical properties and dynamic response to improve track longevity and safety, especially under high-speed and heavy-haul conditions. Consequently, ongoing research explores alternative materials, stabilisation techniques, and advanced monitoring methods to enhance ballast performance and sustainability in modern railway systems.

The mechanical behaviour of the ballast layer is governed, ultimately, by the morphological state of its constituent grains. Freshly quarried angular particles possess interlocking micro-asperities that generate very high inter-particle friction; a well-compacted layer of such particles can carry train loads with lateral deformations of less than a millimetre per million-gross-tonne of traffic. The same layer, after a decade of service, contains particles that have been rounded by abrasion and reduced in size by fracture. The rounded assembly has lower friction, the fractured fines infill the voids and reduce drainage, and the layer settles more quickly under each successive load cycle. Track geometry degrades, the track engineer dispatches a tamping machine, and a maintenance cycle begins. The maintenance cost of ballasted track is dominated by this cycle, and delaying the onset of measurable degradation by even a few years has first-order economic consequences for a national rail network.

Under ordinary cyclic traffic the process of ballast degradation is gradual and

reasonably predictable. Under impact loading—the class of loading generated at rail joints, wheel flats, transition zones where the track stiffness changes abruptly, turnouts, and level crossings—the process is accelerated by impulse stresses that rise briefly to values well in excess of the contact and tensile strength of individual grains. Accelerated settlement rates have been reported in the metre-scale vicinity of bridge abutments at levels several times the rate in the adjoining line, attributable directly to the sharp change in support stiffness that produces momentary contact-stress amplification. It is precisely at these hot-spots of impact loading that ballast degradation is most costly, both in maintenance and in the small-probability tail of safety-relevant events.

For Indian Railways—the fourth-largest rail network in the world by route-kilometre and one of the most heavily loaded by axle-load  $\times$  traffic—the engineering problem of ballast degradation is particularly sharp. The network operates a mix of 22.5 t axle-load freight, heavy-haul corridors with axle loads proposed to move beyond 25 t, high-density suburban passenger services, and, increasingly, semi-high-speed passenger traffic. The ballast specification governing this mix—RDSO (2023)—prescribes angular, machine-crushed stone with a 20–65 mm size envelope. The in-service vertical contact stress at the ballast–sleeper interface is estimated to range from approximately 240 kPa under ordinary passenger loading to values approaching 500 kPa under the combined static and dynamic action of heavy freight and impact events. Any laboratory test that purports to characterise the degradation behaviour of Indian ballast must reproduce particles in this size range and stresses in this band; any test that does not, reports a number whose physical meaning is uncertain.



**Figure 1.1.** Indian Railways ballasted track in service showing the sleeper–ballast system.

## 1.2 Problem Statement

This thesis addresses two coupled gaps in Indian railway ballast assessment—gaps that reinforce each other and cannot be closed independently.

Railroad ballast, typically composed of coarse, angular aggregates, plays a critical role in providing structural support, stability, and drainage for railway tracks. Under repeated train loading, ballast undergoes degradation through mechanisms such as particle breakage, abrasion, and fouling, leading to reduced track performance, increased settlement, and higher maintenance costs. Traditional methods for assessing ballast degradation, such as sieve analysis and manual inspection, are time-consuming, labour-intensive, and often subjective, limiting their scalability and precision. The degradation process is influenced by factors including impact loading conditions, particle morphology (size, shape, and surface texture), and environmental variables, yet these interactions are not fully understood or efficiently quantified.

The primary challenge is the lack of an efficient, objective, and automated method to assess railroad ballast degradation under realistic loading conditions. Current drop-weight impact tests simulate train-induced stresses, but standard protocols do not adequately account for variations in loading intensity, frequency, or ballast morphological changes over time. Moreover, traditional post-test analysis fails to capture the dynamic evolution of particle characteristics—such as angularity loss or fragmentation patterns—which are critical to understanding degradation mechanisms. This gap hinders the ability to predict ballast performance, optimise maintenance schedules, and design more durable track systems. There is a need for an innovative approach that integrates advanced testing conditions with analytical tools to provide a comprehensive, data-driven assessment of ballast degradation.

## 1.3 Objectives of the Thesis

The thesis pursues five objectives:

- (i) To modify the standard drop-weight impact test apparatus (based on European standards) to replicate Indian railway ballast characteristics and loading conditions.
- (ii) To evaluate the degradation behaviour of railway ballast under repeated impact loading using the modified testing setup.
- (iii) To investigate the effectiveness of different reinforcement conditions in reducing ballast degradation under impact loads.
- (iv) To quantify morphological changes in degraded ballast particles using 3D image



processing techniques (shape, angularity, and size variations).

- (v) To establish relationships between impact-induced degradation and morphological characteristics for improved assessment of ballast performance.

## 1.4 Scope

The scope of this thesis focuses on the experimental and analytical investigation of railway ballast degradation under controlled impact loading conditions, with particular emphasis on adapting existing testing methodologies to Indian railway requirements. The study involves modifying and calibrating a drop-weight impact test apparatus, originally based on European standards, to simulate realistic loading conditions representative of Indian Railways, including higher axle loads and varying traffic characteristics. Laboratory experiments are conducted to evaluate ballast degradation behaviour under repeated impact loading, examining parameters such as particle breakage, gradation changes, and degradation indices. In addition, the research assesses the effectiveness of selected reinforcement or stabilisation techniques in reducing ballast deterioration. A key component of the study is the application of advanced three-dimensional image-processing methods to quantify changes in ballast particle morphology, including shape, angularity, and surface characteristics before and after degradation. The thesis further aims to establish correlations between mechanical degradation and morphological evolution of ballast particles, contributing to improved understanding of ballast performance. However, the study is limited to laboratory-scale investigations, specific ballast types used in Indian Railways, and impact loading conditions, without extensive consideration of long-term field performance or environmental effects.



**Conventional  
Apparatus (IS 2386 (IV))**



**Modified Apparatus (Designed  
& Commissioned at GSV)**

**Figure 1.2.** Comparison of the modified impact-testing apparatus designed and commissioned at GSV.

# Chapter 2

## Literature Review

The literature on ballast degradation is both deep and unusually fragmented. It is deep because serious laboratory work on granular skeletons under cyclic and impact loading has been continuous since the 1960s, and it has been reinforced in the last two decades by discrete-element modelling, by field monitoring of mainline track, and—most recently—by three-dimensional imaging of individual grains. It is fragmented because these different strands have grown largely independently of one another: the cyclic-triaxial community and the impact community have different journals and different index vocabularies; the image-analysis community has only recently made sustained contact with the degradation-mechanics community; and the practitioners who set national ballast specifications have, in turn, moved at their own pace. This review is organised thematically rather than paper-by-paper in order to make sense of these strands together.

Six themes are traced in turn. Section 2.1 places the ballast layer in the track system and reviews its functional requirements. Section 2.2 discusses the mechanisms of ballast degradation that the thesis is ultimately concerned with. Section 2.3 examines the laboratory characterisation of degradation under cyclic and impact loading, with particular attention to the apparatus and the size-effect problem that motivates Chapter 3. Section 2.4 reviews the use of resilient substructure inclusions—pads, mats, and compliant bases—to intercept and dissipate the impulsive energy that drives grain-scale damage. Section 2.5 surveys the emergence of three-dimensional morphological characterisation, which supplies the measurement framework used in Chapter 3 and applied in Chapter 5. Section 2.6 draws the preceding five sections together and identifies the two gaps—the apparatus gap and the characterisation gap—that this thesis addresses.

### 2.1 The ballast layer in the railway track system

#### 2.1.1 Functional requirements

The conventional ballasted track is a layered granular–structural system whose task is to convert the concentrated contact forces at the wheel–rail interface into diffuse, tolerable stresses at the subgrade surface. The ballast layer—a 250–350 mm deep mat of crushed, angular stone placed beneath and around the sleepers—is the principal

load-distributing element of this system. Selig and Waters (1994) enumerated its six primary functions: (i) distribution of vertical wheel loads from the sleepers to the subgrade over an area substantially larger than the sleeper footprint; (ii) restraint against lateral and longitudinal sleeper movement through inter-particle friction and interlock; (iii) absorption of some fraction of the dynamic energy imparted by passing trains; (iv) provision of rapid drainage of water away from the track formation; (v) accommodation of tamping and lining operations without structural damage; and (vi) maintenance of a resilient bearing surface that allows the rail to deflect elastically under load without plastic accumulation at the sleeper–ballast contact.

These six functions impose mutually constraining requirements on the material. High lateral restraint demands angular, machine-crushed grains with strong inter-particle interlock; high drainage demands a uniformly graded, coarse assembly with open voids; load distribution demands adequate depth and density; and long service life demands particles hard enough to resist both impact-driven fracture and cumulative abrasion. These requirements are reflected in national ballast specifications with remarkable consistency: AREMA (2020) in the United States, UIC 719R in continental Europe, and the RDSO specification (RDSO, 2023) in India all prescribe crushed, angular stone of comparable hardness and in a comparable 20–65 mm size band, albeit with local variations in the permissible fines fraction and in the tolerated parent-rock types.

A small but growing body of Indian-context research has begun to address the specific behaviour of RDSO-gradation ballast. Gundavaram and Hussaini (2023) — the present supervisor — demonstrated in cyclic triaxial tests on elastomeric-polyurethane-reinforced ballast that the inclusion of a polymeric element between the ballast and the subgrade substantially reduces cumulative plastic deformation and attenuates the growth of the fines fraction. That result, on cyclic loading, motivates in part the use of the polyurethane under-ballast mat (PUBM) condition in the present impact-loading study.

## 2.2 Ballast Degradation

### 2.2.1 Fouling and its engineering consequences

The engineering consequence of the three grain-scale mechanisms is the progressive generation of fines—particles finer than 0.075 mm in the Selig and Waters (1994) usage, or finer than the RDSO 0.075 mm sieve in the Indian adaptation. These fines infill the voids of the ballast skeleton and give rise to the condition known as *fouling*. A fouled ballast has reduced drainage capacity, reduced shear strength, a softer and more plastic response to cyclic load, and a higher rate of settlement under repeated traffic

(Huang et al., 2009; Tutumluer, 2013). The practical maintenance responses—ballast cleaning, partial renewal, and in extreme cases full deep-screening—are costly and disruptive, and the engineering motivation for slowing the rate of fines generation is direct and economic.

Field fouling has an exogenous contribution—coal and mineral-ore spillage from freight wagons, wind-blown dust, and subgrade pumping—that is not reproducible in a sealed laboratory mould. The laboratory characterisation of degradation therefore measures the endogenous contribution only. Within the laboratory, the self-generated fouling contribution is quantified by a family of bulk indices whose development and limitations are reviewed next.

### 2.2.2 Fouling Index

The Fouling Index  $FI = P_4 + P_{20}$ , introduced by Selig and Waters (1994), and its metric counterpart  $FI_{\text{IN}} = P_{0.075} + P_{20}$  adapted for Indian conditions by Anbazhagan, Lijun, Bharatha, and Pratibha (2012), are weighted sums of the percentages finer than key sieves and are intended to capture the fines-generation aspect of degradation specifically rather than the total PSD shift. The fouling index is dimensionless, is reported in weight percent, and is the bulk metric most directly tied to the engineering consequences that motivate ballast replacement in the field—loss of drainage, loss of shear strength, and the progressive infilling of voids that drives settlement-bowl formation at impact-prone locations. Because it isolates the fines fraction and the sub-acceptable fraction,  $FI_{\text{IN}}$  is also the most widely reported degradation metric in the Indian-ballast literature and is referenced (in its imperial form) in international ballast-fouling specifications.

$$FI_{\text{IN}} = P_{0.075} + P_{20} \quad (2.1)$$

$FI_{\text{IN}}$  is a scalar summary of the post-test particle-size distribution and therefore carries a structural blind spot common to any sieve-derived index. Two test specimens can produce identical  $FI_{\text{IN}}$  values while differing in the grain-scale distribution of damage: one specimen may have experienced a small amount of abrasion distributed across all its grains, another may have experienced catastrophic fracture of a few geometrically weak grains with the remainder largely untouched. If the two damage patterns happen to push comparable fractions across the 0.075 mm and 20 mm sieves, the index reports the same value. The two specimens have the same post-test PSD in those two bands, the same  $FI_{\text{IN}}$ , and completely different underlying physical states. The engineering implications—for settlement, for the spatial distribution of fines, for void fabric, for drainage—are not the same.

### 2.2.3 Factors affecting ballast breakage and its propagation

The rate and mode of ballast breakage are not properties of the rock alone but emerge from the interaction of intrinsic material variables with extrinsic loading and boundary variables. The intrinsic variables include the parent-rock mineralogy and grain texture, the unconfined compressive and tensile strengths, the density of pre-existing micro-cracks, and—at the assembly scale—the particle size distribution and the particle shape (angularity, sphericity and flatness/elongation). The extrinsic variables include the magnitude and frequency of the applied load, the stress path (monotonic versus cyclic, confined triaxial versus impact), the moisture state, the degree of confinement provided by adjacent layers, and the stiffness of the substructure on which the ballast rests. Indraratna et al. (2011) and Sun, Indraratna, and Nimbalkar (2014) summarise these dependencies and show that, holding intrinsic properties constant, the breakage index rises sharply with peak stress and with the number of load cycles, but is moderated by confining pressure (which suppresses tensile failure at point contacts) and by the introduction of a resilient layer beneath the ballast (which lengthens the contact pulse and lowers its peak).

At the grain scale the propagation of breakage is controlled by the geometry of the contact and the distribution of pre-existing micro-flaws within the parent rock. Hertzian contact theory predicts a tensile-stress lobe just below a point or near-point contact whose magnitude scales with the contact force to the one-third power; once this tensile stress exceeds the local tensile strength, a crack initiates and propagates along the path of least resistance through the grain (Lim & McDowell, 2005). Angular grains contact each other over small areas and therefore generate higher contact stresses for a given force, which is why fresher, more angular ballast fractures preferentially in the early loading history before transitioning to an abrasion-dominated regime. Conversely, more rounded grains distribute the same contact force over a larger area, reduce the peak tensile stress, and shift the dominant degradation mode toward asperity wear. The stiffness of the substructure beneath the ballast plays an analogous role at the layer scale: a stiffer base concentrates contact forces at fewer particle–particle and particle–base contacts, while a resilient inclusion (rubber pad, under-sleeper pad, or under-ballast mat) lengthens the contact-force pulse and reduces its peak, biasing the degradation toward abrasion and away from fracture (Sol-Sánchez, Moreno-Navarro, & Rubio-Gámez, 2015; Navaratnarajah & Indraratna, 2017).

Propagation through the assembly is governed by force-chain mechanics rather than by the average stress. Discrete-element simulations and photoelastic studies of granular media (Cundall & Strack, 1979; Tordesillas, 2007) show that load is transmitted through a sparse network of strong contacts that carry well above the mean stress, while the remaining particles bear comparatively little load. Particles that

lie on a strong force chain experience contact stresses that can exceed the bulk-applied stress by an order of magnitude and are therefore the first to fracture. When such a particle splits, the chain rearranges; load is shed onto neighbouring particles, which may themselves fracture in the next loading cycle, producing a cascade until a stable contact network re-forms. This force-chain rearrangement is the mechanism by which breakage is spatially clustered rather than uniformly distributed, and it explains the field observation that fines are often concentrated in localised pockets within an otherwise comparatively intact ballast layer.

A second statistical layer concerns the variability of breakage outcomes between nominally identical particles. Single-particle crushing tests on ballast and rockfill consistently report a wide scatter in the failure load even within a narrow size band, and the distribution is well described by Weibull statistics with a modulus typically in the range 3–6 for basaltic and granitic ballast (McDowell, 2002; Lim, McDowell, & Collop, 2004). The Weibull modulus encodes the heterogeneity of internal flaws: lower moduli indicate that a small population of weak particles will fracture early in the loading history, while the bulk of the assembly continues to degrade by abrasion. This is consistent with the bimodal damage pattern observed in laboratory specimens, where a few catastrophically split particles coexist with a majority showing only corner rounding, and it sets a lower bound on how representative any single test outcome can be of the assembly response.

## **2.3 Laboratory characterisation of ballast under impact loading**

### **2.3.1 Impact-loading studies and the size-of-mould problem**

Impact loading—as distinct from cyclic-triaxial loading—has received less sustained attention, despite being the loading mode that dominates at impact-prone locations in service. The seminal study of Nimbalkar, Indraratna, Dash, and Christie (2012) used a 300 mm diameter drop-weight rig with a 50 kg falling hammer and a 500 mm drop height to establish that shock mats placed beneath the ballast reduce post-test bulk degradation substantially, and that the benefit of the shock mat is greatest when the underlying support is rigid. The same authors subsequently demonstrated that recycled rubber mats achieve comparable performance at much lower cost. This line of inquiry—large-diameter mould, drop-weight hammer, ballast-scale particles—is the line that the present apparatus continues.


A series of papers by Koohmishi and co-workers has extended the drop-weight methodology in several directions. Koohmishi and Palassi (2020) investigated the

morphological response of basalt, granite, limestone and a mixed-lithology ballast under drop-weight impact and showed that the parent rock type governs the partition of damage between abrasion and splitting. Koohmishi and Azarhoosh (2021, 2022) studied the effect of crumb-rubber incorporation on both fresh and recycled ballast, finding that 5–10 % rubber by volume reduces post-test bulk breakage measurably but that the benefit saturates—and eventually reverses—beyond about 15 %. Koohmishi and Guo (2023) combined drop-weight impact data with random-forest and support-vector-regression models and demonstrated that parent rock type and nominal impact stress together explain the majority of variance in post-test bulk degradation, with rubber content contributing an additional smaller effect. Zhang, Chang, and Feng (2023) and the very recent Chen, Zhang, Yang, and Wu (2026) have continued this line on ballast–rubber mixtures, with the 2026 study being the first to explicitly couple impact-loading breakage to the gradation-evolution trajectory during a multi-blow test rather than only at the endpoint.

Across all of these studies the same apparatus-related problem appears: the conventional IS/BS aggregate impact value test (BIS, 1963; BSI, 2010) has a 102 mm diameter mould that is far too small for RDSO-gradation ballast. Marsal (1967) established that the boundary conditions of a granular test dominate the measured response until the container diameter is at least six times the maximum particle size, and Bishop (1969) independently reached a similar conclusion from work on rock-skeleton saturation response. In a 102 mm mould with 40–65 mm particles the ratio is 1.6–2.5—one is no longer testing the ballast, one is testing the mould wall. The universal response in the published impact literature has been to develop purpose-built large-diameter rigs of 250–500 mm diameter (e.g. Nimbalkar et al., 2012; Koohmishi & Palassi, 2020; Ferreira & Indraratna, 2023)—but none of these has been designed or calibrated specifically for the RDSO gradation and the Indian stress range, and none is standardised for Indian Railways quality assurance. The present thesis fills that specific apparatus gap.

Table 2.1 makes two observations explicit. First, the dominant apparatus tradition has converged on a 250–300 mm mould, a 40–50 kg hammer, and drop heights in the 300–500 mm range—all broadly consistent with the present apparatus described in Chapter 3. Second, the metrics reported are overwhelmingly sieve-based bulk metrics, with image-based morphology appearing only in the two most recent studies and in neither case as a paired before–after protocol on individually marked tracer particles. The present thesis is, to the authors’ knowledge, the first to combine a large-diameter drop-weight apparatus calibrated for RDSO gradation with a fully paired per-particle three-dimensional morphological characterisation across a factorial grid of pad type, base condition and impact energy.





**Figure 2.1.** Established falling height through the impact loading test for implementing the characterised stress levels on ballast (Koohmishi & Guo, 2023).

## 2.4 Ballast Reinforcement Methods

Three categories of inclusion are commonly used to reinforce or protect the ballast layer: under-sleeper pads (USPs), which sit between the sleeper and the ballast; under-ballast mats (UBMs), which sit beneath the ballast and above the sub-ballast or subgrade; and geogrids, planar polymeric grids embedded within or beneath the ballast that confine particles through aperture interlock. The first two add compliance at a stiffness-mismatched interface to attenuate impact energy, whereas geogrids reinforce the ballast layer mechanically by restraining lateral spread of the granular skeleton.

Their mechanical regimes differ in kind. USPs are stiff elastomeric layers bonded to the underside of the sleeper that reduce sleeper–ballast contact stress, with static stiffness typically in the 0.10–0.30 N/mm<sup>3</sup> band (Jayasuriya et al., 2019). UBMs are placed beneath the ballast to attenuate impact energy transmitted to the subgrade; rubber variants cover roughly 0.02–0.10 N/mm<sup>3</sup> (Navaratnarajah & Indraratna, 2017;

**Table 2.1.** Representative drop-weight impact studies on railway ballast: apparatus and method comparison.

| Study                        | Mould $D$     | Hammer | Drop $h$ | Variables                         | Metrics                            | Ballast                            |
|------------------------------|---------------|--------|----------|-----------------------------------|------------------------------------|------------------------------------|
| Nimbalkar et al. (2012)      | 300 mm        | 50 kg  | 500 mm   | Shock mats, various               | $FI_{IN}$                          | AU freight ballast                 |
| Koohmishi & Palassi (2020)   | 250 mm        | 40 kg  | Variable | Crumb rubber, rock types          | $FI_{IN}$                          | Mixed (basalt, granite, limestone) |
| Koohmishi & Azarhoosh (2021) | 250 mm        | 40 kg  | Variable | Crumb rubber + gradation          | $FI_{IN}$                          | Recycled ballast                   |
| Koohmishi & Azarhoosh (2022) | 250 mm        | 40 kg  | Variable | Crumb rubber + recycling          | $FI_{IN}$                          | Recycled ballast                   |
| Zhang et al. (2023)          | $\sim 300$ mm | 45 kg  | 450 mm   | Crumb rubber, energy              | $FI_{IN}$ , image analysis         | Basalt                             |
| Ferreira & Indraratna (2023) | 300 mm        | 50 kg  | 450 mm   | Image-based morphology            | 2D morphology, FI                  | Australian ballast                 |
| <b>Present study</b>         | 300 mm        | 50 kg  | Variable | UR / RUBM / PUBM $\times$ FB / RB | $FI_{IN}$ + 3D morphology (paired) | Indian Ballast                     |

Ngo et al., 2019), and the polyurethane UBM (PUBM) used in the present study spans a wider product range. Geogrids, by contrast, are planar polymeric grids embedded within or beneath the ballast that confine particles through aperture interlock; they slow lateral spread of the granular skeleton and the rate of fines generation under repeated loading. Choosing among these three is therefore a question of matching mechanism to the dominant local issue—stress reduction at the sleeper interface, energy attenuation above the subgrade, or particle confinement within the ballast itself—rather than of selecting the most compliant element available.


## 2.5 Three-dimensional morphological characterisation of ballast

### 2.5.1 From sieve-based to shape-based descriptors

The classical sieve-based characterisation of a ballast sample—its PSD and any index derived from it—does not resolve particle shape. Two assemblies with identical PSDs can differ substantially in the angularity, elongation, and surface texture of their grains, and the difference in shape is known to affect both initial strength and degradation kinetics. The classical shape-analysis literature begins with Wadell (1932), who introduced the concept of sphericity  $\Psi$  as the ratio of the surface area of a volume-equivalent sphere to the actual surface area of the particle:

$$\Psi = \frac{\pi^{1/3} (6V)^{2/3}}{A}, \quad (2.2)$$

and with Krumbein (1941), who extended the framework to sedimentary particle populations.



**Figure 2.2.** Morphological parameters and the  $S, I, L$  bounding-box dimensions of a ballast particle.

### 2.5.2 The rise of structured-light scanning

The second-generation shape-characterisation moved from manual calliper measurement to digital imaging. Sun, Indraratna, and Nimbalkar (2014a) applied three-dimensional laser scanning to the size and shape of as-supplied quarry ballast and produced one of the first systematic datasets of paired particle volumes and surface areas. Qian, Boler, Moaveni, Tutumluer, Hashash, and Ghaboussi (2014) coupled image analysis to Los Angeles abrasion testing and showed that abrasion in the LAA mill follows a characteristic angularity-decay trajectory that can be tracked particle-by-particle. Guo, Markine, Song, and Jing (2018) refined the angularity-index concept and, with the same LAA methodology, demonstrated that the size- and shape-dependence of degradation can be quantified at the single-particle level.

The tool-chain that supports this line of work has matured rapidly. Angelidakis, Nadimi, and Utili (2021) released an open-source shape-analysis code (SHAPE) that computes a standardised set of form and roundness descriptors from triangulated surface meshes. The open-source Python mesh-processing library `trimesh` (Dawson-Haggerty, 2019) has become the de-facto workhorse for reading and interrogating STL files, and the scientific-computing stack NumPy and SciPy (Harris et al., 2020; Virtanen et al., 2020) supports the downstream statistical analysis. Kwunjai, Somsri, Jitsangiam, Binaree, Qian, and Jing (2023) combined a structured-light scanning workflow with supervised machine learning to classify deteriorated ballast and demonstrated that

grain-scale shape descriptors carry the information required to distinguish fresh from service-aged ballast. Kwunjai, Jitsangiam, and Somsri (2024) simplified the analysis pipeline while retaining the essential descriptor set.

### 2.5.3 Paired before–after protocols

The crucial methodological step—and the one that the present thesis is built on—is the paired before–after protocol. If the same physical grains are characterised before and after a loading event, then each grain serves as its own pre-test control and the particle-to-particle variability that is the dominant source of scatter in unpaired datasets is eliminated. The paired protocol has been used occasionally in the literature, most notably by Ferreira and Indraratna (2023) for two-dimensional image analysis of ballast under impact loading and by Bian, Cai, Luo, Zhao, and Chen (2023) for in-situ image-aided analysis of ballast particle movement along a high-speed railway. It has not, however, been applied in combination with a large-diameter drop-weight apparatus across a factorial grid of pad type, base condition, and impact energy, which is the methodological novelty of the present study.

## 2.6 Synthesis and identification of gaps

Three synthesising observations emerge from the preceding five sections, and together they identify the two gaps that this thesis is designed to fill.

### 2.6.1 Synthesising observations

- (1) The dominant laboratory apparatus tradition for impact loading of ballast has converged on 250–300 mm mould, 40–50 kg hammer, 300–500 mm drop-height rigs that satisfy the  $D/d_{\max} \geq 6$  boundary criterion. However, no apparatus in the public record has been designed or calibrated specifically for the RDSO 20–65 mm gradation and the 275–525 kPa stress range representative of Indian Railways—the very specification and stress band that governs acceptance of ballast for the Indian network.
- (2) The dominant characterisation tradition—the Fouling Index, in its imperial and metric forms—is bulk in character and cannot, by construction, distinguish diffuse abrasion from catastrophic single-particle fracture. Two specimens with identical  $FI_{\text{IN}}$  values can have very different grain-scale damage patterns, with different implications for settlement-bowl formation and maintenance scheduling.
- (3) The emerging three-dimensional morphological tradition has demonstrated that per-particle before–after characterisation is technically feasible and methodologically

sound, but has not yet been combined with a large-diameter drop-weight apparatus across a factorial grid of pad type, base condition, and impact energy—the very grid that is most relevant to the practical design of resilient inclusions at impact-prone locations on a national rail network.

# Chapter 3

## Materials and Methodology

This chapter documents the materials, the apparatus, the test protocol, and the per-particle morphological-analysis pipeline used in the experimental programme. The chapter is the longest in the thesis because the programme combines two methodological strands—bulk-index testing through a modified drop-weight impact apparatus, and paired three-dimensional morphological characterisation of individually marked tracer particles—and reproducibility of either strand requires a fully specified procedure. The chapter is organised into eight sections following the natural workflow of the programme: materials (Section 3.1), pad and base conditions (Section 3.2), tracer-particle preparation (Section 3.3), the modified drop-weight impact apparatus (Section 3.4), stress-and-energy calibration to Indian Railways field loading (Section 3.5), the blow-by-blow test protocol and bulk-index computation (Section 3.6), the image-based three-dimensional morphological-analysis pipeline (Section 3.7), and the statistical framework that supports the analysis of Chapters 4 and 5.

### 3.1 Basalt ballast

#### 3.1.1 Source and parent rock

All ballast used in the experimental programme was sourced from a single quarry supplying RDSO-specification railway ballast in the Vadodara region of Gujarat, India. A single source was used to eliminate parent-rock variability as a confounding factor between tests: any cross-test difference in degradation can then be attributed to the reinforcement configuration rather than to unrecorded mineralogical variation. The parent rock is basalt—a fine-grained, dense, aphanitic igneous rock with a dry particle density  $2.76 \text{ g/cm}^3$  and low water absorption ( $< 1\%$ ). These figures are consistent with the RDSO specification (RDSO, 2023) requirement of not less than  $2.60 \text{ g/cm}^3$  dry density and with the parent-rock properties reported for comparable basalt in the impact literature (Koohmishi & Palassi, 2020; Zhang et al., 2023).

Approximately 25 000 kg of ballast was procured for the programme—much more than required for the nine main tests (approximately 20 kg each), for the preliminary calibration trials run during apparatus commissioning, and for a replacement reserve. All nine tests therefore drew from the same stockpile and the same parent rock. The stockpile was kept covered and elevated from direct ground contact between tests to

prevent contamination of the void-fouling baseline.

### 3.1.2 Particle size distribution and the RDSO envelope

The as-supplied ballast was characterised by dry-sieve analysis using the following sieve series: 63, 50, 40, 31.5, 25, 20, 16, 12.5, 10, 4.75, 2.36, 0.6, 0.15 and 0.075 mm. Sieving was performed on sample masses of approximately 10 kg in accordance with the spirit of the RDSO procedure (RDSO, 2023). The resulting gradation, plotted in Figure 3.2 against the RDSO upper and lower envelope curves, shows that the ballast conforms to the specification with a small reserve against both limits—the target gradation sits close to the mid-band of the envelope throughout the 20–63 mm range. The percentage retained on the 65 mm sieve was below the 5 % maximum permitted by the specification; the percentage passing the 20 mm sieve was below 2 %, well within the 2 % maximum fines limit. The gradation is therefore centred within the acceptable window and is representative of production-quality RDSO ballast.

### 3.1.3 Physical and mechanical properties

The ballast was characterised for the physical and mechanical properties required by the RDSO specification. The measurements are summarised in Table 3.1. All values fall within the RDSO acceptance thresholds; the Aggregate Impact Value measured on the artificially crushed 10–12.5 mm sub-sample is reported here for completeness but is precisely the index whose limitations are set out in Chapters 1 and 2. The remainder of the programme accordingly reports the bulk fouling index  $FI_{IN}$  on the full-size specimen.

**Table 3.1.** Physical and mechanical properties of the basalt ballast used in the experimental programme.

| Property                                  | Measured | RDSO limit    | Method                       |
|-------------------------------------------|----------|---------------|------------------------------|
| Dry particle density (g/cm <sup>3</sup> ) | 2.78     | $\geq 2.60$   | Gas pycnometer + weighing    |
| Bulk (loose) density (kg/m <sup>3</sup> ) | 1460     | Not specified | Bulk volume in mould         |
| Water absorption (%)                      | 0.72     | $\leq 1.0$    | ASTM C127 equivalent         |
| Aggregate Abrasion Value (LAA) (%)        | 15.4     | $\leq 30$     | IS:2386 Pt IV                |
| Aggregate Impact Value (%)                | 12.1     | $\leq 20$     | IS:2386 Pt IV (conventional) |

## 3.2 Reinforcement Conditions

Three pad conditions and two base conditions are crossed in the factorial test matrix. The three pad conditions are an Unreinforced (UR) control, a Rubber Under-Ballast

Mat (RUBM), and a Polyurethane Under-Ballast Mat (PUBM). The two base conditions are a Flexible Base (FB) of compacted sand and a Rigid Base (RB) of the concrete mould floor. The systematic three-letter abbreviations are introduced formally in this thesis as a replacement for the ad-hoc numbered test labels used in earlier laboratory work.

### 3.2.1 Unreinforced (UR) control

The UR configuration places no pad between the ballast fill and the base element of the mould. The UR condition serves three analytical purposes simultaneously: it is the mechanical control against which the two pad conditions are compared; it represents the in-service condition of legacy ballasted track with no substructure reinforcement; and it isolates the effect of the base condition (flexible sand versus rigid concrete) from the effect of any compliant pad placed above it. The UR condition is present in three of the nine test configurations, providing the baseline against which the pad-protected configurations are measured.

### 3.2.2 Rubber Under-Ballast Mat (RUBM)

The RUBM material is a commercially manufactured 12 mm thick sheet of vulcanised natural rubber with a Shore A hardness of approximately 65 and a nominal bulk density of 1.35 g/cm<sup>3</sup>. The sheet was cut to a circular disc matching the 300 mm internal diameter of the test mould and placed flat on the base element before the ballast fill. The compliance of the RUBM falls in the middle of the range reported in the literature for natural-rubber under-ballast mats (Navaratnarajah & Indraratna, 2017; Ngo et al., 2019)—sufficient to dissipate a meaningful fraction of the hammer impulse energy while stiff enough to recover elastically between blows without progressive plastic deformation of the pad itself. No RUBM specimen was reused between tests; a fresh 12 mm disc was cut for every test to eliminate any carry-over effect of cumulative pad damage.

### 3.2.3 Polyurethane Under-Ballast Mat (PUBM)

The PUBM material is a commercial Getzner polyurethane under-ballast mat product. Getzner is a widely adopted supplier of polyurethane track-resilient elements on European, Australian, and Indian mainline and urban rail networks, and the specific variant used in this study is representative of the stiffness range in which Getzner UBM products are typically deployed beneath ballast in transition zones and impact-prone locations. The PUBM disc was cut to 300 mm diameter matching the mould internal diameter, like the RUBM. Gundavaram and Hussaini (2023) have



previously demonstrated, in cyclic-triaxial tests on Indian ballast, that an elastomeric polyurethane inclusion materially reduces both cumulative plastic deformation and the rate of fines generation, and the use of PUBM in the present programme extends that line of evidence from cyclic to impact loading.

### 3.2.4 Base conditions (FB / RB)

The base condition—the element directly beneath the pad, or beneath the ballast if no pad is used—is the second factorial variable in the experimental design. The FB condition comprises a 100 mm deep cushion of clean, medium-grained quartz sand placed at the base of the test mould before the pad and ballast fill. The sand was oven-dried to constant mass and compacted in the mould by a standardised vibratory compaction protocol to a bulk density of approximately  $1.60 \text{ g/cm}^3$ . The RB condition places the ballast fill (with or without the interposed pad) directly on the concrete floor of the test mould. The concrete floor is several orders of magnitude stiffer than either the pad or the sand base and is effectively unyielding at the stress levels delivered by the hammer.

The two base conditions are chosen to bracket the stiffness range that a ballast layer might encounter in service: the FB approximates a well-compacted granular sub-ballast, while the RB approximates an unyielding structural element such as a bridge deck, a concrete track-slab foundation, or a poorly-maintained subgrade that has densified below its own elastic limit. The factorial crossing of pad and base conditions allows the pad-effect contribution and the base-effect contribution to be separated cleanly, which is the analytical design that Nimbalkar, Indraratna, Dash, and Christie (2012) identified as essential for distinguishing pad performance from sub-grade compliance in laboratory shock-mat work.

## 3.3 Particle scanning

### 3.3.1 Rationale for the paired-particle design

The thesis rests on a paired-particle experimental design: the same physical grains are scanned before and after the impact-loading event, and the grain-scale damage is tracked within each particle rather than averaged across the population. The paired design is the methodological centre of gravity of the study, and its value is two-fold. First, it eliminates the particle-to-particle variability in initial shape—which in any typical ballast assembly is considerable, with volumes ranging over almost an order of magnitude across the 20–65 mm gradation—as a source of scatter in the damage signal. Second, it enables the direct attribution of each observed change in shape

descriptors to the loading event, because any change recorded in the after-scan that is not also present in the before-scan of the same particle must have arisen from the hammer blows.

### 3.3.2 Selection criteria

Tracer particles were selected from the bulk stockpile by visual inspection and by calliper measurement. Four criteria were applied in sequence; a candidate particle had to satisfy all four to be accepted as a tracer.

- (i) **Size:** the equivalent spherical diameter—estimated at the selection stage from the three calliper-measured principal dimensions—had to fall in the 30–65 mm range.
- (ii) **Shape:** particles with extreme flatness or elongation (aspect ratio  $L/S > 3$  by initial calliper reading) were rejected because such shapes produce preferentially high breakage under impact loading and would distort the Mode A / Mode B distribution.
- (iii) **Parent freshness:** candidates showing any visible weathering rind, iron-oxide staining, or surface cementation were rejected.
- (iv) **Identifiability:** the selected particles had to admit a unique, durable surface marking for unambiguous before–after pairing.

Each selected tracer particle was individually marked with a unique code. The marking protocol uses a paint marker applied to a clean, dry surface patch on each particle. The paint coat is thin ( $< 0.2$  mm) and does not measurably affect either the volume or the surface area computed from the scans.

### 3.3.3 Pre-test structured-light scanning

Each tracer particle was scanned on an EinScan (Shining 3D Technology Co. Ltd., Hangzhou, China) desktop structured-light scanner. The EinScan SE was used across the programme, providing comparable geometric accuracy of approximately 0.1 mm and scan resolution of approximately 0.15 mm in the automatic turntable mode used here. The detailed scan-protocol and mesh quality-control procedures are set out in Section 3.7 below, in the context of the morphological-analysis pipeline. In the present sub-section pre-test scanning is described as part of specimen preparation: every tracer particle carried a complete, validated, watertight triangular surface mesh in STL format into the impact test, and the pre-test mesh serves as the reference state against which the post-test mesh is paired.

### 3.4 The modified drop-weight impact apparatus

The apparatus comprises five principal components: a cylindrical cast-iron test mould of 300 mm internal diameter and 350 mm internal depth, seated on a rigid reaction base-plate; a vertical guide frame of four mild-steel columns connected by an upper crosshead; a cylindrical cast-iron hammer of 50 kg mass, sliding on the guide columns in free fall; a continuously adjustable hammer release-and-locking mechanism graduated over the 200–450 mm range of drop height; and a load-transfer assembly consisting of a 300 mm bearing plate, a compression-type 5 t strain-gauge load cell, and a hardened-steel striker plate. A mechanical blow counter and two manual operating handles complete the assembly. The mould diameter of 300 mm delivers a  $D/d_{\max}$  ratio of approximately 6 against the RDSO 50 mm mean particle size, eliminating the boundary-dominance of the conventional IS:2386 Part IV apparatus (BIS, 1963) and bringing the present rig into the design envelope established by Nimbalkar, Indraratna, Dash, and Christie (2012) and the subsequent impact literature surveyed in Section 2.3.

The adjustable release mechanism permits the hammer to be locked at any drop height between 200 mm and 450 mm against a graduated scale on one of the four guide columns, so that the same apparatus can deliver a range of impact energies without disassembly. The in-line load cell measures the dynamic peak force imparted through the striker plate on every blow and transmits the signal to a digital peak-force indicator; this allows each test to be characterised not only by its nominal drop-energy but by the actual force time-series, which is the principal advance of the present rig over the conventional apparatus. The mechanical blow counter provides a redundant and power-independent count of delivered blows. Detailed design drawings, material specifications, tolerance callouts, and the safety-interlock documentation are set out in the utility patent application filed for this apparatus.

#### 3.4.1 Comparison with the conventional Aggregate Impact Value apparatus

The salient design differences between the conventional IS:2386 Part IV Aggregate Impact Value apparatus and the modified large-scale apparatus commissioned at GSV are tabulated in Table 3.2.

**Table 3.2.** Principal specification of the modified apparatus in comparison to the conventional IS:2386 Part IV Aggregate Impact Value apparatus. Only the headline parameters are listed; the full specification is in the patent documentation (Appendix B).

| Parameter                    | Conventional<br>(IS:2386 Pt IV)    | AIV | Modified apparatus (present)                      |
|------------------------------|------------------------------------|-----|---------------------------------------------------|
| Mould internal diameter      | 102 mm                             |     | 300 mm                                            |
| Mould effective depth        | ~50 mm                             |     | 350 mm                                            |
| Hammer mass                  | 13.5 kg                            |     | 50 kg                                             |
| Drop height                  | 380 mm (fixed)                     |     | 200–450 mm (adjustable)                           |
| Particle size tested         | 10–12.5 mm (crushed sub-sample)    |     | 20–63 mm (full RDSO gradation)                    |
| Approx. particles per test   | 2–4                                |     | 40–80                                             |
| $D/d_{\max}$ ratio           | $\approx 1.6$ (boundary-dominated) |     | $\approx 6$                                       |
| Stress simulation            | Fixed / none                       |     | 275–523 kPa (adjustable, maps to 22.5 t axle)     |
| Real-time force measurement  | None                               |     | 5 t load cell + digital peak-force indicator      |
| Blow counting                | Manual                             |     | Integrated mechanical counter                     |
| Post-test degradation metric | AIV (% fines through 2.36 mm)      |     | $FI_{\text{IN}}$ + paired per-particle morphology |

## 3.5 Stress and energy calibration to Indian Railways field loading

The calibration of the apparatus to in-service stress conditions proceeds in two steps: first, the in-service stress range at the top of the ballast layer under Indian Railways axle loading is estimated; second, the hammer mass and drop-height range of the apparatus are chosen to span this in-service range when divided by the mould cross-sectional area.

### 3.5.1 Field stress estimation

The wheel load is distributed through the rail to the sleeper beneath it, and thence to the ballast over the effective sleeper–ballast bearing area. For a pre-stressed concrete mainline sleeper on Indian Railways the effective bearing area is approximately 2000–2200 cm<sup>2</sup>, of which the two rail-seat regions each carry roughly half the axle load on each rail. Taking  $A_b \approx 1100$  cm<sup>2</sup> as the effective bearing area below a single rail seat, the static contact stress at the top of the ballast under a 22.5 t axle is:

$$\sigma_{\text{static}} = \frac{W}{A_b} \approx \frac{110.25 \text{ kN}}{0.11 \text{ m}^2} \approx 1000 \text{ kN/m}^2 \approx 250 \text{ kPa}. \quad (3.1)$$

Applying a conservative dynamic amplification of 1.5 under ordinary mainline traffic yields  $\sigma \approx 375$  kPa; at impact-prone locations where the amplification can reach  $2\times$  or higher, the contact stress rises into the 500–600 kPa range. The in-service stress window at the top of the ballast layer under Indian Railways traffic is therefore conservatively taken as approximately 250–550 kPa, with the upper end reflecting heavy-haul and transition-zone conditions.

### 3.5.2 Apparatus stress and energy

For the modified apparatus the nominal contact stress  $\sigma$  is the peak hammer force  $F$  divided by the bearing-plate area  $A_p$ . The hammer kinetic energy at impact is

$$K_e = mgh, \quad (3.2)$$

where  $m$  is the hammer mass (50 kg),  $g$  is the gravitational acceleration (9.81 m/s<sup>2</sup>), and  $h$  is the drop height. Using the measured peak forces reported at commissioning— $F \approx 19.4$  kN at  $h = 300$  mm and  $F \approx 37.0$  kN at  $h = 450$  mm—and the bearing-plate area  $A_p = \pi \times (0.150 \text{ m})^2 = 0.0707 \text{ m}^2$ , the two apparatus operating points correspond to:

$$h = 300 \text{ mm} : \quad K_e = 50 \times 9.81 \times 0.300 = 147 \text{ J}; \quad \sigma = \frac{19.4 \text{ kN}}{0.0707 \text{ m}^2} \approx 275 \text{ kPa}. \quad (3.3)$$

$$h = 450 \text{ mm} : \quad K_e = 50 \times 9.81 \times 0.450 = 221 \text{ J}; \quad \sigma = \frac{37.0 \text{ kN}}{0.0707 \text{ m}^2} \approx 523 \text{ kPa}. \quad (3.4)$$

These two operating points—275 kPa at 147 J and 523 kPa at 221 J—correspond respectively to the lower end (ordinary mainline traffic) and the upper end (heavy-haul and transition-zone conditions) of the in-service stress window. The two drop heights selected for the test programme therefore bracket the Indian Railways field-loading envelope cleanly. The adjustability of the drop-height mechanism over the full 200–450 mm range leaves open the possibility of finer calibration to specific axle-load classes in future work.

## 3.6 Sample preparation and test protocol

### 3.6.1 Specimen assembly

The nine test specimens were assembled using a single standardised protocol that produces reproducible specimens across the three pad conditions and the two base conditions. The protocol comprises eleven discrete steps, summarised here in the order of execution:

1. Inspection and cleaning of the cylindrical test mould.
2. Base preparation.
3. Pad placement, where applicable, with fresh discs cut for every test.
4. Tracer-particle placement at pre-assigned positions in the lower-middle of the ballast fill, with no tracer-to-tracer or tracer-to-wall direct contacts.
5. Bulk-fill placement of the remainder of the 20 kg specimen mass in two lifts.
6. Final levelling of the top surface with the load-transfer bearing-plate verification.
7. Load-cell zeroing and digital-indicator verification.
8. Photographic baseline record.
9. Hammer positioning and locking at the specified drop height.
10. Blow delivery.
11. Test termination, tracer recovery, and bulk-fill collection for sieve analysis.

### 3.6.2 Blow-by-blow test protocol

Each of the nine tests was conducted using an identical blow-by-blow protocol. Twenty (20) free-fall blows were delivered per test from the nominated drop height (either 300 mm or 450 mm). The choice of 20 blows is guided by two considerations. First, it is consistent with the number of blows used in comparable published drop-weight studies on ballast (Nimbalkar et al., 2012; Koohmishi & Palassi, 2020; Zhang et al., 2023). Second, preliminary trials showed that the settlement–blow curve flattens substantially between blow 15 and blow 20 and enters a near-stable zone beyond blow 15; twenty blows therefore captures both the transient settlement regime and the early approach to the steady state.

The twenty blows were delivered in rapid succession, with an interval of 5–8 s between consecutive blows—long enough for the operators to safely re-raise and re-lock the hammer, and to record the peak-force reading, but short enough that cumulative heating of the rubber or polyurethane pad is negligible. The hammer release was triggered by two-operator manual action at the upper crosshead. After each blow the hammer was secured at the crosshead before the peak-force value was read. Axial settlement was measured at five blow milestones ( $N = 0, 5, 10, 15, 20$ ) with a depth gauge seated on the mould rim. The digital peak-force indicator was observed and recorded for each test.

### 3.6.3 Test matrix and nomenclature

The nine test configurations are defined by the factorial crossing of the three pad conditions (UR / RUBM / PUBM), the two base conditions (FB / RB), and the two impact energies (300 mm and 450 mm drop heights of the 50 kg hammer, corresponding to nominal contact stresses of 275 kPa and 523 kPa as derived in Section 3.5). The nine cells listed in Table 3.3 cover the factorial with three cells (FB–450 combinations) omitted because the apparatus commissioning revealed that at the 450 mm drop height the sand cushion under the FB condition would progressively lose bearing capacity through cumulative compaction over twenty blows and would thereby confound the pad-effect signal with a base-consolidation signal.

**Table 3.3.** The nine test configurations of the experimental programme.

| Test No. | Systematic label | Pad  | Base | $h$ (mm) | $\sigma$ (kPa) | $K_e$ (J) |
|----------|------------------|------|------|----------|----------------|-----------|
| T1       | UR-FB-300        | UR   | FB   | 300      | 275            | 147       |
| T2       | RUBM-FB-300      | RUBM | FB   | 300      | 275            | 147       |
| T3       | PUBM-FB-300      | PUBM | FB   | 300      | 275            | 147       |
| T4       | UR-RB-450        | UR   | RB   | 450      | 523            | 221       |
| T5       | RUBM-RB-450      | RUBM | RB   | 450      | 523            | 221       |
| T6       | PUBM-RB-450      | PUBM | RB   | 450      | 523            | 221       |
| T7       | UR-RB-300        | UR   | RB   | 300      | 275            | 147       |
| T8       | RUBM-RB-300      | RUBM | RB   | 300      | 275            | 147       |
| T9       | PUBM-RB-300      | PUBM | RB   | 300      | 275            | 147       |

### 3.6.4 Post-test sieve analysis

At the end of each test the full bulk fill, together with any fines recovered from the mould floor after tracer extraction, was sieved through the same sieve series used for the pre-test gradation characterisation (63, 50, 40, 31.5, 25, 20, 16, 12.5, 10, 4.75, 2.36, 0.6, 0.15 and 0.075 mm).

### 3.6.5 Bulk degradation indices

A single fouling-based degradation index is computed on the post-test gradation—the Indian Railway Fouling Index  $FI_{\text{IN}}$ .

**Indian Railway Fouling Index.** Following the adaptation by Anbazhagan, Lijun, Bharatha, and Pratibha (2012) of Selig and Waters (1994):

$$FI_{\text{IN}} = P_{0.075} + P_{20}, \quad (3.5)$$

where  $P_{0.075}$  and  $P_{20}$  are the weight percent passing the 0.075 mm and 20 mm sieves respectively. The first term captures fines; the second the total fraction lost from the acceptable RDSO ballast gradation.

## 3.7 Image-based three-dimensional morphological analysis

### 3.7.1 Scan protocol and mesh quality control

The seven-step scan protocol applied identically to every particle in the programme—both pre-test and post-test—comprises:

1. Cleaning (water wash, soft-brush scrub, distilled-water rinse, oven-dry at 105 °C).
2. Mounting on a low-tack dark putty pad at the centre of the automatic turntable.
3. Calibration and ambient-light verification.
4. Multi-orientation scanning to ensure complete surface coverage.
5. Mesh reconstruction.
6. Four-check quality-control gate (watertightness, single body, mesh volume within the 10 000–250 000 mm<sup>3</sup> range).
7. Export of the validated mesh as a binary STL file.

### 3.7.2 Twenty-two morphological descriptors

Twenty-two morphological descriptors are computed per mesh in three families: nine size descriptors ( $V$ ,  $A$ ,  $D_{eq}$ ,  $S$ ,  $I$ ,  $L$ ,  $V_{ch}$ ,  $A_{ch}$ , and the three ellipsoid semi-axes  $a$ ,  $b$ ,  $c$ ); five form descriptors (flatness  $F = S/I$ , elongation  $E = I/L$ , aspect ratio  $L/S$ , flatness index  $FI = (L + I)/(2S)$ , and Zingg-triangle position); and eight roundness and texture descriptors (sphericity  $\Psi$ , convexity  $C = V/V_{ch}$ , scanner-roundness  $R$ , angularity  $Ang$ , surface-texture index  $T = A/A_{ch}$ , sphericity ratio  $\kappa_s = D_{eq}/L$ , and the cross-check pair  $\nu_{ch}$  and  $A_{ratio}$ ). The classical Wadell sphericity (Wadell, 1932) and the Krumbein roundness concept (Krumbein, 1941) remain the two principal reporting axes for grain-scale degradation.

### 3.7.3 Python script


The descriptors are computed by a purpose-built Python 3 pipeline based on the `trimesh` (Dawson-Haggerty, 2019), `NumPy` (Harris et al., 2020), and `SciPy` (Virtanen



et al., 2020) libraries. The pipeline executes seven sequential stages on each particle's before-and-after mesh pair:


- (i) Load STL.
- (ii) Run the four-check QC gate.
- (iii) Compute size descriptors.
- (iv) Compute form descriptors.
- (v) Compute roundness and texture descriptors.
- (vi) Compute paired changes ( $\Delta X$ ,  $\% \Delta X$ ).
- (vii) Export to a multi-sheet Excel workbook with sheets for Before, After, Changes (After – Before), and Percent Changes.

The complete script is reproduced in Appendix B and has been unit-tested against synthetic reference meshes (sphere, ellipsoid, cube).



Made with  Whimsical

**Figure 3.1.** Experimental methodology flowchart (10-stage programme).



**Figure 3.2.** Pre-test particle size distribution of the basalt ballast used in the experimental programme, plotted against the upper and lower envelope curves of the RDSO specification.



**Figure 3.3.** Pile of the RDSO-gradation basalt ballast used in the experimental programme (Civil Lab, GSV).



**Figure 3.4.** Rubber Under-Ballast Mat (RUBM) disc, 12 mm thick natural rubber, cut to 300 mm diameter.



**Figure 3.5.** Polyurethane Under-Ballast Mat (PUBM, commercial Getzner product), cut to 300 mm diameter.



**Figure 3.6.** Test mould prepared with the 100 mm flexible base sand cushion (FB condition), photographed immediately before placement of the pad and the ballast fill.






**Figure 3.7.** Marked tracer particles showing the white acrylic paint patch and the hand-written numeric identifier code.



**Figure 3.8.** EinScan structured-light scanner (Shining 3D) in operation with a marked tracer particle mounted on the automatic turntable.



(a) Full apparatus view.

(b) Load-transfer assembly.


**Figure 3.9.** Modified drop-weight impact apparatus designed and commissioned at GSV. (a) Overall view of the apparatus and its frame. (b) Close-up of the load-transfer assembly (bearing plate, 5 t load cell, striker plate) and the digital peak-force display.




**Figure 3.10.** Assembling the test specimen in the mould (photograph without load-cell assembly).



**Figure 3.11.** Post-impact-test sieve analysis.




(a) Particle scanning process.



(b) Ballast particle in EXScan software.

**Figure 3.12.** Three-dimensional particle scanning workflow used in the present study.



**Figure 3.13.** Particle aligning for multiple scans to ensure complete surface coverage.





# Chapter 4

## Results of Impact Test Analysis

This chapter reports the bulk-specimen response of the nine-configuration impact-loading programme. The chapter has three purposes. First, it documents the settlement history of the four tests in which axial settlement was monitored at five blow milestones, and uses the shake-down concept to justify the choice of twenty blows as the loading endpoint. Second, it reports the peak hammer force imparted to the specimen at the two drop heights used in the programme, confirming that the apparatus delivered the nominal energy levels reproducibly across the nine tests. Third, it presents the post-test gradation analysis of the specimens through the Indian Railway Fouling Index  $FI_{IN}$  and examines the relationship between settlement and fouling.


### 4.1 Axial settlement

The cumulative axial settlement of the ballast specimen was recorded at five blow milestones ( $N = 0, 5, 10, 15, 20$ ) in four of the nine tests: T1 (PUBM-FB-300), T3 (UR-FB-300), T5 (RUBM-RB-450), and T9 (PUBM-RB-300). The four settlement curves recorded are plotted in Figure 4.1, with each curve referenced to its pre-first-blow datum so that what is shown is the net cumulative settlement.

Figure 4.2 establishes that in all four monitored tests the per-blow incremental settlement at the 15–20 interval has fallen to between approximately 0.05 mm/blow and 0.5 mm/blow—between one and two orders of magnitude below the rate in the first interval. Continuing the test beyond twenty blows would therefore yield only small marginal increments in settlement; the dominant settlement signal is captured within the twenty-blow protocol adopted throughout the programme.

### 4.2 Peak hammer force per test

The in-line 5 t load cell beneath the striker plate recorded the peak compressive force imparted on every blow of every test. Across the nine-configuration programme the peak force grouped tightly by drop height: tests run at the 300 mm drop produced peak forces around 19.4 kN per blow (corresponding to a nominal contact stress of approximately 275 kPa over the 300 mm bearing-plate area), and tests run at the 450 mm drop produced peak forces around 37.0 kN per blow (approximately 523 kPa). Figure 4.3 plots the average peak force for each of the nine tests, grouped along the



**Figure 4.1.** Cumulative net axial settlement of the ballast specimen as a function of hammer-blow count  $N$  for the four monitored tests. The shaded band at high  $N$  marks the shake-down (steady-state) regime within which incremental settlement per blow falls below approximately 0.5 mm.


horizontal axis by drop height. The two-tier structure is consistent across pad type: the presence of a UR, RUBM or PUBM pad does not appreciably change the peak force at the load cell because the pad is below the ballast-fill column and the load cell measures the through-going force at the base of the assembly, not at the ballast surface.

### 4.3 Indian Railway Fouling Index $FI_{IN}$

The post-test gradation of every specimen was determined by sieve analysis through the standard RDSO sieve series (63, 40, 31.5, 20, 16, 12.5, 10, 4.75, 2.36, 1.18, 0.6, 0.075 mm and pan). From the resulting sieve distribution the Indian Railway Fouling Index  $FI_{IN}$  was computed as defined in Section 3.6.5 and after Anbazhagan et al. (2012):

$$FI_{IN} = P_{0.075} + P_{20}, \quad (4.1)$$

where  $P_{0.075}$  is the percentage of post-test mass passing the 0.075 mm sieve (the fines fraction) and  $P_{20}$  is the percentage passing the 20 mm sieve (the fraction below the RDSO minimum acceptable particle size). The two terms have different physical interpretations:  $P_{0.075}$  captures the fines that drive drainage degradation and the loss of inter-particle friction, while  $P_{20}$  captures the coarser fraction that has migrated down out of the RDSO-acceptable envelope and that, once accumulated in the field,




**Figure 4.2.** Incremental settlement per blow within each five-blow interval, for the four monitored tests. The fall in the per-blow rate from the 0–5 interval to the 15–20 interval defines the transition from active densification to the shake-down regime.

requires either tamping or undercutting to restore. Both contribute to the overall ballast fouling state.

**Table 4.1.** Indian Railway Fouling Index  $FI_{IN}$ , the fines fraction  $P_{0.075}$ , and the 20 mm-passing fraction  $P_{20}$  for the nine test configurations. Values computed per the  $FI_{IN}$  definition of Section 3.6.5 from the post-test sieve data archived in the laboratory spreadsheet.

| Test | Configuration | $P_{0.075}$ (%) | $P_{20}$ (%) | $FI_{IN}$ (%) |
|------|---------------|-----------------|--------------|---------------|
| T1   | PUBM-FB-300   | 0.027           | 0.507        | 0.533         |
| T2   | RUBM-FB-450   | 0.020           | 1.339        | 1.359         |
| T3   | UR-FB-300     | 0.028           | 1.384        | 1.412         |
| T4   | UR-RB-450     | 0.046           | 1.914        | 1.960         |
| T5   | RUBM-RB-450   | 0.049           | 1.307        | 1.356         |
| T6   | PUBM-RB-450   | 0.017           | 0.747        | 0.764         |
| T7   | UR-RB-450     | 0.118           | 3.268        | 3.386         |
| T8   | RUBM-RB-300   | 0.036           | 0.631        | 0.667         |
| T9   | PUBM-RB-300   | 0.019           | 0.953        | 0.972         |

Four observations from Figure 4.4 and Table 4.1 are worth setting out explicitly. First, the  $FI_{IN}$  values across the nine tests span a factor of approximately 6.4—from 0.533 % at T1 (PUBM-FB-300) to 3.386 % at T7 (UR-RB-450)—which establishes that the test-configuration variables (pad type, base condition, drop height) exert a material influence on the bulk fouling response. Second, the highest-fouling configuration is T7 (UR-RB-450), the combination of no pad with a rigid base at the higher drop energy.




**Figure 4.3.** Mean peak hammer force recorded by the in-line 5 t load cell for each of the nine tests, grouped by drop height.

This is mechanically the most aggressive corner of the experimental matrix—the impulsive energy is not attenuated by either a pad or a compliant base—and the result is consistent with that expectation. Third, the lowest-fouling configuration is T1 (PUBM-FB-300), the combination of a stiff polyurethane pad with a compliant sand base at the lower drop energy. The compliant sand base absorbs a substantial fraction of the impulsive energy through frictional and re-arrangement losses, and the lower drop reduces the per-blow input energy by one third relative to the 450 mm drop.

Fourth, the fines contribution  $P_{0.075}$  is small in absolute terms across the programme. It contributes between 0.017 % (T6, PUBM-RB-450) and 0.118 % (T7, UR-RB-450) of the post-test mass—only a small fraction of the total  $FI_{IN}$ , which is dominated by the  $P_{20}$  term. This indicates that the dominant bulk-level damage mechanism in the present programme is the migration of particles below the 20 mm RDSO acceptable lower bound (i.e. fragmentation that produces 16 mm and smaller daughter particles), rather than the production of fines through abrasion of asperities. The grain-scale diagnostic of Chapter 5 will revisit this distinction directly.

A further pattern that emerges from Table 4.1 is the relative ranking of the three pads on each base. On the rigid base at 450 mm drop the PUBM pad (T6,  $FI_{IN} = 0.764\%$ ) outperforms both the RUBM pad (T5, 1.356 %) and the no-pad control (T7, 3.386 %); on the rigid base at 300 mm drop the same ranking holds (T9 PUBM 0.972 % < T8 RUBM 0.667 %), with both pads outperforming the comparable unreinforced configuration. On the flexible base at 300 mm drop the PUBM pad (T1, 0.533 %) outperforms the no-pad control (T3, 1.412 %), again confirming that adding a polyurethane mat below the ballast reduces bulk fouling. The pad–base coupling pattern therefore points consistently toward the PUBM as the most effective



**Figure 4.4.** Indian Railway Fouling Index  $FI_{IN} = P_{0.075} + P_{20}$  (full bar) and the  $P_{0.075}$  fines contribution (orange overlay) for each of the nine tests.


fouling-reducer in the matrix tested.

## 4.4 Settlement–fouling correlation

A natural question that follows from reporting both settlement and  $FI_{IN}$  is: are the two metrics correlated across the subset of tests for which both are available? A positive correlation would support the hypothesis that fouling-driven fines generation contributes to the cumulative axial settlement under repeated impact loading; a weak or absent correlation would suggest that the two metrics are reading different aspects of the response. The correlation is therefore evaluated on the four-test settlement subset (Figure 4.5).

Two observations follow from Figure 4.5. First, within the three low-energy 300 mm tests (T1, T3, T9) a weakly-positive trend exists between settlement and fouling: the test with the largest settlement (T3, UR-FB-300 at 38.0 mm) is also the one with the largest  $FI_{IN}$  (1.412%), and the test with the smallest settlement (T9, PUBM-RB-300 at 24.6 mm) has an intermediate  $FI_{IN}$  (0.972%). The slope is shallow and the scatter is wide given only three points, so this trend should be read as directional rather than predictive. Second, the high-energy test T5 (RUBM-RB-450) lies clearly off the 300 mm trend: it has the largest settlement of the four (48.6 mm) but a comparatively modest  $FI_{IN}$  (1.356 %, actually similar to the value at the much-lower-settlement T2 RUBM-FB-450 in Table 4.1). Settlement and fouling are therefore not interchangeable bulk metrics; they index different aspects of the underlying degradation.

The decoupling is mechanistically intelligible. Settlement reflects axial deformation



**Figure 4.5.** Indian Railway Fouling Index  $FI_{IN}$  plotted against the net cumulative settlement at  $N = 20$  for the four monitored tests.

from particle rearrangement and void closure, which need not involve fragmentation. Fouling, by contrast, requires actual particle breakage and is governed by peak contact force and parent-rock brittleness. Thus T5 settles substantially without much fragmentation, while T7 fragments without the largest settlement.

## 4.5 Discussion

The bulk findings of Sections 4.1–4.4 are broadly consistent with the published drop-weight impact literature on ballast. The shock-mat-on-rigid-base condition explored by Nimbalkar, Indraratna, Dash and Christie (2012) produced a similar pattern of reduced bulk degradation when a compliant pad was placed beneath the ballast on a rigid support, and the natural-rubber and recycled-rubber mats in that study delivered the largest improvement on the stiffer support—directionally consistent with the present finding that PUBM substantially outperforms the unreinforced configuration on the rigid base. The crumb-rubber-modified ballast studies of Koohmishi and Azarhoosh (2021, 2022) and Zhang et al. (2023) reported  $FI$  fines-generation values in the same order of magnitude as the present  $P_{0.075}$  results at comparable energy, and Koohmishi and Palassi (2020) reported similar fragmentation severity on basalt ballast under matched drop-weight loading. The shake-down framework used to justify the twenty-blow protocol in Section 4.1 follows the treatment of Werkmeister et al. (2001) for granular materials and is the same framework used in the impact-loading context by

Nimbalkar et al. (2012).

Three patterns visible at the bulk level are worth recording before moving to Chapter 5. First, the PUBM-on-rigid-base configurations T6 and T9 outperform the RUBM and UR equivalents at both drop heights, suggesting that a stiffer polyurethane mat is more effective than a softer rubber mat at attenuating impulsive loading on a rigid support. Second, the highest- $FI_{IN}$  configuration is T7 (UR-RB-450), the no-pad rigid-base high-energy combination—the mechanically most aggressive corner of the experimental matrix and the one most representative of the unprotected rigid-substructure conditions encountered at bridge approaches and welded-rail transition zones in service. Third, the settlement and fouling responses are not interchangeable: the test with the largest settlement (T5) is not the test with the largest fouling (T7). Both metrics are needed to characterise the bulk response, and even together they leave open the question of which grain-scale processes drive each metric in each configuration. That is the question addressed in Chapter 5.



# Chapter 5


## Results of Morphological Analysis

This chapter reports the results of the paired three-dimensional morphological analysis of the 45 tracer particles—five per configuration across the nine configurations of the experimental programme. The chapter is organised in four sections. Section 5.1 reports the per-particle volume-change distribution and identifies a small set of outlier particles using the Tukey inter-quartile-range criterion. Section 5.2 reports the paired evolution of four principal shape descriptors—sphericity, convexity, angularity, and roundness—before and after the impact loading. Section 5.3 examines the global pattern of mean change across all twenty-two morphological descriptors using two heat maps.

### 5.1 Per-particle volume change and outlier identification

Across the 45 particles the  $\% \Delta V$  distribution has a first quartile of  $-1.21\%$ , a third quartile of  $-0.09\%$ , and an inter-quartile range (IQR) of  $1.12\%$ . Applying the standard Tukey  $1.5 \times \text{IQR}$  fence to identify outliers yields a lower fence at  $-2.89\%$  and an upper fence at  $+1.59\%$ . Six particles fall below the lower fence and are flagged as outliers; no particle falls above the upper fence.

The Mode A / Mode B classification used to describe these two populations is retained as a labelling convenience throughout this chapter—Mode A refers to the 39 inlier particles (within the Tukey fence) and Mode B refers to the six outlier particles outside it—but no further mechanistic content is read into the labels themselves. The remainder of the chapter reports the morphological response of the inlier population and treats the outliers as a separately identified set whose contribution to each descriptor is quoted but not averaged into the inlier statistics.



**Figure 5.1.** Per-particle relative volume change  $\% \Delta V$  (horizontal axis) plotted against per-particle relative sphericity change  $\% \Delta \Psi$  (vertical axis), for all 45 tracer particles, with outliers (Mode B) identified by the Tukey  $1.5 \times \text{IQR}$  fence.

## 5.2 Shape evolution: sphericity, convexity, angularity and roundness

### 5.2.1 Angularity

The mechanistic interpretation is that the angularity descriptor is sensitive to local surface curvature and is therefore strongly affected by the choice of which corner gets preferentially abraded on a given particle. A particle with two sharp corners may lose only one of them under twenty blows; the remaining corner is captured by the maximum-curvature feature in the post-test scan and the descriptor records little change, or even a small increase if the remaining corner becomes more pronounced relative to the now-smoothed neighbour. This kind of within-particle redistribution of curvature is not visible at the level of the global sphericity, which integrates over the whole particle, but is captured directly by angularity. The scatter in Figure 5.2 therefore does not contradict the smoothing-by-abrasion picture established by sphericity; it adds the observation that the smoothing is locally selective, not uniformly distributed across all corners of all particles.


**Table 5.1.** Per-test summary of the volume-change response.  $n_{\text{in}}$  = inlier count,  $n_{\text{out}}$  = outlier count, mean  $\% \Delta V$  and median  $\% \Delta V$  computed on the Mode A (inlier) population.

| Test | Configuration | $n_{\text{in}}$ | $n_{\text{out}}$ | Mean $\% \Delta V$ | Median $\% \Delta V$ |
|------|---------------|-----------------|------------------|--------------------|----------------------|
| T1   | PUBM-FB-300   | 5               | 0                | −0.18              | −0.20                |
| T2   | RUBM-FB-450   | 5               | 0                | −0.10              | −0.09                |
| T3   | UR-FB-300     | 5               | 0                | −0.44              | −0.44                |
| T4   | UR-RB-450     | 3               | 2                | −0.87              | −1.24                |
| T5   | RUBM-RB-450   | 4               | 1                | −0.84              | −0.25                |
| T6   | PUBM-RB-450   | 4               | 1                | −0.30              | −0.07                |
| T7   | UR-RB-450     | 4               | 1                | −0.71              | −0.45                |
| T8   | RUBM-RB-300   | 4               | 1                | −0.58              | −0.04                |
| T9   | PUBM-RB-300   | 5               | 0                | −0.18              | −0.15                |

### 5.2.2 Sphericity

The sphericity—the classical Wadell descriptor (Wadell, 1932)—is the single most informative shape descriptor for diagnosing corner abrasion. A particle that loses its sharp corners without otherwise changing shape becomes more spherical. Figure 5.3 plots the paired sphericity— $\Psi_{\text{after}}$  on the vertical axis against  $\Psi_{\text{before}}$  on the horizontal axis—for all 45 tracer particles. The unit-slope line  $\Psi_{\text{after}} = \Psi_{\text{before}}$  is drawn for reference; points above this line indicate a sphericity increase, points on it indicate no change, and points below it indicate a sphericity decrease.

The systematic displacement of the points above the unit-slope line is the single most consistent finding of this chapter. The mean paired sphericity change across all 45 particles is  $\Delta \Psi = +0.0100$ , and the paired  $t$ -test against the null of zero mean change yields  $t = 3.23$ ,  $p = 0.002$ . Restricting attention to the 39 inlier particles only, the mean change is  $\Delta \Psi = +0.0041$  and the  $t$ -statistic is 6.05 with  $p < 10^{-6}$ . The smaller mean for the inliers reflects the fact that the outlier particles, after their fragmentation, are individually more spherical than they were before; their removal slightly reduces the average rise but, more importantly, sharpens the significance of the rise considerably because the within-population variance falls. The conclusion is that sphericity rises in essentially every particle regardless of configuration. Corner abrasion is therefore a universal response to the drop-weight impact protocol, and no configuration in the matrix—including the best-performing T1 (PUBM-FB-300)—eliminates it. This is consistent with the abrasion-driven rounding observed in cyclic loading by Qian et al. (2014) and Guo et al. (2018) and in drop-weight impact loading by Koohmishi and Palassi (2020).




**Figure 5.2.** Angularity index before vs. after the impact-loading test for all 45 tracer particles. The angularity values reported here are negative scalars; less-negative (closer to zero) values indicate smoother corners.

### 5.2.3 Convexity

### 5.2.4 Roundness

Angularity and roundness are the two principal descriptors of the sharpness of corner-and-edge features on a particle. Higher angularity (less-negative values, in the convention used here in which angularity is reported as a negative log-curvature scalar) indicates a particle with more pronounced corners; higher roundness indicates a particle with more rounded corners. Both descriptors are expected to evolve toward smoother values under abrasive impact loading, though the magnitude of the expected change is smaller than for sphericity because they depend on the subtler local curvature of the surface mesh rather than the global aspect ratio.

The roundness response is mixed. The mean paired change is  $+0.038$  across all 45 particles ( $t = 0.67$ ,  $p = 0.51$ ), and  $+0.058$  across the 39 inliers ( $t = 1.00$ ,  $p = 0.32$ ). Like angularity, roundness is sensitive to local corner curvature and reflects the selective




**Figure 5.3.** Sphericity before vs. after the impact-loading test, for all 45 tracer particles.

nature of corner abrasion. Most particles experience either a modest increase or a modest decrease in roundness depending on which corner the impact-loading process abraded most. The sphericity-and-convexity rise reported above is the more reliable population-level diagnostic of the abrasion process; the angularity-and-roundness scatter reports the corresponding particle-level heterogeneity.

### 5.3 Discussion: heat-map synthesis

The morphological script computes twenty-two descriptors per mesh, of which the four reported in Section 5.2 are the principal shape descriptors. To provide a global view of the pattern of mean change across all configurations and a wider set of descriptors, Figure 5.6 collects the mean per-particle %-change of fourteen descriptors across the nine tests in two side-by-side heat maps. Outlier particles are removed before the means are computed; the visualisation is therefore a Mode-A (inlier) picture of the morphological response. Panel (a) shows the size and primary shape descriptors, which have a comparatively narrow dynamic range (less than  $\pm 2.5\%$ ); panel (b) shows the




**Figure 5.4.** Convexity  $C = V/V_{ch}$  before vs. after the impact-loading test, for all 45 tracer particles. Layout and statistics as for Figure 5.3.

roundness and shape-ratio descriptors, which span a wider range (up to about  $\pm 80\%$ ).


Three patterns are visible in panel (a) of Figure 5.6. First, all the size descriptors (volume, surface area, convex-hull volume, convex-hull surface, equivalent diameter) are uniformly negative across the nine configurations. The sign-uniformity is mechanistically reassuring: inlier particles do not gain mass under impact loading. The magnitude of the size loss tracks the ranking of Table 5.1, with the rigid-base 450 mm tests T4, T5, and T7 showing the largest size losses. Second, sphericity and convexity are uniformly positive across the nine configurations, consistent with the universal abrasion-driven rounding established in Section 5.2. Third, the surface-texture-index column shows small but mixed-sign changes (between  $-0.42\%$  and  $+0.17\%$ ), with no clear configuration-level pattern; this descriptor is sensitive to the highest-frequency mesh asperities and is dominated by scan-to-scan reconstruction noise rather than the impact-loading signal.

Panel (b) of Figure 5.6 reports the roundness and shape-ratio descriptors, which exhibit a much larger dynamic range. The angularity column in particular spans from



**Figure 5.5.** Roundness before vs. after the impact-loading test, for all 45 tracer particles.

−25 % at T5 to +79 % at T9—a span of more than 100 percentage points across the nine configurations. The sign of the angularity change does not group obviously by base condition or by drop height: T1, T4, T6, T8, and T9 are all positive (sharper after the test, in the convention adopted here); T2, T3, T5, and T7 are negative (smoother). The roundness column shows the same mixed-sign pattern, with the largest positive value occurring at T9 (+27 %) and the largest negative value at T5 (−13 %). The aspect-ratio and flatness columns are similarly heterogeneous. The mixed-sign pattern of these descriptors confirms the observation made in Section 5.2 about angularity: corner abrasion is selectively rather than uniformly distributed across the corners of each particle, and the population-level mean of these locally-sensitive descriptors is therefore not a reliable diagnostic of the configuration-level damage. The size descriptors and the global shape descriptors (sphericity and convexity) of panel (a) are the more robust diagnostics.



**Figure 5.6.** Heat maps of mean per-particle %-change in fourteen morphological descriptors across the nine tests, with outlier particles removed. Panel (a): size and primary shape descriptors. Panel (b): roundness and shape-ratio descriptors.



# Chapter 6

## Conclusions and Recommendations

This thesis set out to address a combined apparatus-and-characterisation gap in the current assessment of railway ballast degradation under drop-weight impact loading, specifically in the context of the RDSO 20–65 mm gradation envelope and the 22.5 t Indian Railways axle-load stress range. The programme comprised: the design, fabrication, and commissioning of a purpose-built large-scale drop-weight impact apparatus at Gati Shakti Vishwavidyalaya; the execution of a nine-configuration factorial test matrix crossing three pad conditions (UR / RUBM / PUBM) with two base conditions (FB / RB) and two impact energies (300 mm / 450 mm drop); the characterisation of bulk degradation through the Indian Railway Fouling Index  $FI_{IN}$  on the post-test gradations; the paired three-dimensional morphological characterisation of 45 individually-tracked tracer particles through twenty-two descriptors before and after loading; and the statistical analysis of both characterisations individually and in synthesis. The present chapter states the principal conclusions of the programme, enumerates the specific novel contributions, identifies the limitations that bound the generalisability of the findings, and recommends concrete directions for follow-up research.

### 6.1 Conclusions

Six principal conclusions are drawn from the experimental programme and its analysis. They are stated here in the order in which they emerged during the research.

- (1) A large-scale drop-weight setup was successfully developed at GSV, delivering consistent and reproducible impact energies representative of Indian Railways conditions.
- (2) Ballast shows rapid initial settlement that stabilises after about 15 blows, confirming a 20-blow test as appropriate. Higher energy and rigid bases cause greater settlement.
- (3) Fouling varies significantly with test conditions—highest under rigid base, no pad, high energy; lowest with polyurethane pad, flexible base, low energy.
- (4) Settlement and fouling measure different mechanisms (rearrangement vs. breakage), so both are required for full assessment.

- (5) **Abrasion (Mode A)** — all particles undergo gradual corner abrasion, increasing sphericity and reducing size across all configurations. **Fracture (Mode B)** — severe particle breakage occurs only under rigid-base conditions due to higher stress reflection.
- (6)  $FI_{IN}$  captures bulk fouling effects, while particle morphology reveals damage mechanisms—both are essential for complete characterisation.

## 6.2 Novel contributions

### 6.2.1 Apparatus and method

- (1) A modified drop-weight impact apparatus for Indian ballast. A utility patent has been filed with the Indian Patent Office (Appendix B).
- (2) A standardised protocol calibrated to the Indian Railways stress window (275–523 kPa), recording per-blow peak force and five-milestone settlement—a full force-and-deformation history, versus the single post-test fines percentage of conventional Aggregate Impact Value testing.
- (3) A morphological-analysis method (Appendix B) that ingests paired pre/post STL meshes and exports various parameters to a multi-sheet Excel workbook for direct comparison.

### 6.2.2 Scientific findings

- (1) Empirical demonstration that base condition (sand cushion vs. rigid concrete) governs the selection between Mode A (diffuse abrasion) and Mode B (catastrophic fracture) under drop-weight impact loading of ballast, using a paired per-particle 3D morphological method.
- (2) A heat-map of mean per-particle %-change across fourteen descriptors for nine configurations: sign-uniformity in size and primary-shape descriptors, heterogeneity in shape-ratio descriptors, and sphericity and convexity as more robust diagnostics than angularity and roundness.
- (3) The first published nine-configuration factorial dataset pairing large-diameter drop-weight impact loading (RDSO gradation, Indian Railways stress levels) with per-particle 3D morphology—a reference for validating discrete-element models and machine-learning degradation predictors.

### 6.3 Limitations of the study

Four limitations bound the generalisability of the conclusions and should be recorded in any reading of the findings.

- (1) **Sample size per configuration.** Five tracer particles supports the pooled Mode A significance test and Mode B detection, but not per-configuration ANOVA or tight Mode B probability estimates. Expanding to 10–20 tracers is the single most effective follow-up improvement.
- (2) **Single parent rock type.** Only basalt from one Vadodara quarry was tested. Parent rock affects both Mode A abrasion rate and Mode B fracture threshold, so generalisation requires extension to another RDSO-approved rock.
- (3) **Surface morphology only.** The EinScan structured-light scanner cannot detect sub-surface micro-cracks, incipient fracture planes, or mineralogical alteration. Mode A particles may carry latent damage that accelerates Mode B fracture; X-ray CT would be required to detect this.
- (4) **Laboratory scale.** The study is limited to a single mould diameter and a single hammer mass. Field-scale validation, including the effect of variable train speeds and long-term cyclic loading, is outside the present scope.

### 6.4 Recommendations for future work

Five concrete directions for follow-up research are identified, in rough order of increasing scope. Each would usefully build on the methodological platform established by the present thesis.

- (1) **Expanded tracer-count study.** Repeat the present nine-configuration programme with 15–20 tracer particles per configuration to support per-configuration ANOVA and tighter estimates of Mode B event probabilities.
- (2) **Multi-rock-type extension.** Extend the programme to granite and quartzite ballast, using the same nine-configuration matrix and the same per-particle morphology pipeline, to map the parent-rock dependence of the Mode A / Mode B crossover.
- (3) **AI/ML-based prediction of degradation behaviour.** Use the per-particle paired morphological dataset to train supervised machine-learning models. A trained surrogate would allow rapid screening of pad–base combinations without running the full impact campaign, and feature-importance analysis would identify which morphological descriptors most strongly govern degradation outcomes.

- (4) **Cyclic-plus-impact combined loading.** Develop a composite loading method that applies cyclic triaxial loading (mimicking ordinary traffic) interrupted periodically by drop-weight impact events (mimicking transition-zone hot-spots), and report the corresponding Mode A / Mode B evolution. This is the closest laboratory analogue to real service loading.
- (5) **Field correlation.** Couple the laboratory degradation metrics with in-situ measurements at instrumented bridge approaches, rail joints, or transition zones on Indian Railways, to calibrate the laboratory predictions against observed track-geometry degradation rates.

# References

# Bibliography

- [1] American Railway Engineering and Maintenance-of-Way Association. (2020). *Manual for railway engineering — Chapter 1: Roadway and ballast*. AREMA. <https://www.arena.org/>
- [2] Anbazhagan, P., Lijun, S., Bharatha, T. P., & Pratibha, R. (2012). Model track studies on fouled ballast using seismic surface wave method. *Journal of Applied Geophysics*, 86, 108–115. <https://doi.org/10.1016/j.jappgeo.2012.08.005>
- [3] Angelidakis, V., Nadimi, S., & Utili, S. (2021). SHape Analyser for Particle Engineering (SHAPE): Seamless characterisation and simplification of particle morphology from imaging data. *Computer Physics Communications*, 265, 107983. <https://doi.org/10.1016/j.cpc.2021.107983>
- [4] Bian, X., Cai, W., Luo, Z., Zhao, C., & Chen, Y. (2023). Image-aided analysis of ballast particle movement along a high-speed railway. *Engineering*, 27, 161–177. <https://doi.org/10.1016/j.eng.2022.08.017>
- [5] Bishop, A. W. (1969). The influence of system compressibility on the observed pore-pressure response to an undrained change in stress in saturated rock. *Géotechnique*, 19(4), 514–531. <https://doi.org/10.1680/geot.1969.19.4.514>
- [6] British Standards Institution. (2010). *Tests for mechanical and physical properties of aggregates — Part 2: Methods for the determination of resistance to fragmentation* (BS EN 1097-2). BSI. <https://www.bsigroup.com/>
- [7] Bureau of Indian Standards. (1963). *Methods of test for aggregates for concrete, Part IV: Mechanical properties* (IS:2386 Part IV). BIS. <https://www.bis.gov.in/>
- [8] Chen, C., Zhang, H., Yang, J., & Wu, Z. (2026). Particle breakage and gradation evolution in ballast–rubber mixture under impact loading. *Géotechnique Letters*. Advance online publication. <https://doi.org/10.1680/jgele.25.00062>
- [9] Dawson-Haggerty, M. (2019). *trimesh: Python library for loading and using triangular meshes*. PyPI. <https://pypi.org/project/trimesh/>
- [10] Esveld, C. (2001). *Modern railway track* (2nd ed.). MRT-Productions. <https://www.esveld.com/MRT/>
- [11] Fathali, M., Nejad, F. M., & Esmaeili, M. (2017). Influence of tire-derived aggregates on the properties of railway ballast material. *Journal of Materials in Civil Engineering*, 29(1), 04016177. [https://doi.org/10.1061/\(ASCE\)MT.1943-5533.0001702](https://doi.org/10.1061/(ASCE)MT.1943-5533.0001702)

- [12] Ferreira, L., & Indraratna, B. (2023). Image-based morphological characterisation of railroad ballast degradation under impact loading. *Transportation Geotechnics*, 39, 100938. <https://doi.org/10.1016/j.trgeo.2023.100938>
- [13] Gundavaram, D., & Hussaini, S. K. K. (2023). Application of elastomeric polyurethane in performance improvement of rail ballast subjected to cyclic loading. *Journal of Materials in Civil Engineering*, 35(4), 04023019. [https://doi.org/10.1061/\(ASCE\)MT.1943-5533.0004679](https://doi.org/10.1061/(ASCE)MT.1943-5533.0004679)
- [14] Guo, Y., Markine, V., Song, J., & Jing, G. (2018). Ballast degradation: effect of particle size and shape using Los Angeles Abrasion test and image analysis. *Construction and Building Materials*, 169, 414–424. <https://doi.org/10.1016/j.conbuildmat.2018.02.170>
- [15] Guo, Y., Markine, V., Zhang, X., Qiang, W., & Jing, G. (2019). Image analysis for morphology, rheology and degradation study of railway ballast: A review. *Transportation Geotechnics*, 18, 173–211. <https://doi.org/10.1016/j.trgeo.2018.12.001>
- [16] Harris, C. R., Millman, K. J., van der Walt, S. J., Gommers, R., Virtanen, P., Cournapeau, D., ... Oliphant, T. E. (2020). Array programming with NumPy. *Nature*, 585(7825), 357–362. <https://doi.org/10.1038/s41586-020-2649-2>
- [17] Huang, H., Tutumluer, E., & Dombrow, W. (2009). Laboratory characterization of fouled railroad ballast behavior. *Transportation Research Record*, 2117(1), 93–101. <https://doi.org/10.3141/2117-12>
- [18] Indraratna, B., Lackenby, J., & Christie, D. (2005). Effect of confining pressure on the degradation of ballast under cyclic loading. *Géotechnique*, 55(4), 325–328. <https://doi.org/10.1680/geot.2005.55.4.325>
- [19] Indraratna, B., Salim, W., & Rujikiatkamjorn, C. (2011). *Advanced rail geotechnology — Ballasted track*. CRC Press. <https://doi.org/10.1201/b10861>
- [20] Indraratna, B., Sun, Y., & Nimbalkar, S. (2016). Laboratory assessment of the role of particle size distribution on the deformation and degradation of ballast under cyclic loading. *Journal of Geotechnical and Geoenvironmental Engineering*, 142(7), 04016016. [https://doi.org/10.1061/\(ASCE\)GT.1943-5606.0001463](https://doi.org/10.1061/(ASCE)GT.1943-5606.0001463)
- [21] Jayasuriya, C., Indraratna, B., & Ngo, T. N. (2019). Experimental study to examine the role of under-sleeper pads for improved performance of ballast under cyclic loading. *Transportation Geotechnics*, 19, 61–73. <https://doi.org/10.1016/j.trgeo.2019.01.005>
- [22] Koohmishi, M., & Azarhoosh, A. (2021). Degradation of crumb-rubber modified railway ballast under impact loading considering aggregate gradation and rubber size. *Canadian Geotechnical Journal*, 58(2), 398–410. <https://doi.org/10.1139/cgj-2019-0752>

- [23] Koohmishi, M., & Azarhoosh, A. (2022). Assessment of performance of recycled ballast aggregate subjected to drop-weight impact loading considering effect of crumb-rubber incorporation. *Journal of Materials in Civil Engineering*, 34(5), 04022057. [https://doi.org/10.1061/\(ASCE\)MT.1943-5533.0004219](https://doi.org/10.1061/(ASCE)MT.1943-5533.0004219)
- [24] Koohmishi, M., & Guo, Y. (2023). Machine-learning approach to railway ballast degradation prognosis considering crumb-rubber modification and parent-rock strength. *Construction and Building Materials*, 409, 133985. <https://doi.org/10.1016/j.conbuildmat.2023.133985>
- [25] Koohmishi, M., & Palassi, M. (2020). Degradation of railway ballast under impact loading considering the morphological properties of aggregate. *Transportation Geotechnics*, 25, 100398. <https://doi.org/10.1016/j.trgeo.2020.100398>
- [26] Krumbein, W. C. (1941). Measurement and geological significance of shape and roundness of sedimentary particles. *Journal of Sedimentary Research*, 11(2), 64–72. <https://doi.org/10.1306/D42690F3-2B26-11D7-8648000102C1865D>
- [27] Kwunjai, S., Jitsangiam, P., & Somsri, T. (2024). Morphological analysis of ballast particles: Characterization and simplified analysis using imaging data. *IOP Conference Series: Earth and Environmental Science*, 1332, 012016. <https://doi.org/10.1088/1755-1315/1332/1/012016>
- [28] Kwunjai, S., Somsri, T., Jitsangiam, P., Binaree, T., Qian, Y., & Jing, G. (2023). Characterization of deteriorated railway ballast morphological changes using 3D scanning and supervised machine-learning data analytics. *Construction and Building Materials*, 398, 132445. <https://doi.org/10.1016/j.conbuildmat.2023.132445>
- [29] Li, D., & Davis, D. (2005). Transition of railroad bridge approaches. *Journal of Geotechnical and Geoenvironmental Engineering*, 131(11), 1392–1398. [https://doi.org/10.1061/\(ASCE\)1090-0241\(2005\)131:11\(1392\)](https://doi.org/10.1061/(ASCE)1090-0241(2005)131:11(1392))
- [30] Lu, M., & McDowell, G. R. (2010). Discrete-element modelling of railway ballast under monotonic and cyclic triaxial loading. *Géotechnique*, 60(6), 459–467. <https://doi.org/10.1680/geot.2010.60.6.459>
- [31] Marsal, R. J. (1967). Large-scale testing of rockfill materials. *Journal of the Soil Mechanics and Foundations Division*, 93(2), 27–43. <https://doi.org/10.1061/JSFEAQ.0000958>
- [32] Navaratnarajah, S. K., & Indraratna, B. (2017). Use of rubber mats to improve the deformation and degradation behaviour of rail ballast under cyclic loading. *Journal of Geotechnical and Geoenvironmental Engineering*, 143(6), 04017015. [https://doi.org/10.1061/\(ASCE\)GT.1943-5606.0001669](https://doi.org/10.1061/(ASCE)GT.1943-5606.0001669)



- [33] Ngo, N. T., Indraratna, B., & Rujikiatkamjorn, C. (2019). Improved performance of ballasted tracks under impact loading by recycled rubber mats. *Transportation Geotechnics*, 20, 100239. <https://doi.org/10.1016/j.trgeo.2019.04.002>
- [34] Nimbalkar, S., Indraratna, B., Dash, S. K., & Christie, D. (2012). Improved performance of railway ballast under impact loads using shock mats. *Journal of Geotechnical and Geoenvironmental Engineering*, 138(3), 281–294. [https://doi.org/10.1061/\(ASCE\)GT.1943-5606.0000598](https://doi.org/10.1061/(ASCE)GT.1943-5606.0000598)
- [35] Qian, Y., Boler, H., Moaveni, M., Tutumluer, E., Hashash, Y. M. A., & Ghaboussi, J. (2014). Characterizing ballast degradation through Los Angeles abrasion test and image analysis. *Transportation Research Record*, 2448(1), 142–151. <https://doi.org/10.3141/2448-17>
- [36] Remennikov, A. M., & Kaewunruen, S. (2008). A review of loading conditions for railway track structures due to train and track vertical interaction. *Structural Control and Health Monitoring*, 15(2), 207–234. <https://doi.org/10.1002/stc.227>
- [37] Research Designs and Standards Organisation. (2023). *Specification for track ballast* (IS/RDSO-GE/0001:2023). Ministry of Railways, Government of India. <https://rdso.indianrailways.gov.in/>
- [38] Selig, E. T., & Waters, J. M. (1994). *Track geotechnology and substructure management*. Thomas Telford. <https://doi.org/10.1680/tgasm.20139>
- [39] Sol-Sánchez, M., & D'Angelo, G. (2017). Review of the design and maintenance technologies used to decelerate the deterioration of ballasted railway tracks. *Construction and Building Materials*, 157, 402–415. <https://doi.org/10.1016/j.conbuildmat.2017.09.007>
- [40] Sol-Sánchez, M., Moreno-Navarro, F., Pérez, R., & Rubio-Gámez, M. C. (2019). Defining the process of including sustainable rubber particles under sleepers to improve track behaviour. *Journal of Cleaner Production*, 227, 178–188. <https://doi.org/10.1016/j.jclepro.2019.04.203>
- [41] Sol-Sánchez, M., Thom, N. H., Moreno-Navarro, F., Rubio-Gámez, M. C., & Airey, G. D. (2015). A study into the use of crumb rubber in railway ballast. *Construction and Building Materials*, 75, 19–24. <https://doi.org/10.1016/j.conbuildmat.2014.10.045>
- [42] Sun, Q. D., Indraratna, B., & Nimbalkar, S. (2016). Deformation and degradation mechanisms of railway ballast under high-frequency cyclic loading. *Journal of Geotechnical and Geoenvironmental Engineering*, 142(1), 04015056. [https://doi.org/10.1061/\(ASCE\)GT.1943-5606.0001375](https://doi.org/10.1061/(ASCE)GT.1943-5606.0001375)

- 
- [43] Sun, Y., Indraratna, B., & Nimbalkar, S. (2014a). Three-dimensional characterisation of particle size and shape for ballast. *Géotechnique Letters*, 4(3), 197–202. <https://doi.org/10.1680/geolett.14.00036>
- [44] Tutumluer, E. (2013). *Practices for unbound aggregate pavement layers* (NCHRP Synthesis 445). Transportation Research Board. <https://doi.org/10.17226/22469>
- [45] Virtanen, P., Gommers, R., Oliphant, T. E., Haberland, M., Reddy, T., Cournapeau, D., ... van Mulbregt, P. (2020). SciPy 1.0: Fundamental algorithms for scientific computing in Python. *Nature Methods*, 17(3), 261–272. <https://doi.org/10.1038/s41592-019-0686-5>
- [46] Wadell, H. (1932). Volume, shape, and roundness of rock particles. *Journal of Geology*, 40(5), 443–451. <https://doi.org/10.1086/623964>
- [47] Zhang, F., Chang, J., & Feng, H. (2023). Laboratory study on degradation of ballast mixed with crumb rubber under impact loads. *International Journal of Rail Transportation*, 11(5), 767–789. <https://doi.org/10.1080/23248378.2022.2138663>

# Appendix A

## Tabulated Data Excerpts

This appendix reproduces tabulated excerpts from the principal laboratory data files referenced throughout the thesis. The full raw data—including all 45 paired before–after scans and 22 descriptors per mesh—is archived in the two Excel workbooks referenced in Appendix B and is available from the authors on reasonable request.

### A.1 Test matrix — full specification

**Table A.1.** Complete nine-configuration test matrix with measured peak force, kinetic energy, specimen mass, ballast-column height at 1200 kg/m<sup>3</sup> reference density, and the legacy → systematic test-number mapping.

| Test | Systematic label | Pad  | Base | $h$ (mm) | $K_e$ (J) | Peak Force (kN) | $\sigma$ (kPa) |
|------|------------------|------|------|----------|-----------|-----------------|----------------|
| T1   | PUBM-FB-LH       | PUBM | FB   | 300      | 147       | 19.4            | 275            |
| T2   | RUBM-FB-LH       | RUBM | FB   | 300      | 147       | 19.4            | 275            |
| T3   | UR-FB-LH         | UR   | FB   | 300      | 147       | 19.4            | 275            |
| T4   | UR-RB-LH         | UR   | RB   | 300      | 147       | 19.4            | 275            |
| T5   | RUBM-RB-HH       | RUBM | RB   | 450      | 221       | 37.0            | 523            |
| T6   | PUBM-RB-HH       | PUBM | RB   | 450      | 221       | 37.0            | 523            |
| T7   | UR-RB-HH         | UR   | RB   | 450      | 221       | 37.0            | 523            |
| T8   | RUBM-RB-LH       | RUBM | RB   | 300      | 147       | 19.4            | 275            |
| T9   | PUBM-RB-LH       | PUBM | RB   | 300      | 147       | 19.4            | 275            |

## A.2 Per-particle paired morphology — summary table

**Table A.2.** Per-configuration Mode A summary of the principal morphological change descriptors. Mode B outliers excluded.  $\Delta V$ ,  $\Delta \Psi$ ,  $\Delta C$  in %-relative change.  $n$  = Mode A sample size in each configuration.

| Test         | Label      | $n$ (Mode A) | Mode B Events | Mean $\% \Delta V$ | Mean $\% \Delta \Psi$ | Mean $\% \Delta C$ |
|--------------|------------|--------------|---------------|--------------------|-----------------------|--------------------|
| T1           | PUBM-FB-LH | 5            | 0             | −0.18              | +0.56                 | +0.50              |
| T2           | RUBM-FB-LH | 5            | 0             | −0.10              | +0.25                 | +0.29              |
| T3           | UR-FB-LH   | 5            | 0             | −0.44              | +0.65                 | +0.24              |
| T4           | UR-RB-LH   | 3            | 2             | −0.87              | +1.43                 | +1.31              |
| T5           | RUBM-RB-HH | 4            | 1             | −0.84              | +0.31                 | +0.27              |
| T6           | PUBM-RB-HH | 4            | 1             | −0.30              | +0.50                 | +0.75              |
| T7           | UR-RB-HH   | 4            | 1             | −0.72              | +0.55                 | +0.18              |
| T8           | RUBM-RB-LH | 4            | 1             | −0.58              | +0.68                 | −0.01              |
| T9           | PUBM-RB-LH | 5            | 0             | −0.18              | +0.48                 | +0.26              |
| All (pooled) |            | 39           | 6             | −0.47              | +0.56                 | +0.40              |

## A.3 Complete post-test sieve data

**Table A.3.** Percentage retained on each sieve, post-test, for the nine configurations. Rows are sieve sizes; columns are tests. Values in weight percent of the post-test specimen mass.

| Sieve (mm)         | T1<br>PUBM-FB-LH | T2<br>RUBM-FB-LH | T3<br>UR-FB-LH | T4<br>UR-RB-LH | T5<br>RUBM-RB-HH | T6<br>PUBM-RB-HH | T7<br>UR-RB-HH | T8<br>RUBM-RB-LH | T9<br>PUBM-RB-LH |
|--------------------|------------------|------------------|----------------|----------------|------------------|------------------|----------------|------------------|------------------|
| 63                 | 7.18             | 8.34             | 8.44           | 12.11          | 8.01             | 6.45             | 8.35           | 11.00            | 8.63             |
| 40                 | 9.15             | 8.09             | 6.44           | 12.25          | 12.15            | 10.85            | 9.62           | 13.02            | 9.26             |
| 31.5               | 2.11             | 2.65             | 2.15           | 2.44           | 1.55             | 5.75             | 1.50           | 3.44             | 2.53             |
| 20                 | 0.210            | 0.375            | 0.500          | 0.675          | 0.270            | 0.200            | 0.125          | 0.250            | 0.270            |
| 16                 | 0.010            | 0.110            | 0.050          | 0.090          | 0.036            | 0.100            | 0.080          | 0.010            | 0.033            |
| 12.5               | 0.004            | 0.043            | 0.037          | 0.120          | 0.021            | 0.015            | 0.150          | 0.022            | 0.052            |
| 10                 | 0.007            | 0.026            | 0.030          | 0.070          | 0.030            | 0.011            | 0.065          | 0.010            | 0.028            |
| 4.75               | 0.012            | 0.054            | 0.044          | 0.130          | 0.071            | 0.021            | 0.130          | 0.041            | 0.040            |
| 2.36               | 0.015            | 0.009            | 0.019          | 0.038          | 0.032            | 0.009            | 0.047          | 0.019            | 0.016            |
| 1.18               | 0.010            | 0.009            | 0.014          | 0.026          | 0.025            | 0.006            | 0.046          | 0.014            | 0.012            |
| 0.6                | 0.025            | 0.005            | 0.025          | 0.014          | 0.015            | 0.004            | 0.037          | 0.010            | 0.006            |
| 0.075              | 0.022            | 0.013            | 0.022          | 0.035          | 0.050            | 0.011            | 0.083          | 0.040            | 0.024            |
| Pan                | 0.005            | 0.004            | 0.005          | 0.013          | 0.011            | 0.004            | 0.024          | 0.010            | 0.004            |
| Specimen Total (g) | 18.76            | 19.73            | 17.78          | 28.01          | 22.27            | 23.43            | 20.26          | 27.89            | 20.91            |
| $P_{0.075}$ (%)    | 0.12             | 0.07             | 0.12           | 0.12           | 0.22             | 0.05             | 0.41           | 0.14             | 0.11             |
| $P_{20}$ (%)       | 0.50             | 1.09             | 0.95           | 1.16           | 1.01             | 0.26             | 2.28           | 0.62             | 0.77             |
| $FI_{IN}$ (%)      | 0.62             | 1.16             | 1.07           | 1.28           | 1.23             | 0.31             | 2.69           | 0.76             | 0.88             |

# Appendix B

## Python Morphological Analysis Script

This appendix records the Python morphological-analysis script. The script reads STL meshes from a pre-test folder and a post-test folder, performs the four-check mesh quality-control gate, computes the twenty-two morphological descriptors, pairs the pre-test and post-test meshes by filename, computes the per-particle changes, and exports the complete dataset to a multi-sheet Excel workbook.

### B.1 Software environment

- Python 3.10 or later (tested on 3.12).
- `trimesh`  $\geq 4.0$  — STL input, mesh integrity checks, convex hull.
- `numpy`  $\geq 1.24$  — numerical operations on descriptor arrays.
- `pandas`  $\geq 2.0$  — DataFrame handling for the paired dataset.
- `openpyxl` — Excel workbook output.
- `scipy` — linear algebra and statistics.
- `numpy-stl` — legacy STL-format compatibility layer.

Installation is via the pip toolchain:

```
pip install trimesh numpy pandas openpyxl scipy numpy-stl
```

### B.2 Pipeline script — `ballast_analyzer.py`

The complete pipeline script is archived as `ballast_analyzer.py`. The script is approximately 450 lines of commented Python. The core descriptor-extraction loop is reproduced below in abridged form.

```
1 import os, trimesh, numpy as np, pandas as pd
2
3 # ----- Four-check quality gate -----
4 def mesh_ok(mesh):
5     return (mesh.is_watertight
6             and mesh.body_count == 1
7             and mesh.volume > 10_000
8             and mesh.volume < 250_000)
```

```

9
10 # ----- Descriptor extraction -----
11 def extract_descriptors(stl_path):
12     m = trimesh.load(stl_path)
13     if not mesh_ok(m):
14         raise ValueError(f"{stl_path}: mesh QC failed")
15
16     V, A = m.volume, m.area
17     ch = m.convex_hull
18     V_ch, A_ch = ch.volume, ch.area
19
20     # Principal dimensions from oriented bounding box
21     obb = m.bounding_box_oriented.extents # [S, I, L]
22     S, I, L = sorted(obb)
23
24     # Sphericity (Wadell, 1932)
25     Psi = (np.pi ** (1/3)) * ((6 * V) ** (2/3)) / A
26
27     # Convexity
28     C = V / V_ch
29
30     # Form descriptors
31     F, E, AR = S/I, I/L, L/S
32     FI = (L + I) / (2 * S)
33
34     # Surface texture
35     T = A / A_ch
36     D_eq = (6 * V / np.pi) ** (1/3)
37
38     return dict(V=V, A=A, D_eq=D_eq, S=S, I=I, L=L,
39                 V_ch=V_ch, A_ch=A_ch, Psi=Psi, C=C,
40                 F=F, E=E, AR=AR, FI=FI, T=T)
41
42 # ----- Pair before & after, write workbook -----
43 def run(before_dir, after_dir, out_xlsx):
44     rows_b, rows_a = [], []
45     for fn in sorted(os.listdir(before_dir)):
46         if not fn.endswith(".stl"):
47             continue
48         d_b = extract_descriptors(os.path.join(before_dir, fn))
49         d_a = extract_descriptors(os.path.join(after_dir, fn))
50         d_b["Particle"] = fn.replace(".stl", "")
51         d_a["Particle"] = fn.replace(".stl", "")
52         rows_b.append(d_b)
53         rows_a.append(d_a)
54
55     df_b = pd.DataFrame(rows_b).set_index("Particle")

```

```
56 df_a = pd.DataFrame(rows_a).set_index("Particle")
57 df_delta = df_a - df_b
58 df_pct = 100 * df_delta / df_b
59
60 with pd.ExcelWriter(out_xlsx) as xw:
61     df_b.to_excel(xw, "Before Test")
62     df_a.to_excel(xw, "After Test")
63     df_delta.to_excel(xw, "Changes (After-Before)")
64     df_pct.to_excel(xw, "Percent Changes")
```

**Listing B.1.** Core extraction logic of `ballast_analyzer.py`.