
GuitarTap

Tap Tone Analysis Report

Jul 17, 2026 at 11:58 AM

Measurement Name:	Plate UMIK-1 3 Tap Swift iPad
Type:	Material (Plate)
Frequency Range:	20.0 Hz – 200.0 Hz
Microphone:	Umik-1 Gain: 18dB · calibrated (7108913)

Frequency Spectrum



Detected Peaks

Frequency	Magnitude	Note	Q Factor	Role
117.2 Hz	-59.4 dB	A#2	40.0	Cross-grain (C)

Gore Target Thickness

2.79 mm

Body: 490 × 368 mm · f_vs = 60 (Classical Top)

GLC (Shear Modulus): 0.359 GPa

Plate Properties

Sample Dimensions

Length: **557.5 mm** Width: **220.5 mm** Thickness: **4.85 mm**

Mass: **208.0 g** Density: **0.349 g/cm³**

fL: **67.2 Hz** fC: **117.2 Hz** fLC: **36.3 Hz**

Speed of Sound (L): **4191 m/s**

Speed of Sound (C): **1143 m/s**

Young's Modulus (L): **6.13 GPa**

Young's Modulus (C): **0.46 GPa**

GLC (Shear Modulus): **0.359 GPa**

Specific Modulus (L): **17.6** (Fair)

Specific Modulus (C): **1.3** (Very Good)

Radiation Ratio (L): **12.0**

Radiation Ratio (C): **3.3**

Cross/Long Ratio: **0.074**
typical: 0.04–0.08

Long/Cross Ratio: **13.4**
typical: 12–25

Overall Quality: **Good**

Three-Tap Measurement Process:

- **1. Longitudinal (L) Tap**
  Hold plate at 22% from one end along the length, near one long edge (not at the width node). Tap center.
- **2. Cross-grain (C) Tap**
  Rotate 90°. Hold plate at 22% from one end along the width, near one short edge (not at the length node). Tap center.
- **3. FLC (Diagonal) Tap**
  Hold plate at the midpoint of one long edge. Tap near the opposite corner (~22% from both the end and the side). Measures shear stiffness.

The strongest peak from each tap is auto-selected.