

**Test Report
on Steel Reinforcing Bars**

Test Report No. : 220712ME248723

Page : 1 of 1

Date of issue : 28-10-2024

Test Method:

Mass per meter, Rebend test and Surface geometry: CS2: 2012 + Amd. 1/2016 + Amd. 2/2018 Cl. 6.1 & 6.2, & 6.5 & 6.7

Tensile test: CS2: 2012 + Amd. 1/2016 + Amd. 2/2018 Cl. 6.1 & 6.4


Sample Details as Supplied by Customer :

Customer	: PWL (GE/2021/25) for CEDD/ NDO	Contract No.	: ND/2019/05
Address	: -	Test Request No.	: CMSTE2490890000-001
Job Title	: Fanling North New Development Area, Phase 1: Fanling Bypass Eastern Section (Shung Him Tong to Kau Lung Hang)	Customer Ref. No.:	: C5-ST-203
Location	: Eastern Section (Shung Him Tong to Kau Lung Hang) Noise Barrier (NB29) at TWSRW	Account No.	: ND/2019/05/01
Sample Description	: Produced in Straight Lengths by Hot Rolling	Stocklist Name	: SW Construction Limited
Nominal Bar Size (mm)	: 25	Bar Pattern Code	: MAL21
Steel Grade	: 500B	Date delivered to Site	: 07/10/2024
Country of Origin	: Malaysia	Means of straightening of coil sample	: -
Class No.	: 2	Steel Manufacturer	:
Batch No.	:	Stocklist Lot No.	: MAL21-13235B
Mass of Test Unit (Tonnes)	:	Cast / Heat No.	: 42-6-8866
Mill Certificate No.	: ASSB-QC-MC-CS-2024-1009 to 2024-1013		


Laboratory Information and Test Result

Date Received	: 14-10-2024	Condition of Sample when Received	: Straight Lengths
Date Tested	: 18-10-2024	Location of Lab	: San Tin Branch Lab
No. of Specimens	: 8	Gauge Length for Tensile Test(mm)	: -
Conditions of Aging Treatment	: -	Test Machine No.	: M-001-6

1. Determination of Mass per meter, Tensile properties & Bend performance

Specimen No.			Mass per meter run		Yield strength (MPa)	Tensile strength (MPa)	Tensile / yield strength ratio	Total elongation at maximum force (%)	Rebend Test
Laboratory	Customer	RFID Tag No./ Electronic Sample ID	Measured (kg/m)	Deviation from nominal mass per (%)					
ME248723/1	S1	SA1135086	3.739	-3.0	584	701	1.20	10.8	-
ME248723/2	S2	SA1135087	3.736	-3.1	568	693	1.22	10.5	-
ME248723/3	S3	SA1135088	3.724	-3.4	573	692	1.21	11.8	-
ME248723/4	S4	SA1135089	3.738	-3.0	576	695	1.21	11.9	-
ME248723/5	S5	SA1135090	3.728	-3.3	575	691	1.20	11.4	-
ME248723/6	S6	SA1135091	3.731	-3.2	573	693	1.21	10.0	-
ME248723/7	S7	SA1135092	-	-	-	-	-	-	Pass
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-

2. Surface Geometry

Specimen No.			Relative Rib Area
Laboratory	Customer	Electronic Sample ID	
ME248723/8	S8	SA1135093	0.088

Remarks

1. All test results relate only to the samples tested, the laboratory has no responsibility on sampling and all the test results apply to the samples as received.

Checked By

ME-R-67 (23-8-2024)

Lau Hon Sum, Sam (Independent Checker)

Approved Signatory :

Chan Fai Ki, Tommy (Contract Manager)

**** End of Report ****