

FAA CORE TEST RESULTS											
Applied Materials & Engineering, Inc. 980 41st Street, Oakland, CA 94608											
(All Cells in Yellow are User Fillable)											
Project Name:	Runway 1R-19L and Taxiway W					Client / Agency:	AtkinsRéalis USA Inc. / SFO				
Lot Number:	2					Location:	GARCO, Santa Clara				
Sublot No.:	4,					Mix Design No.:	15347				
Material Specification:	P401					Batch Plant:	Pleasanton				
Date Sampled:	5/20/26					Date Tested:	5/21/26				
SECTION 1 – CORE HEIGHT MEASUREMENTS (Average of 4 Readings)											
	As Received Height (in)						Trimmed Height / After Cut (in)				
Core ID	Reading 1	Reading 2	Reading 3	Reading 4	Average → Section 2		Reading 1	Reading 2	Reading 3	Reading 4	Average → Section 2
M4	4.08	4.05	4.03	4.06	4.06		3.84	3.87	3.88	3.84	3.86
J4	4.29	4.31	4.25	4.29	4.29		4.08	4.05	4.17	4.15	4.11
Note: M = Mat Core and J = Joint Core											
SECTION 2 – BULK SPECIFIC GRAVITY OF CORES (ASTM D2726)											
Core ID	Core Ht., in. as Received (avg of 4 rdgs)	Core Ht., in. After Cut (avg of 4 rdgs)	Dry Wt, A (g)	Submerged Wt, C (g)	SSD Wt, B (g)	Volume = B - C (cm³)	Bulk Sp. Grav. Gmb = A / B - C	Bulk Density (pcf) Gmb × 62.24	Rice Sp. Grav. Gmm (ASTM D2041)	Percent Absorption = (B - A / B - C) × 100	Percent Compaction = (Gmb / Gmm)×100
M4	4.06	3.86	4054.2	2358.4	4057.8	1699.1	2.386	148.1	2.478	0.2%	96.3%
J4	4.29	4.11	4264.7	2477.9	4270.5	1793.1	2.379	148.1	2.478	0.3%	96.0%
Note: Core ID & heights linked from Section 1. Ref: ASTM D2726											
Tested By:						Reviewed / Approved By:					
Atiqullah Durani						Mohammed Faiyaz					