

FAA CORE TEST RESULTS											
Applied Materials & Engineering, Inc. 980 41st Street, Oakland, CA 94608											
(All Cells in Yellow are User Fillable)											
Project Name:	Runway 1R-19L and Taxiway W					Client / Agency:	AtkinsRéalis USA Inc. / SFO				
Lot Number:	2					Location:	GARCO, Santa Clara				
Sublot No.:	1, 2 & 3					Mix Design No.:	15347				
Material Specification:	P401					Batch Plant:	Pleasanton				
Date Sampled:	5/20/26					Date Tested:	5/21/26				
SECTION 1 – CORE HEIGHT MEASUREMENTS (Average of 4 Readings)											
	As Received Height (in)						Trimmed Height / After Cut (in)				
Core ID	Reading 1	Reading 2	Reading 3	Reading 4	Average → Section 2		Reading 1	Reading 2	Reading 3	Reading 4	Average → Section 2
M1	5.49	5.49	5.48	5.49	5.49		4.09	4.05	4.07	4.05	4.07
M2	4.23	4.25	4.33	4.24	4.26		4.09	4.07	4.00	4.08	4.06
M3	6.80	7.12	6.95	7.08	6.99		4.00	4.03	4.16	4.13	4.08
J1	4.44	4.48	4.44	4.41	4.44		4.06	4.08	4.17	4.11	4.11
J2	5.30	5.80	5.36	5.45	5.48		4.05	4.10	4.10	4.08	4.08
J3	4.01	4.02	4.01	4.02	4.02		3.92	3.83	3.92	3.98	3.91
Note: M = Mat Core and J = Joint Core											
SECTION 2 – BULK SPECIFIC GRAVITY OF CORES (ASTM D2726)											
Core ID	Core Ht., in. as Received (avg of 4 rdgs)	Core Ht., in. After Cut (avg of 4 rdgs)	Dry Wt, A (g)	Submerged Wt, C (g)	SSD Wt, B (g)	Volume = B - C (cm³)	Bulk Sp. Grav. Gmb = A / B - C	Bulk Density (pcf) Gmb × 62.24	Rice Sp. Grav. Gmm (ASTM D2041)	Percent Absorption = (B - A / B - C) × 100	Percent Compaction = (Gmb / Gmm)×100
M1	5.49	4.07	4234.3	2459.2	4237.0	1778.1	2.382	148.1	2.465	0.2%	96.6%
M2	4.26	4.06	4202.4	2435.2	4209.2	1774.1	2.369	147.1	2.474	0.4%	95.8%
M3	6.99	4.08	4259.7	2477.5	4265.1	1788.1	2.383	148.1	2.471	0.3%	96.4%
J1	4.44	4.11	4243.9	2455.4	4252.5	1797.1	2.362	147.1	2.465	0.5%	95.8%
J2	5.48	4.08	4209.0	2435.1	4217.8	1783.1	2.361	147.1	2.474	0.5%	95.4%
J3	4.02	3.91	4021.8	2329.8	4027.6	1698.1	2.369	147.1	2.471	0.3%	95.9%
Note: Core ID & heights linked from Section 1. Ref: ASTM D2726											
Tested By:						Reviewed / Approved By:					
Atiqullah Durani						Mohammed Faiyaz					